




OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL



Area
Direct Strip Mill/Finishing
 Machine Id
NL2 ROUGHER/EDGER LUBE OIL SYSTEM (DSC017) (S/N 1000016877)
 Component
Gear Lube System
 Fluid
ISO 680 (12000 LTR)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.
 Please specify the brand, type, and viscosity of the oil on your next sample.

Wear

All component wear rates are normal.

Contamination

The system cleanliness is acceptable for your target ISO 4406 cleanliness code. The system and fluid cleanliness is acceptable.

Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

SAMPLE INFORMATION

	method	limit/base	current	history1	history2
Sample Number	Client Info		WC0837461	WC0780839	WC0813688
Sample Date	Client Info		26 Sep 2023	08 Aug 2023	21 Jun 2023
Machine Age	hrs	Client Info	0	0	0
Oil Age	hrs	Client Info	0	0	0
Oil Changed	Client Info		N/A	N/A	N/A
Sample Status			NORMAL	NORMAL	NORMAL

WEAR METALS

	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185(m) >150	20	19	18
Chromium	ppm	ASTM D5185(m) >10	0	<1	<1
Nickel	ppm	ASTM D5185(m) >10	<1	<1	<1
Titanium	ppm	ASTM D5185(m)	0	0	0
Silver	ppm	ASTM D5185(m)	<1	0	0
Aluminum	ppm	ASTM D5185(m) >25	<1	<1	0
Lead	ppm	ASTM D5185(m) >100	<1	0	0
Copper	ppm	ASTM D5185(m) >50	<1	<1	<1
Tin	ppm	ASTM D5185(m) >10	0	0	0
Antimony	ppm	ASTM D5185(m) >5	0	0	0
Vanadium	ppm	ASTM D5185(m)	0	0	0
Beryllium	ppm	ASTM D5185(m)	0	0	0
Cadmium	ppm	ASTM D5185(m)	0	0	0

ADDITIVES

	method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185(m)	1	1	1
Barium	ppm	ASTM D5185(m)	<1	0	0
Molybdenum	ppm	ASTM D5185(m)	0	0	0
Manganese	ppm	ASTM D5185(m)	0	<1	<1
Magnesium	ppm	ASTM D5185(m)	0	0	<1
Calcium	ppm	ASTM D5185(m)	<1	1	1
Phosphorus	ppm	ASTM D5185(m)	87	93	98
Zinc	ppm	ASTM D5185(m)	2	2	2
Sulfur	ppm	ASTM D5185(m)	7236	6953	7342
Lithium	ppm	ASTM D5185(m)	<1	<1	<1

CONTAMINANTS

	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185(m) >50	<1	2	<1
Sodium	ppm	ASTM D5185(m)	1	0	<1
Potassium	ppm	ASTM D5185(m) >20	<1	0	<1

FLUID CLEANLINESS

	method	limit/base	current	history1	history2
Particles >4µm	ASTM D7647	>640000	235632	231250	176130
Particles >6µm	ASTM D7647	>160000	38428	35161	36559
Particles >14µm	ASTM D7647	>40000	146	133	197
Particles >21µm	ASTM D7647	>10000	14	16	26
Particles >38µm	ASTM D7647	>2500	0	0	0
Particles >71µm	ASTM D7647	>640	0	0	0
Oil Cleanliness	ISO 4406 (c)	>26/24/22	25/22/14	25/22/14	25/22/15


FLUID DEGRADATION

	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D974*	1.89	1.68	1.96




OIL ANALYSIS REPORT


Particle Trend




Acid Number



Viscosity @ 40°C




Particle Trend






VISUAL	method	limit/base	current	history1	history2
White Metal	scalar	Visual*	NONE	NONE	NONE
Yellow Metal	scalar	Visual*	NONE	NONE	NONE
Precipitate	scalar	Visual*	NONE	NONE	NONE
Silt	scalar	Visual*	NONE	NONE	NONE
Debris	scalar	Visual*	NONE	NONE	NONE
Sand/Dirt	scalar	Visual*	NONE	NONE	NONE
Appearance	scalar	Visual*	NORML	NORML	NORML
Odor	scalar	Visual*	NORML	NORML	NORML
Emulsified Water	scalar	Visual*	>0.1	NEG	NEG
Free Water	scalar	Visual*		NEG	NEG

FLUID PROPERTIES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D7279(m)	680	679	673

SAMPLE IMAGES	method	limit/base	current	history1	history2
---------------	--------	------------	---------	----------	----------



GRAPHS



Laboratory : WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9 **ALGOMA STEEL INC. - STORES DEPT.**
Sample No. : WC0837461 **Received** : 02 Oct 2023 301 WALLACE TERRACE
Lab Number : 02586176 **Diagnosed** : 03 Oct 2023 SAULT STE MARIE, ON
Unique Number : 5655242 **Diagnostician** : Wes Davis CA P6C 1K8
Test Package : IND 2 (Additional Tests: TAN Man)
 Contact: Algoma Reliability
 algomareliability@algoma.com

To discuss this sample report, contact Customer Service at 1-800-268-2131.
 Test denoted (*) outside scope of accreditation, (m) method modified, (e) tested at external lab.
 Validity of results and interpretation are based on the sample and information as supplied.

T: (705)206-1059
 F: (705)945-3585