




OIL ANALYSIS REPORT

Sample Rating Trend

NORMAL



Area
MSE
 Machine Id
41P08-DI-20T
 Component
Reduction Gear
 Fluid
MOBIL SHC 630 (30 LTR)

DIAGNOSIS

Recommendation

Échantillonner de nouveau l'équipement au prochain intervalle de vidange afin d'en surveiller la condition.

Wear

Les taux d'usure de tous les composants sont normaux.

Contamination

Il n'y a aucun indice de contamination dans l'huile.

Fluid Condition

L'état de l'huile est acceptable pour la durée de service.

SAMPLE INFORMATION		method	limit/base	current	history1	history2
Sample Number	Client Info			WC0855435	WC0568331	---
Sample Date	Client Info			26 Sep 2023	03 Jun 2021	---
Machine Age	hrs	Client Info		0	0	---
Oil Age	hrs	Client Info		0	0	---
Oil Changed	Client Info			N/A	N/A	---
Sample Status				NORMAL	NORMAL	---

WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185(m)	>117	2	21	---
Chromium	ppm	ASTM D5185(m)	>2	0	<1	---
Nickel	ppm	ASTM D5185(m)	>2	0	<1	---
Titanium	ppm	ASTM D5185(m)		0	0	---
Silver	ppm	ASTM D5185(m)		<1	<1	---
Aluminum	ppm	ASTM D5185(m)	>11	<1	2	---
Lead	ppm	ASTM D5185(m)	>10	0	2	---
Copper	ppm	ASTM D5185(m)	>55	2	49	---
Tin	ppm	ASTM D5185(m)	>15	0	3	---
Antimony	ppm	ASTM D5185(m)	>5	0	<1	---
Vanadium	ppm	ASTM D5185(m)		0	0	---
Beryllium	ppm	ASTM D5185(m)		0	0	---
Cadmium	ppm	ASTM D5185(m)		0	0	---

ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185(m)		1	6	---
Barium	ppm	ASTM D5185(m)		<1	1	---
Molybdenum	ppm	ASTM D5185(m)		0	0	---
Manganese	ppm	ASTM D5185(m)		0	<1	---
Magnesium	ppm	ASTM D5185(m)		0	<1	---
Calcium	ppm	ASTM D5185(m)		<1	<1	---
Phosphorus	ppm	ASTM D5185(m)		415	112	---
Zinc	ppm	ASTM D5185(m)		1	9	---
Sulfur	ppm	ASTM D5185(m)		194	2080	---
Lithium	ppm	ASTM D5185(m)		<1	2	---


CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185(m)	>50	27	52	---
Sodium	ppm	ASTM D5185(m)		<1	<1	---
Potassium	ppm	ASTM D5185(m)	>20	0	<1	---

INFRA-RED		method	limit/base	current	history1	history2
Soot %	%	ASTM D7844*		0	0	---
Nitration	Abs/cm	ASTM D7624*		4.5	3.6	---
Sulfation	Abs/.1mm	ASTM D7415*		13.2	36.7	---

FLUID DEGRADATION		method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	ASTM D7414*		5.0	43.4	---



OIL ANALYSIS REPORT






VISUAL	method	limit/base	current	history1	history2
White Metal	scalar	Visual*	NONE	NONE	---
Yellow Metal	scalar	Visual*	NONE	NONE	---
Precipitate	scalar	Visual*	NONE	NONE	---
Silt	scalar	Visual*	NONE	NONE	---
Debris	scalar	Visual*	NONE	VLITE	LTMOD
Sand/Dirt	scalar	Visual*	NONE	NONE	---
Appearance	scalar	Visual*	NORML	NORML	---
Odor	scalar	Visual*	NORML	NORML	---
Emulsified Water	scalar	Visual*	>0.1	NEG	---
Free Water	scalar	Visual*		NEG	---

FLUID PROPERTIES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D7279(m)	217.7	218	225

SAMPLE IMAGES	method	limit/base	current	history1	history2
---------------	--------	------------	---------	----------	----------

Color			no image
Bottom			no image

GRAPHS



Laboratory : WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9
Sample No. : WC0855435 **Received** : 03 Oct 2023
Lab Number : 02586523 **Diagnosed** : 03 Oct 2023
Unique Number : 5655589 **Diagnostician** : Wes Davis
Test Package : IND 1 (Additional Tests: FT-IR)

To discuss this sample report, contact Customer Service at 1-800-268-2131.
 Test denoted (*) outside scope of accreditation, (m) method modified, (e) tested at external lab.
 Validity of results and interpretation are based on the sample and information as supplied.

RTA - UGB
 C.P. 900
 Ville de la Baie, QC
 CA G7B 4G9
 Contact: Alcan Epc
 mathieu.tremblay2@riotinto.com
 T: (418)697-9568
 F: (418)697-9550