




OIL ANALYSIS REPORT

Sample Rating Trend

NORMAL



Area
BOF/SCRAP YARD
 Machine Id
A - 2 Yard G/B Scrap Box Transfer Car Drive G/B
 Component
Gearbox
 Fluid
SHELL OMALA 220 (20 GAL)



DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

The system cleanliness is acceptable for your target ISO 4406 cleanliness code. The system and fluid cleanliness is acceptable.

Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

SAMPLE INFORMATION

	method	limit/base	current	history1	history2
Sample Number	Client Info		WC0866326	WC02273776	WC22131636
Sample Date	Client Info		04 Oct 2023	21 Apr 2019	12 Sep 2018
Machine Age	hrs	Client Info	0	0	0
Oil Age	hrs	Client Info	0	0	0
Oil Changed	Client Info		N/A	N/A	N/A
Sample Status			NORMAL	NORMAL	ATTENTION

WEAR METALS

	method	limit/base	current	history1	history2
PQ	ASTM D8184*	>DFLT	41	58	81
Iron	ppm	ASTM D5185(m) >200	71	59	121
Chromium	ppm	ASTM D5185(m) >15	<1	1	12
Nickel	ppm	ASTM D5185(m) >15	<1	<1	<1
Titanium	ppm	ASTM D5185(m)	0	0	<1
Silver	ppm	ASTM D5185(m)	<1	0	0
Aluminum	ppm	ASTM D5185(m) >25	1	1	5
Lead	ppm	ASTM D5185(m) >100	8	10	20
Copper	ppm	ASTM D5185(m) >200	<1	<1	<1
Tin	ppm	ASTM D5185(m) >25	0	0	0
Antimony	ppm	ASTM D5185(m) >5	0	0	0
Vanadium	ppm	ASTM D5185(m)	0	0	0
Beryllium	ppm	ASTM D5185(m)	0	0	0
Cadmium	ppm	ASTM D5185(m)	0	0	<1

ADDITIVES

	method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185(m) 4.4	1	1	12
Barium	ppm	ASTM D5185(m) 0.0	<1	0	<1
Molybdenum	ppm	ASTM D5185(m) 0	0	0	0
Manganese	ppm	ASTM D5185(m)	<1	1	3
Magnesium	ppm	ASTM D5185(m) 0	3	3	9
Calcium	ppm	ASTM D5185(m) 0	10	10	29
Phosphorus	ppm	ASTM D5185(m) 215	271	292	▲ 525
Zinc	ppm	ASTM D5185(m) 0	4	6	▲ 29
Sulfur	ppm	ASTM D5185(m) 7039	9638	10056	10022
Lithium	ppm	ASTM D5185(m)	<1	0	<1

CONTAMINANTS






	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185(m) >50	5	5	13
Sodium	ppm	ASTM D5185(m)	1	1	8
Potassium	ppm	ASTM D5185(m) >20	0	<1	5

FLUID CLEANLINESS

	method	limit/base	current	history1	history2
Particles >4µm	ASTM D7647		223762	170079	196160
Particles >6µm	ASTM D7647	>10240000	117483	83067	123930
Particles >14µm	ASTM D7647	>10240000	6120	2429	3216
Particles >21µm	ASTM D7647	>2560000	1628	463	370
Particles >38µm	ASTM D7647	>640000	70	2	4
Particles >71µm	ASTM D7647	>160000	2	0	0
Oil Cleanliness	ISO 4406 (c)	>--/30/30	25/24/20	25/24/18	25/24/19



OIL ANALYSIS REPORT




FLUID DEGRADATION		method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D974*		0.42	0.455	0.88






VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	Visual*	NONE	NONE	NONE	NONE
Yellow Metal	scalar	Visual*	NONE	NONE	NONE	NONE
Precipitate	scalar	Visual*	NONE	NONE	NONE	NONE
Silt	scalar	Visual*	NONE	NONE	NONE	NONE
Debris	scalar	Visual*	NONE	NONE	VLITE	LIGHT
Sand/Dirt	scalar	Visual*	NONE	LIGHT	NONE	NONE
Appearance	scalar	Visual*	NORML	NORML	NORML	NORML
Odor	scalar	Visual*	NORML	NORML	NORML	NORML
Emulsified Water	scalar	Visual*	>5	NEG	NEG	NEG
Free Water	scalar	Visual*		NEG	NEG	NEG

FLUID PROPERTIES		method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D7279(m)	220	248	248	215

SAMPLE IMAGES



GRAPHS



Laboratory : WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9 **STELCO - BOSC - Basic Oxygen Slab Caster**
Sample No. : WC0866326 **Received** : 04 Oct 2023 2330 Regional Road #3, Door: BOSC8
Lab Number : 02586909 **Diagnosed** : 05 Oct 2023 NANTICOKE, ON
Unique Number : 5655975 **Diagnostician** : Wes Davis CA N0A 1L0
Test Package : IND 2 (Additional Tests: PQ, PrtCount, TAN Man)

To discuss this sample report, contact Customer Service at 1-800-268-2131.
 Test denoted (*) outside scope of accreditation, (m) method modified, (e) tested at external lab.
 Validity of results and interpretation are based on the sample and information as supplied.

Contact: Tom Walden
 Thomas.Walden@stelco.com
 T: (519)587-4541
 F: (519)587-7702