




OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL



Machine Id
International 52435

Component
Diesel Engine

Fluid
SUPREME 15W-40 4-STROKE MOTORCYCLE OIL (40 LTR)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The condition of the oil is acceptable for the time in service.

SAMPLE INFORMATION

	method	limit/base	current	history1	history2
Sample Number	Client Info		WC0850751	---	---
Sample Date	Client Info		21 Aug 2023	---	---
Machine Age	kms	Client Info	855946	---	---
Oil Age	kms	Client Info	16667	---	---
Oil Changed	Client Info		Changed	---	---
Sample Status			NORMAL	---	---

CONTAMINATION

	method	limit/base	current	history1	history2
Fuel	WC Method	>3.0	<1.0	---	---
Glycol	WC Method		NEG	---	---

WEAR METALS

	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185(m) >165	79	---	---
Chromium	ppm	ASTM D5185(m) >5	<1	---	---
Nickel	ppm	ASTM D5185(m) >4	0	---	---
Titanium	ppm	ASTM D5185(m) >2	0	---	---
Silver	ppm	ASTM D5185(m) >2	<1	---	---
Aluminum	ppm	ASTM D5185(m) >20	3	---	---
Lead	ppm	ASTM D5185(m) >150	6	---	---
Copper	ppm	ASTM D5185(m) >90	7	---	---
Tin	ppm	ASTM D5185(m) >5	0	---	---
Antimony	ppm	ASTM D5185(m)	0	---	---
Vanadium	ppm	ASTM D5185(m)	0	---	---
Beryllium	ppm	ASTM D5185(m)	0	---	---
Cadmium	ppm	ASTM D5185(m)	0	---	---

ADDITIVES

	method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185(m) 1	<1	---	---
Barium	ppm	ASTM D5185(m) 0	<1	---	---
Molybdenum	ppm	ASTM D5185(m) 60	64	---	---
Manganese	ppm	ASTM D5185(m) 0	<1	---	---
Magnesium	ppm	ASTM D5185(m) 1010	1017	---	---
Calcium	ppm	ASTM D5185(m) 1070	1104	---	---
Phosphorus	ppm	ASTM D5185(m) 1150	1054	---	---
Zinc	ppm	ASTM D5185(m) 1270	1232	---	---
Sulfur	ppm	ASTM D5185(m) 2060	2527	---	---
Lithium	ppm	ASTM D5185(m)	<1	---	---

CONTAMINANTS

	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185(m) >35	14	---	---
Sodium	ppm	ASTM D5185(m)	3	---	---
Potassium	ppm	ASTM D5185(m) >20	0	---	---

INFRA-RED


	method	limit/base	current	history1	history2
Soot %	%	ASTM D7844* >7.5	0.8	---	---
Nitration	Abs/cm	ASTM D7624* >20	10.7	---	---
Sulfation	Abs/.1mm	ASTM D7415* >30	22.0	---	---

FLUID DEGRADATION

	method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	ASTM D7414* >25	17.8	---	---











OIL ANALYSIS REPORT



VISUAL	method	limit/base	current	history1	history2
Emulsified Water	scalar	Visual*	>0.2	NEG	---
Free Water	scalar	Visual*		NEG	---

FLUID PROPERTIES	method	limit/base	current	history1	history2
Visc @ 100°C	cSt	ASTM D7279(m)	15.6	14.2	---

GRAPHS



Laboratory : WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9
Sample No. : WC0850751 **Received** : 06 Oct 2023
Lab Number : 02587750 **Diagnosed** : 06 Oct 2023
Unique Number : 5656816 **Diagnostician** : Wes Davis
Test Package : MOB 1

Bruce Orford
 950 Perryville Rd East
 Spring Bay, ON
 CA P0P 2B0
 Contact: Bruce Orford
 bruceorfordfarms@gmail.com
 T: (705)920-1511
 F:

To discuss this sample report, contact Customer Service at 1-800-268-2131.
 Test denoted (*) outside scope of accreditation, (m) method modified, (e) tested at external lab.
 Validity of results and interpretation are based on the sample and information as supplied.