

# **OIL ANALYSIS REPORT**

### Area Goodyear - G04000 Machine Id A2310051

Component Hydraulic System Fluid AW HYDRAULIC OIL ISO 68 (--- GAL)

#### DIAGNOSIS

Recommendation


This is a baseline read-out on the submitted sample.

## Wear

Copper and iron ppm levels are noted.

Contamination {not applicable}

Fluid Condition {not applicable}



Sample Rating Trend



NORMAL

SAMPLE INFORM	IATION	method	limit/base	current	history1	history2
Batch #		Client Info		2023 10 0090		
Machine ID		Client Info		A2310051		
Department		Client Info		Production		
Sample From		Client Info		Machine		
Production Stage		Client Info		Initial		
Sent to WC		Client Info		10/10/2023		
Sample Number		Client Info		E30000499		
Sample Date		Client Info		10 Oct 2023		
Machine Age	hrs	Client Info		0		
Oil Age	hrs	Client Info		0		
Oil Changed		Client Info		N/A		
Sample Status				NORMAL		
WEAR METALS		method	limit/base	current	history1	history2
PQ		ASTM D8184*		0		
Iron	ppm	ASTM D5185(m)	>20	44		
Chromium	ppm	ASTM D5185(m)	>10	<1		
Nickel	ppm	ASTM D5185(m)	>10	2		
Titanium	ppm	ASTM D5185(m)		0		
Silver	ppm	ASTM D5185(m)		<1		
Aluminum	ppm	ASTM D5185(m)	>10	6		
Lead	ppm	ASTM D5185(m)	>20	17		
Copper	ppm	ASTM D5185(m)	>20	125		
Tin	ppm	ASTM D5185(m)	>10	<1		
Antimony	ppm	ASTM D5185(m)		0		
Vanadium	ppm	ASTM D5185(m)		0		
Beryllium	ppm	ASTM D5185(m)		0		
Cadmium	ppm	ASTM D5185(m)		0		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185(m)	5	2		
Barium	ppm	ASTM D5185(m)	5	<1		
Molybdenum	ppm	ASTM D5185(m)	5	0		
Manganese	ppm	ASTM D5185(m)		<1		
Magnesium	ppm	ASTM D5185(m)	25	7		
Calcium	ppm	ASTM D5185(m)	200	48		
Phosphorus	ppm	ASTM D5185(m)	300	667		
Zinc	ppm	ASTM D5185(m)	370	543		
Sulfur	ppm	ASTM D5185(m)	2500	2199		
Lithium	ppm	ASTM D5185(m)		<1		
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185(m)	>15	14		
Sodium	ppm	ASTM D5185(m)		1		
Potassium	ppm	ASTM D5185(m)	>20	<1		



# **OIL ANALYSIS REPORT**



VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	Visual*	NONE	NONE		
Yellow Metal	scalar	Visual*	NONE	NONE		
Precipitate	scalar	Visual*	NONE	LIGHT		
Silt	scalar	Visual*	NONE	NONE		
Debris	scalar	Visual*	NONE	NONE		
Sand/Dirt	scalar	Visual*	NONE	NONE		
Appearance	scalar	Visual*	NORML	MILKY		
Odor	scalar	Visual*	NORML	NORML		
SAMPLE IMAGES	5	method	limit/base	current	history1	history2
Color					no image	no image
Bottom					no image	no image
GRAPHS						
Ferrous Alloys				PQ		
iron			220	TE		

