


Area
[R1-22768]
 Machine Id
RG6090L135432
 Component
Diesel Fuel
 Fluid
DISEL FUEL No. 2 (--- GAL)



DIAGNOSIS

Recommendation

Laboratory test indicate that this fuel is suitable for use and meets all test requirements. Resample at the next service interval to monitor.

Corrosion

{not applicable}

Contaminants

The system cleanliness is acceptable for your target ISO 4406 cleanliness code. The water content is negligible. There is no indication of any contamination in the diesel fuel.

Fuel Condition

All laboratory tests indicate that this sample meets specifications for No.2 diesel fuel, low sulfur (US EPA/CGSB-3.517-3 type B).

SAMPLE INFORMATION		method	limit/base	current	history1	history2
Sample Number	Client Info			VPA060018	---	---
Sample Date	Client Info			11 Oct 2023	---	---
Machine Age	hrs	Client Info		0	---	---
Sample Status				NORMAL	---	---

PHYSICAL PROPERTIES		method	limit/base	current	history1	history2
Specific Gravity		ASTM D1298*	0.850	0.833	---	---
Fuel Color	text	Visual Screen*	YELLOW	Orang	---	---
Visc @ 40°C	cSt	ASTM D7279(m)	4.1	2.4	---	---
Pensky-Martens Flash Point	°C	ASTM D7215*	40	57.5	---	---

SULFUR CONTENT		method	limit/base	current	history1	history2
Sulfur	ppm	ASTM D5185(m)		8	---	---






DISTILLATION		method	limit/base	current	history1	history2
Initial Boiling Point	°C	ASTM D2887*	174	166	---	---
5% Distillation Point	°C	ASTM D2887*		187	---	---
10% Distill Point	°C	ASTM D2887*	186	196	---	---
15% Distillation Point	°C	ASTM D2887*		204	---	---
20% Distill Point	°C	ASTM D2887*	206	212	---	---
30% Distill Point	°C	ASTM D2887*	226	229	---	---
40% Distill Point	°C	ASTM D2887*	245	245	---	---
50% Distill Point	°C	ASTM D2887*	260	261	---	---
60% Distill Point	°C	ASTM D2887*	272	275	---	---
70% Distill Point	°C	ASTM D2887*	285	289	---	---
80% Distill Point	°C	ASTM D2887*	315	304	---	---
85% Distillation Point	°C	ASTM D2887*		314	---	---
90% Distill Point	°C	ASTM D2887*	360	324	---	---
95% Distillation Point	°C	ASTM D2887*		339	---	---
Final Boiling Point	°C	ASTM D2887*	>360	369	---	---

IGNITION QUALITY		method	limit/base	current	history1	history2
API Gravity		ASTM D1298*	35.0	38	---	---
Cetane Index		ASTM D4737*	<40.0	51	---	---

CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185(m)	<1.0	0	---	---
Sodium	ppm	ASTM D5185(m)	<0.1	0	---	---
Potassium	ppm	ASTM D5185(m)	<0.1	<1	---	---
Water	%	ASTM D6304*	<0.05	0.003	---	---
ppm Water	ppm	ASTM D6304*	<500	35.0	---	---

FLUID CLEANLINESS		method	limit/base	current	history1	history2
Particles >4µm		ASTM D7647	>2500	1084	---	---
Particles >6µm		ASTM D7647	>640	295	---	---
Particles >14µm		ASTM D7647	>80	20	---	---
Particles >21µm		ASTM D7647	>20	5	---	---
Particles >38µm		ASTM D7647	>4	0	---	---
Particles >71µm		ASTM D7647	>3	0	---	---
Oil Cleanliness		ISO 4406 (c)	>18/16/13	17/15/11	---	---




FUEL REPORT



HEAVY METALS	method	limit/base	current	history1	history2
Aluminum	ppm	ASTM D5185(m)	<0.1	0	---
Nickel	ppm	ASTM D5185(m)	<0.1	0	---
Lead	ppm	ASTM D5185(m)	<0.1	0	---
Vanadium	ppm	ASTM D5185(m)	<0.1	0	---
Iron	ppm	ASTM D5185(m)	<0.1	<1	---
Calcium	ppm	ASTM D5185(m)	<0.1	0	---
Magnesium	ppm	ASTM D5185(m)	<0.1	0	---
Phosphorus	ppm	ASTM D5185(m)	<0.1	0	---
Zinc	ppm	ASTM D5185(m)	<0.1	0	---

SAMPLE IMAGES	method	limit/base	current	history1	history2
Color				no image	no image
Bottom				no image	no image

GRAPHS



Laboratory : WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9
Sample No. : VPA060018
Lab Number : 02590428
Unique Number : 5659494
Test Package : FUEL (Additional Tests: CC Flash, GC-PercFuel, PrtCount)

CULLEN DIESEL POWER - 695335
 9300 192 ST
 SURREY, BC
 CA V4N 3R8
 Contact: Venu Iyer
 vji@cullendiesel.com
 T: (604)455-2207
 F:

To discuss this sample report, contact Customer Service at 1-800-268-2131.
 Test denoted (*) outside scope of accreditation, (m) method modified, (e) tested at external lab.
 Validity of results and interpretation are based on the sample and information as supplied.