OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL

Area
[412498400]
Machine Id
2260 (GARAGE HOTSY) (S/N 15-GTOHP687)
Component
Pump
Fluid
TOTAL FINA NEVASTANE FG AW 68 (--- GAL)

DIAGNOSIS

Recommendation
Resample at the next service interval to monitor. NOTE: Please provide information regarding reservoir capacity, filter type and micron rating with next sample.

Wear
All component wear rates are normal.

Contamination
There is no indication of any contamination in the oil.

Fluid Condition
The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

SAMPLE INFORMATION		method	limit/base	current	history1	history2
Sample Number		Client Info		**WC0848523**	WC0728033	WC0696293
Sample Date		Client Info		**25 Sep 2023**	03 Aug 2022	08 May 2022
Machine Age	hrs	Client Info		**0**	0	0
Oil Age	hrs	Client Info		**0**	0	0
Oil Changed		Client Info		**N/A**	N/A	N/A
Sample Status				**NORMAL**	NORMAL	NORMAL

WEAR METALS		method	limit/base	current	history1	history2
PQ		ASTM D8184*		**0**	0	0
Iron	ppm	ASTM D5185(m)	>90	**4**	5	5
Chromium	ppm	ASTM D5185(m)	>5	**0**	0	0
Nickel	ppm	ASTM D5185(m)	>5	**<1**	<1	<1
Titanium	ppm	ASTM D5185(m)	>3	**0**	0	0
Silver	ppm	ASTM D5185(m)	>3	**<1**	0	0
Aluminum	ppm	ASTM D5185(m)	>7	**0**	0	<1
Lead	ppm	ASTM D5185(m)	>12	**<1**	<1	<1
Copper	ppm	ASTM D5185(m)	>30	**4**	5	5
Tin	ppm	ASTM D5185(m)	>9	**0**	0	<1
Antimony	ppm	ASTM D5185(m)		**0**	0	0
Vanadium	ppm	ASTM D5185(m)		**0**	0	0
Beryllium	ppm	ASTM D5185(m)		**0**	0	0
Cadmium	ppm	ASTM D5185(m)		**0**	0	0

ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185(m)		**<1**	<1	<1
Barium	ppm	ASTM D5185(m)		**0**	0	0
Molybdenum	ppm	ASTM D5185(m)		**0**	0	0
Manganese	ppm	ASTM D5185(m)		**0**	<1	0
Magnesium	ppm	ASTM D5185(m)		**0**	1	<1
Calcium	ppm	ASTM D5185(m)		**<1**	1	2
Phosphorus	ppm	ASTM D5185(m)		**185**	168	181
Zinc	ppm	ASTM D5185(m)		**19**	22	23
Sulfur	ppm	ASTM D5185(m)		**271**	361	349
Lithium	ppm	ASTM D5185(m)		**<1**	<1	<1

CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185(m)	>60	**2**	2	2
Sodium	ppm	ASTM D5185(m)		**<1**	<1	<1
Potassium	ppm	ASTM D5185(m)	>20	**<1**	<1	<1

FLUID DEGRADATION		method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D974*		**0.45**	0.41	0.34

OIL ANALYSIS REPORT







VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	Visual*	NONE	**NONE**	NONE	NONE
Yellow Metal	scalar	Visual*	NONE	**NONE**	NONE	NONE
Precipitate	scalar	Visual*	NONE	**NONE**	NONE	NONE
Silt	scalar	Visual*	NONE	**NONE**	NONE	NONE
Debris	scalar	Visual*	NONE	**NONE**	NONE	NONE
Sand/Dirt	scalar	Visual*	NONE	**NONE**	NONE	NONE
Appearance	scalar	Visual*	NORML	**NORML**	NORML	NORML
Odor	scalar	Visual*	NORML	**NORML**	NORML	NORML
Emulsified Water	scalar	Visual*	>.1	**NEG**	NEG	NEG
Free Water	scalar	Visual*		**NEG**	NEG	NEG

FLUID PROPERTIES		method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D7279(m)	68	**63.1**	62.9	63.3

SAMPLE IMAGES	method	limit/base	current	history1	history2
Color					
Bottom					

GRAPHS











ISO 17025:2017 Accredited Laboratory

Laboratory : WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9
Sample No. : WC0848523 **Received** : 24 Oct 2023
Lab Number : 02591396 **Diagnosed** : 25 Oct 2023
Unique Number : 5668475 **Diagnostician** : Wes Davis
Test Package : IND 2 (Additional Tests: TAN Man)

To discuss this sample report, contact Customer Service at 1-800-268-2131.
Test denoted (*) outside scope of accreditation, (m) method modified, (e) tested at external lab.
Validity of results and interpretation are based on the sample and information as supplied.

Cargill Meat Solutions
165 Dunlop Drive
Guelph, ON
CA N1L 1P4
Contact: Jakub Posluszny
jakub_posluszny@cargill.com
T: (519)823-5200
F: (519)823-5893