

OIL ANALYSIS REPORT

Sample Rating Trend



Machine Id MANITOU 732 FOR411 Component

Rear Differential Fluid ESSO HYDRAUL 56 (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.


Fluid Condition

The condition of the oil is acceptable for the time in service.

SAMPLE INFORM	IATION	method	limit/base	current	history1	history2
Sample Number		Client Info		WC0861403		
Sample Date		Client Info		21 Oct 2023		
Machine Age	hrs	Client Info		9954		
Oil Age	hrs	Client Info		0		
Oil Changed		Client Info		Not Changd		
Sample Status				NORMAL		
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185(m)	>500	111		
Chromium	ppm	ASTM D5185(m)	>10	<1		
Nickel	ppm	ASTM D5185(m)	>10	<1		
Titanium	ppm	ASTM D5185(m)		0		
Silver	ppm	ASTM D5185(m)		<1		
Aluminum	ppm	ASTM D5185(m)	>25	1		
Lead	ppm	ASTM D5185(m)	>25	0		
Copper	ppm	ASTM D5185(m)	>100	<1		
Tin	ppm	ASTM D5185(m)	>10	0		
Antimony	ppm	ASTM D5185(m)	>5	0		
Vanadium	ppm	ASTM D5185(m)		0		
Beryllium	ppm	ASTM D5185(m)		0		
Cadmium	ppm	ASTM D5185(m)		0		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185(m)		92		
Barium	ppm	ASTM D5185(m)		<1		
Molybdenum	ppm	ASTM D5185(m)		0		
Manganese	ppm	ASTM D5185(m)		<1		
Magnesium	ppm	ASTM D5185(m)		12		
Calcium	ppm	ASTM D5185(m)		3102		
Phosphorus	ppm	ASTM D5185(m)		1068		
Zinc	ppm	ASTM D5185(m)		1258		
Sulfur	ppm	ASTM D5185(m)		3407		
Lithium		ASTM D5185(m)		<1		
	ppm	ASTIVI D3103(III)		<1		
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185(m)	>75	14		
Sodium	ppm	ASTM D5185(m)		7		
Potassium	ppm	ASTM D5185(m)	>20	3		
VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	Visual*	NONE	NONE		
Yellow Metal	scalar	Visual*	NONE	NONE		
Precipitate	scalar	Visual*	NONE	NONE		
Silt	scalar	Visual*	NONE	NONE		
Debris	scalar	Visual*	NONE	NONE		
Sand/Dirt	scalar	Visual*	NONE	NONE		
Appearance	scalar	Visual*	NORML	NORML		
Odor	scalar	Visual*	NORML	NORML		
Emulsified Water	scalar	Visual*	>.2	NEG		
Free Water	scalar	Visual*		NEG		
:36:07) Rev: 1			Co	ntact/Location:	Mitch Lamontag	ne - KIR370KIR



OIL ANALYSIS REPORT



2	FLUID PROPERTIES	method limit/base	current	history1	history2
	Visc @ 40°C cSt	ASTM D7279(m) 53	48.1		
	SAMPLE IMAGES	method limit/base	current	history1	history2
23	Color			no image	no image
0421/23	Bottom			no image	no image
	GRAPHS				
	Iron (ppm) 2000 1500 Severe 1000	120 100 80 長 60	- Gevere		
Là	500 - Abnormal	40 20 EZ1(770	Abnormal		0et21/23
	Aluminum (ppm)	30 	Chromium (pp	m)	0 - -
	40 40 20 0	ي الم الم الم الم الم الم الم الم الم	- Abnormal		
	Copper (ppm)	821,1229 0	Silicon (ppm)		0ct21/23
E.	200 - Severe 150 - Abnormal	200 150 100			
	50	004521/23			0ct21/23
	Viscosity @ 40°C Abnormal		Additives		
	© 50 - 	2500 2000 1500		J	
	0dd21/23	1000 27/733 00471/73	0ct21/23		0ct21/23
CALLA ISO 17025:2017 Accredited Laboratory Laboratory Unique Number Test Package	: WC0861403 Rece : 02592262 Diagr : 5669341 Diagr : MOB 1	nosed : 26 Oct 2023 nostician : Wes Davis	1350 Gove	ernment Rd. W, MA Kirk Contact: Mitc	land Lake, ON CA P2N 3J1 h Lamontagne
To discuss this sample report, of Test denoted (*) outside scope Validity of results and interpreta	of accreditation, (m) method	d modified, (e) tested at extern	nal lab.		ts@agnicoeagle.com (705)567-5208 (705)567-5221

Contact/Location: Mitch Lamontagne - KIR370KIR