



OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL



Machine Id
2355
 Component
Natural Gas Engine
 Fluid
NOT GIVEN (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor. Please specify the component make and model with your next sample. Please specify the brand, type, and viscosity of the oil on your next sample.

Wear

Metal levels are typical for a new component breaking in.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The condition of the oil is acceptable for the time in service.

SAMPLE INFORMATION

	method	limit/base	current	history1	history2
Sample Number	Client Info		WC0849837	---	---
Sample Date	Client Info		23 Oct 2023	---	---
Machine Age	kms	Client Info	11893	---	---
Oil Age	kms	Client Info	0	---	---
Oil Changed	Client Info		N/A	---	---
Sample Status			NORMAL	---	---

WEAR METALS

	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185(m) >50	40	---	---
Chromium	ppm	ASTM D5185(m) >4	<1	---	---
Nickel	ppm	ASTM D5185(m) >2	<1	---	---
Titanium	ppm	ASTM D5185(m)	0	---	---
Silver	ppm	ASTM D5185(m) >3	<1	---	---
Aluminum	ppm	ASTM D5185(m) >9	3	---	---
Lead	ppm	ASTM D5185(m) >30	1	---	---
Copper	ppm	ASTM D5185(m) >35	15	---	---
Tin	ppm	ASTM D5185(m) >4	1	---	---
Antimony	ppm	ASTM D5185(m)	0	---	---
Vanadium	ppm	ASTM D5185(m)	0	---	---
Beryllium	ppm	ASTM D5185(m)	0	---	---
Cadmium	ppm	ASTM D5185(m)	0	---	---

ADDITIVES

	method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185(m)	11	---	---
Barium	ppm	ASTM D5185(m)	2	---	---
Molybdenum	ppm	ASTM D5185(m)	96	---	---
Manganese	ppm	ASTM D5185(m)	10	---	---
Magnesium	ppm	ASTM D5185(m)	591	---	---
Calcium	ppm	ASTM D5185(m)	1173	---	---
Phosphorus	ppm	ASTM D5185(m)	540	---	---
Zinc	ppm	ASTM D5185(m)	605	---	---
Sulfur	ppm	ASTM D5185(m)	1821	---	---
Lithium	ppm	ASTM D5185(m)	<1	---	---

CONTAMINANTS

	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185(m) >+100	39	---	---
Sodium	ppm	ASTM D5185(m)	3	---	---
Potassium	ppm	ASTM D5185(m) >20	1	---	---

INFRA-RED

	method	limit/base	current	history1	history2
Soot %	%	ASTM D7844*	0	---	---
Nitration	Abs/cm	ASTM D7624*	>20	8.6	---
Sulfation	Abs/.1mm	ASTM D7415*	>30	20.1	---

FLUID DEGRADATION


	method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	ASTM D7414*	>25	15.1	---

VISUAL

	method	limit/base	current	history1	history2
Emulsified Water	scalar	Visual*	>0.1	NEG	---
Free Water	scalar	Visual*		NEG	---











OIL ANALYSIS REPORT



FLUID PROPERTIES		method	limit/base	current	history1	history2
Visc @ 100°C	cSt	ASTM D7279(m)		13.3	---	---

GRAPHS



Laboratory : WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9
 Sample No. : WC0849837 Received : 27 Oct 2023
 Lab Number : 02592315 Diagnosed : 27 Oct 2023
 Unique Number : 5669394 Diagnostician : Wes Davis
 Test Package : MOB 1

CITY OF HAMILTON
 2200 UPPER JAMES., MOUNTAIN TRANSIT STOREROOM
 MOUNT HOPE, ON
 CA L0R 1W0
 Contact: Ron Skinner
 ron.skinner@hamilton.ca

To discuss this sample report, contact Customer Service at 1-800-268-2131.
 Test denoted (*) outside scope of accreditation, (m) method modified, (e) tested at external lab.
 Validity of results and interpretation are based on the sample and information as supplied.

T:
 F: (905)679-4502