




COOLANT REPORT

Sample Rating Trend

NORMAL



Area
Power Generation
 Machine Id
V837270 STANDBY POWER GENERATION 4160B PACKAGE
 Component
Coolant
 Fluid
EXTENDED LIFE COOLANT (--- GAL)

DIAGNOSIS

Recommendation

The fluid is suitable for further service. Resample at the next service interval to monitor.

Corrosion

All metal levels are normal indicating no corrosion in the cooling system.

Contaminants

There is no indication of any contamination in the coolant.

Coolant Condition

The nitrite level is acceptable. The pH level of this fluid is within the acceptable limits. The reserve alkalinity of this fluid is acceptable.

SAMPLE INFORMATION		method	limit/base	current	history1	history2
Sample Number	Client Info			PP13927504	PP13854055	PP13819713
Sample Date	Client Info			11 Nov 2023	14 Apr 2023	20 Sep 2022
Machine Age	hrs	Client Info		0	0	0
Oil Age	hrs	Client Info		0	0	0
Oil Changed	Client Info			N/A	N/A	N/A
Sample Status				NORMAL	NORMAL	SEVERE

PHYSICAL TEST RESULTS		method	limit/base	current	history1	history2
Specific Gravity	ASTM D1298*			1.065	1.065	1.064
pH	Scale 0-14	ASTM D1287*	9.0	8.30	8.55	8.82
Nitrites	ppm	Alcan Test Kit*		1080	800	600
Reserve Alkalinity	Scale 0-20	ASTM D1121*		2.0	1.8	5.2
Percentage Glycol	%	ASTM D3321*	50	48.3	47.8	47.2
Freezing Point	°C	ASTM D3321*	-40	-31	-28	-28
Carboxylate				---	---	---


CORROSION INHIBITORS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185(m)		23	25	23
Phosphorus	ppm	ASTM D5185(m)		12	10	11
Boron	ppm	ASTM D5185(m)		53	78	96
Molybdenum	ppm	ASTM D5185(m)		148	185	187

CORROSION		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185(m)	>15	0	2	2
Aluminum	ppm	ASTM D5185(m)	>10	<1	2	2
Copper	ppm	ASTM D5185(m)	>10	0	2	6
Lead	ppm	ASTM D5185(m)	>10	0	0	0
Tin	ppm	ASTM D5185(m)	>10	0	0	<1
Silver	ppm	ASTM D5185(m)	>10	<1	<1	<1
Zinc	ppm	ASTM D5185(m)		0	1	2

CARRIER SALTS		method	limit/base	current	history1	history2
Sodium	ppm	ASTM D5185(m)		5152	2835	2976
Potassium	ppm	ASTM D5185(m)		6370	2646	2786








SCALE POTENTIAL		method	limit/base	current	history1	history2
Calcium	ppm	ASTM D5185(m)	>100	6	6	9
Magnesium	ppm	ASTM D5185(m)	>40	3	5	6
Hardness	mg/L CaCO3	In-house*	<75	24	37	49

VISUAL		method	limit/base	current	history1	history2
Coolant Color	Visual*	Orange/R		Red	Red	Orange
Coolant Appearance	Visual*	Clear		Clear	Clear	Clear





COOLANT REPORT



Laboratory : WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9
Sample No. : PP13927504
Lab Number : 02602436
Unique Number : 5695521
Test Package : COOL

ExxonMobil Canada East Ltd.
 Hebron-Materials and Repair Coordin, Suite 1000, 100 New Gow
 St. John's, NL
 CA A1C 6K3
 Contact: Liam Maher
 liam.m.maher@exxonmobil.com
 T: (709)273-3729
 F:

To discuss this sample report, contact Customer Service at 1-800-268-2131.
 Test denoted (*) outside scope of accreditation, (m) method modified, (e) tested at external lab.
 Validity of results and interpretation are based on the sample and information as supplied.