

# **OIL ANALYSIS REPORT**

#### Sample Rating Trend



#### Machine Id **100-003** Component **Right Final Drive** Fluid **PETRO CANADA TRAXON 80W90 (--- GAL)**

#### DIAGNOSIS

#### Recommendation

Confirm the source of the lubricant being utilized for top-up/fill. Resample at the next service interval to monitor. Please specify the component make and model with your next sample.

## Wear

All component wear rates are normal.

## Contamination

There is no indication of any contamination in the oil.


#### Fluid Condition


Additive levels indicate the addition of a different brand, or type of oil. The condition of the oil is acceptable for the time in service.

)			Mar2023	Dec2023		
SAMPLE INFORM	1ATION	method	limit/base	current	history1	history2
Sample Number		Client Info		WC0872911	LH	
Sample Date		Client Info		06 Dec 2023	30 Mar 2023	
Machine Age	hrs	Client Info		0	0	
Oil Age	hrs	Client Info		0	0	
Oil Changed		Client Info		N/A	N/A	
Sample Status				NORMAL	NORMAL	
CONTAMINATION	١	method	limit/base	current	history1	history2
Water		WC Method	>0.2	NEG	NEG	
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185(m)	>500	363	284	
Chromium	ppm	ASTM D5185(m)	>10	2	2	
Nickel	ppm	ASTM D5185(m)	>10	2	<1	
Titanium	ppm	ASTM D5185(m)		0	<1	
Silver	ppm	ASTM D5185(m)		<1	0	
Aluminum	ppm	ASTM D5185(m)	>25	4	3	
Lead	ppm	ASTM D5185(m)	>25	0	0	
Copper	ppm	ASTM D5185(m)	>50	2	1	
Tin	ppm	ASTM D5185(m)	>10	0	<1	
Antimony	ppm	ASTM D5185(m)	>5	0	0	
Vanadium	ppm	ASTM D5185(m)		0	0	
Beryllium	ppm	ASTM D5185(m)		0	0	
Cadmium	ppm	ASTM D5185(m)		0	0	
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185(m)	243	47	46	
Barium	ppm	ASTM D5185(m)	1	<1	0	
Molybdenum	ppm	ASTM D5185(m)		0	<1	
Manganese	ppm	ASTM D5185(m)		2	2	
Magnesium	ppm	ASTM D5185(m)	2	12	11	
Calcium	ppm	ASTM D5185(m)	6	3455	3715	
Phosphorus	ppm	ASTM D5185(m)	987	907	1014	
Zinc	ppm	ASTM D5185(m)	1	887	866	
Sulfur	ppm	ASTM D5185(m)	21530	7710	8041	
Lithium	ppm	ASTM D5185(m)		<1	<1	
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185(m)	>75	27	26	
Sodium	ppm	ASTM D5185(m)		2	1	
Potassium	ppm	ASTM D5185(m)	>20	4	5	



# **OIL ANALYSIS REPORT**





VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	Visual*	NONE	NONE	VLITE	
ellow Metal	scalar	Visual*	NONE	NONE	NONE	
Precipitate	scalar	Visual*	NONE	NONE	NONE	
Silt	scalar	Visual*	NONE	NONE	NONE	
Debris	scalar	Visual*	NONE	NONE	NONE	
Sand/Dirt	scalar	Visual*	NONE	NONE	NONE	
Appearance	scalar	Visual*	NORML	NORML	NORML	
Ddor	scalar	Visual*	NORML	NORML	NORML	
Emulsified Water	scalar	Visual*	>0.2	NEG	NEG	
Free Water	scalar	Visual*		NEG	NEG	
FLUID PROPERT	IES	method	limit/base	current	history1	history2
/isc @ 40°C	cSt	ASTM D7279(m)	141.0	111	112	
SAMPLE IMAGES		method	limit/base	current	history1	history2
						,
Color						no image
						no inago
Pattam				23		
Bottom						no image
GRAPHS						
Iron (ppm)			150	Lead (ppm)		
Severe				Severe		
Abnormal			트 <sup>100</sup> 토 50	Abnormal		
			0			*****
Mar30/23			Dec6/23	Mar30/23		
				_	222	
Aluminum (ppm)			Chromium (ppm)			
Severe			E 20			
Abnormal			<sup>20</sup> 10	Abnormal		
L.;			0			
Mar30/23			Dec6/23	Mar30/23		
Copper (ppm)			300	Silicon (ppm)		
Severe				Samara		
Abnormal			E 200	Abnormal		
			- 0			
Mar30/23			Dec6/23	Mar30/23		
			ā	Ma		
Viscosity @ 40°C			1000	Additives		
			4000	calcium		
Base			톱 2000	phosphore	IS	
Abnormal			0			***********************
Mar30/23			Dec6/23	30/23		
Mari			Der	Mar30/23		
WearCheck - C8-117 WC0872911 <b>F</b>	leceived		Dec 2023			INTOSH BLV
	iagnos		Dec 2023			AUGHAN, C
			Dec 2020		v	AUGHAN, C
	iagnost	ician : We	s Davis			CA L4K 4

To discuss this sample report, c Test denoted (\*) outside scope of accreditation, (m) method modified, (e) tested at external lab. Validity of results and interpretation are based on the sample and information as supplied.

CALA

ISO 17025:2017 Accredited Laboratory

Laboratory

Sample No. Lab Number

**Unique Number Test Package** 

T:

F: