




# OIL ANALYSIS REPORT

Sample Rating Trend

**NORMAL**



Area  
**(C-FKEX)**  
 Machine Id  
**[C-FKEX] BEECHCRAFT KING AIR B200 PCE-PJ0150**  
 Component  
**Left Jet Turbine**  
 Fluid  
**BP TURBO OIL 2380 (--- GAL)**

## DIAGNOSIS

### Recommendation

Resample at the next service interval to monitor.  
 NOTE: Please provide information regarding reservoir capacity, filter type and micron rating with next sample.

### Wear

All component wear rates are normal. The ferrography results are normal indicating no abnormal wear in the system.

### Contaminants

The water content is negligible. There is no indication of any contamination in the oil.

### Oil Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

## SAMPLE INFORMATION

	method	limit/base	current	history1	history2
Sample Number	Client Info		<b>WC0798261</b>	WC0850512	WC0841646
Sample Date	Client Info		<b>13 Dec 2023</b>	22 Sep 2023	05 Aug 2023
TSN	hrs	Client Info	<b>11612</b>	11415	11231
TSO	hrs	Client Info	<b>903</b>	706	522
Oil Age	hrs	Client Info	<b>0</b>	0	0
Oil Changed		Client Info	<b>Not Changed</b>	N/A	N/A
Sample Status			<b>NORMAL</b>	NORMAL	NORMAL

## WEAR METALS

	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185(m) >8	<b>0</b>	0	0
Chromium	ppm	ASTM D5185(m) >2	<b>0</b>	0	0
Nickel	ppm	ASTM D5185(m) >2	<b>0</b>	0	0
Titanium	ppm	ASTM D5185(m) >2	<b>0</b>	0	0
Silver	ppm	ASTM D5185(m) >2	<b>&lt;1</b>	<1	0
Aluminum	ppm	ASTM D5185(m) >2	<b>0</b>	0	<1
Lead	ppm	ASTM D5185(m) >3	<b>&lt;1</b>	0	0
Copper	ppm	ASTM D5185(m) >3	<b>&lt;1</b>	<1	<1
Tin	ppm	ASTM D5185(m) >2	<b>0</b>	0	0
Antimony	ppm	ASTM D5185(m)	<b>0</b>	0	0
Vanadium	ppm	ASTM D5185(m)	<b>0</b>	0	0
Beryllium	ppm	ASTM D5185(m)	<b>0</b>	0	0
Cadmium	ppm	ASTM D5185(m)	<b>0</b>	0	0

## ADDITIVES

	method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185(m) 0	<b>&lt;1</b>	<1	<1
Barium	ppm	ASTM D5185(m) 0	<b>&lt;1</b>	<1	0
Molybdenum	ppm	ASTM D5185(m) 0	<b>0</b>	0	0
Manganese	ppm	ASTM D5185(m)	<b>0</b>	0	0
Magnesium	ppm	ASTM D5185(m) 0	<b>0</b>	0	0
Calcium	ppm	ASTM D5185(m) 0	<b>&lt;1</b>	0	<1
Phosphorus	ppm	ASTM D5185(m) 2500	<b>2700</b>	2687	2846
Zinc	ppm	ASTM D5185(m) 0	<b>&lt;1</b>	<1	2
Sulfur	ppm	ASTM D5185(m) 0	<b>4</b>	3	3
Lithium	ppm	ASTM D5185(m)	<b>&lt;1</b>	<1	<1

## CONTAMINANTS





	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185(m) >8	<b>&lt;1</b>	<1	1
Sodium	ppm	ASTM D5185(m)	<b>&lt;1</b>	<1	<1
Potassium	ppm	ASTM D5185(m) >20	<b>0</b>	0	0
Water	%	ASTM D6304* >0.1	<b>0.041</b>	0.066	0.088
ppm Water	ppm	ASTM D6304* >1000	<b>417</b>	662.8	888.8

## FLUID DEGRADATION

	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D974* 0.43	<b>0.39</b>	0.31	0.26




# OIL ANALYSIS REPORT







VISUAL	method	limit/base	current	history1	history2
White Metal	scalar	Visual*	NONE	NONE	NONE
Yellow Metal	scalar	Visual*	NONE	NONE	NONE
Precipitate	scalar	Visual*	NONE	NONE	NONE
Silt	scalar	Visual*	NONE	NONE	NONE
Debris	scalar	Visual*	NONE	NONE	NONE
Sand/Dirt	scalar	Visual*	NONE	NONE	NONE
Appearance	scalar	Visual*	NORML	NORML	NORML
Odor	scalar	Visual*	NORML	NORML	NORML
Emulsified Water	scalar	Visual*	>0.1	NEG	NEG
Free Water	scalar	Visual*		NEG	NEG

FLUID PROPERTIES	method	limit/base	current	history1	history2	
Visc @ 40°C	cSt	ASTM D7279(m)	24.2	<b>24.5</b>	25.6	23.6
Visc @ 100°C	cSt	ASTM D7279(m)	4.97	<b>5</b>	5	4.9
Viscosity Index (VI)	Scale	ASTM D2270*	134	<b>133</b>	123	134

### SAMPLE IMAGES



### GRAPHS



**Laboratory** : WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9  
**Sample No.** : WC0798261 **Received** : 19 Dec 2023  
**Lab Number** : **02604110** **Diagnosed** : 21 Dec 2023  
**Unique Number** : 5697195 **Diagnostician** : Kevin Marson  
**Test Package** : AVI 3

**Keewatin Air LP**  
 50 Morberg Way  
 Winnipeg, MB  
 CA R3H 0A4  
 Contact: Heather Karavas  
 hkaravas@keewatinair.ca  
 T: (204)888-0100  
 F: (204)888-5791


To discuss this sample report, contact Customer Service at 1-800-268-2131.  
 Test denoted (\*) outside scope of accreditation, (m) method modified, (e) tested at external lab.  
 Validity of results and interpretation are based on the sample and information as supplied.



# FERROGRAPHY REPORT

Area  
**(C-FKEX)**  
 Machine Id  
**[C-FKEX] BEEHCRAFT KING AIR B200 PCE-PJ0150**  
 Component  
**Left Jet Turbine**  
 Fluid  
**BP TURBO OIL 2380 (--- GAL)**


Magn: 200x Illum: BC



Magn: 50x Illum: RW



Magn: 100x Illum: RW




DR-FERROGRAPHY		method	limit/base	current	history1	history2
Large Particles		DR-Ferr*		<b>2.3</b>	1.0	1.0
Small Particles		DR-Ferr*		<b>2.1</b>	0.3	0.2
Total Particles		DR-Ferr*	>---	<b>4.4</b>	1.3	1.2
Large Particles Percentage	%	DR-Ferr*		<b>4.5</b>	53.8	66.7
Severity Index		DR-Ferr*		<b>0</b>	1	1

FERROGRAPHY		method	limit/base	current	history1	history2
Ferrous Rubbing	Scale 0-10	ASTM D7684*		█ <b>1</b>	█ 1	█ 1
Ferrous Sliding	Scale 0-10	ASTM D7684*				
Ferrous Cutting	Scale 0-10	ASTM D7684*				
Ferrous Rolling	Scale 0-10	ASTM D7684*		█ <b>1</b>	█ 1	
Ferrous Break-in	Scale 0-10	ASTM D7684*				
Ferrous Spheres	Scale 0-10	ASTM D7684*				
Ferrous Black Oxides	Scale 0-10	ASTM D7684*				
Ferrous Red Oxides	Scale 0-10	ASTM D7684*				
Ferrous Corrosive	Scale 0-10	ASTM D7684*				
Ferrous Other	Scale 0-10	ASTM D7684*				
Nonferrous Rubbing	Scale 0-10	ASTM D7684*				
Nonferrous Sliding	Scale 0-10	ASTM D7684*				
Nonferrous Cutting	Scale 0-10	ASTM D7684*				
Nonferrous Rolling	Scale 0-10	ASTM D7684*				
Nonferrous Other	Scale 0-10	ASTM D7684*				
Carbonaceous Material	Scale 0-10	ASTM D7684*				
Lubricant Degradation	Scale 0-10	ASTM D7684*				
Sand/Dirt	Scale 0-10	ASTM D7684*		█ <b>1</b>		█ 1
Fibres	Scale 0-10	ASTM D7684*				
Spheres	Scale 0-10	ASTM D7684*				
Other	Scale 0-10	ASTM D7684*		█ <b>1</b>	█ 1	█ 1

### WEAR

All component wear rates are normal. The ferroggraphy results are normal indicating no abnormal wear in the system.



*This page left intentionally blank*