

GREASE ANALYSIS

Sample Rating Trend

NORMAL

APM 1 - Drive Room Main Bullwheel - Evac Side (S/N 1DMB-E)

Grease

MOBIL SHC GREASE 460 WT (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Grease Condition

The condition of the grease is acceptable for the time in service.

Contaminants

There is no indication of any contamination in the grease.


	,					
			Jun2020	Sep2023		
SAMPLE INFORM	ΛΑΤΙΟΝ	method	limit/base		history1	history2
Sample Number		Client Info		WC0841108	WC0474270	
Sample Date		Client Info		17 Sep 2023	23 Jun 2020	
Machine Age	hrs	Client Info		0	6673	
Grease Age	hrs	Client Info		0	0	
Grease Serviced		Client Info		Not Changd	N/A	
Sample Status				NORMAL	NORMAL	
CONTAMINATIO	N	method	limit/base	current	history1	history2
Water		WC Method	>0.1	NEG	NEG	
WEAR METALS		method	limit/base	current	history1	history2
PQ		ASTM D8184*	>200	0	0	
Iron	ppm	ASTM D5185(m)	>250	1	1	
Chromium	ppm	ASTM D5185(m)	>10	0	0	
Nickel	ppm	ASTM D5185(m)	>5	<1	<1	
Cadmium	ppm	ASTM D5185(m)		0	0	
Titanium	ppm	ASTM D5185(m)		0	0	
Vanadium	ppm	ASTM D5185(m)		0	0	
Lead	ppm	ASTM D5185(m)	>25	<1	<1	
Copper	ppm	ASTM D5185(m)	>75	2	2	
Tin	ppm	ASTM D5185(m)	>5	0	0	
Silver	ppm	ASTM D5185(m)	>5	0	0	
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185(m)		0	<1	
Magnesium	ppm	ASTM D5185(m)		<1	<1	
Vanganese	ppm	ASTM D5185(m)		0	0	
Volybdenum	ppm	ASTM D5185(m)		0	0	
Phosphorus	ppm	ASTM D5185(m)		58	85	
Zinc	ppm	ASTM D5185(m)		85	128	
Antimony	ppm	ASTM D5185(m)		0	0	
THICKENER/SO	٩P	method	limit/base	current	history1	history2
Aluminum	ppm	ASTM D5185(m)		<1	<1	
Barium	ppm	ASTM D5185(m)		0	0	
Calcium	ppm	ASTM D5185(m)		2	1	
Sodium	ppm	ASTM D5185(m)		2	<1	
Lithium	ppm	ASTM D5185(m)		634	643	
Sulfur	ppm	ASTM D5185(m)		696	676	
CONTAMINANTS	\$	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185(m)	>150	<1	<1	
Potassium	ppm	ASTM D5185(m)		<1	<1	
GREASE CONDI	TION	method	limit/base	current	history1	history2
Grease Color		Visual*	Red	Red	Red	
		In-house*		Short fiber	Short fiber	
Texture		III-House		Short liber	Short liber	




GREASE ANALYSIS













: WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9 DCC DOPPELMAYR CABLE CAR Laboratory CALA Sample No. : WC0841108 Recieved : 19 Dec 2023 6100 VISCOUNT RD, GENERAL DELIVERIES 2ND FLOOR Lab Number : 02604284 Diagnosed : 21 Dec 2023 MISSISSAUGA, ON ISO 17025:2017 Accredited Laboratory Unique Number : 5697369 Diagnostician : Bill Quesnel CA L9V 0A1 Test Package : GRS 1 (Additional Tests: BottomAnalysis) Contact: Dave Simpson To discuss this sample report, contact Customer Service at 1-800-268-2131. dsimpson@dccoperations.com Test denoted (*) outside scope of accreditation, (m) method modified, (e) tested at external lab. T: (905)612-8630 Validity of results and interpretation are based on the sample and information as supplied. F: (905)612-0626

Page 2 of 2