


# **OIL ANALYSIS REPORT**

Sample Rating Trend







# CRANE #5

Component

Gearbox

MOBIL MOBILUBE HD 85W140 (--- GAL)

### DIAGNOSIS

### Recommendation

Resample at the next service interval to monitor. NOTE: Please provide information regarding reservoir capacity, filter type and micron rating with next sample.

### Wear

All component wear rates are normal.

### Contamination

There is no indication of any contamination in the


### **Fluid Condition**

The condition of the oil is acceptable for the time in service.

			Dec2022	Dec2023		
SAMPLE INFORM	/ATION	method	limit/base	current	history1	history2
Sample Number		Client Info		WC0887213	WC0765202	
Sample Date		Client Info		09 Dec 2023	18 Dec 2022	
Machine Age	hrs	Client Info		09 Dec 2023	0	
Oil Age	hrs	Client Info		0	0	
Oil Changed	1113	Client Info		N/A	N/A	
Sample Status		Ollerit IIIIO		NORMAL	NORMAL	
CONTAMINATION		method	limit/base	current	history1	history2
Water		WC Method	>0.2	NEG	NEG	
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185(m)	>200	16	13	
Chromium	ppm	ASTM D5185(m)		0	0	
Nickel	ppm	ASTM D5185(m)	>15	0	<1	
Titanium	ppm	ASTM D5185(m)		0	<1	
Silver	ppm	ASTM D5185(m)		0	0	
Aluminum	ppm	ASTM D5185(m)	>25	3	3	
Lead	ppm	ASTM D5185(m)	>100	9	9	
Copper	ppm	ASTM D5185(m)		<1	<1	
Tin	ppm	ASTM D5185(m)	>25	0	<1	
Antimony	ppm	ASTM D5185(m)	>5	0	<1	
Vanadium	ppm	ASTM D5185(m)	. •	0	0	
Beryllium	ppm	ASTM D5185(m)		0	0	
Cadmium	ppm	ASTM D5185(m)		0	0	
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185(m)		144	108	
Barium	ppm	ASTM D5185(m)		4	4	
Molybdenum	ppm	ASTM D5185(m)		0	<1	
Manganese	ppm	ASTM D5185(m)		0	<1	
Magnesium	ppm	ASTM D5185(m)		2	6	
Calcium	ppm	ASTM D5185(m)		7	7	
Phosphorus	ppm	ASTM D5185(m)		952	971	
Zinc	ppm	ASTM D5185(m)		33	36	
Sulfur	ppm	ASTM D5185(m)		18525	18378	
Lithium	ppm	ASTM D5185(m)		<1	<1	
CONTAMINANTS	;	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185(m)	>50	26	26	
Sodium	ppm	ASTM D5185(m)		5	19	
Potassium	ppm	ASTM D5185(m)	>20	<1	2	



## **OIL ANALYSIS REPORT**



VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	Visual*	NONE	NONE	NONE	
Yellow Metal	scalar	Visual*	NONE	NONE	NONE	
Precipitate	scalar	Visual*	NONE	NONE	NONE	
Silt	scalar	Visual*	NONE	NONE	NONE	
Debris	scalar	Visual*	NONE	NONE	NONE	
Sand/Dirt	scalar	Visual*	NONE	NONE	NONE	
Appearance	scalar	Visual*	NORML	NORML	NORML	
Odor	scalar	Visual*	NORML	NORML	NORML	
<b>Emulsified Water</b>	scalar	Visual*	>0.2	NEG	NEG	
Free Water	scalar	Visual*		NEG	NEG	
FLUID PROPERT	IES	method	limit/base	current	history1	history2


718C @ 40°C	CSI	A51W D7279(III)	320	334	334	
SAMPLE IMAGES	6	method	limit/base	current	history1	history2
Color						no image

С **Bottom** no image

### **GRAPHS**

# Ferrous Alloys







CALA ISO 17025:2017 Accredited Laboratory

Report Id: METREX [WCAMIS] 02605127 (Generated: 12/22/2023 17:27:29) Rev: 1

Laboratory Sample No. Lab Number Unique Number : 5698212 Test Package : IND 1

: WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9 : WC0887213 : 02605127

Recieved : 22 Dec 2023 Diagnosed : 22 Dec 2023 Diagnostician : Wes Davis

**Continuous Colour Coat Limited** 

1430 Martin Grove Rd Rexdale, ON CA M9W 4Y1 Contact: Parminder Singh

parminder.singh@materialsciencescorp.com

T: (416)743-7980

To discuss this sample report, contact Customer Service at 1-800-268-2131. Test denoted (\*) outside scope of accreditation, (m) method modified, (e) tested at external lab.

F: (416)743-7138