

# **OIL ANALYSIS REPORT**

Sample Rating Trend





CATERPILLAR 740GL HDTR0836

Middle Left Final Drive Fluid MOBIL 56 (--- GAL)

### DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

### Wear

All component wear rates are normal.

#### Contamination

There is no indication of any contamination in the oil.

## Fluid Condition


The condition of the oil is acceptable for the time in service.

SAMPLE INFORM	IATION	method	limit/base	current	history1	history2
Sample Number		Client Info		WC0879757		
Sample Date		Client Info		18 Dec 2023		
Machine Age	hrs	Client Info		725		
Oil Age	hrs	Client Info		0		
Oil Changed		Client Info		Not Changd		
Sample Status				NORMAL		
CONTAMINATIO	٧	method	limit/base	current	history1	history2
Water		WC Method	>0.2	NEG		
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185(m)	>800	83		
Chromium	ppm	ASTM D5185(m)	>10	<1		
Nickel	ppm	ASTM D5185(m)	>5	<1		
Titanium	ppm	ASTM D5185(m)	>15	0		
Silver	ppm	ASTM D5185(m)	>2	0		
Aluminum	ppm	ASTM D5185(m)	>75	4		
Lead	ppm	ASTM D5185(m)	>10	1		
Copper	ppm	ASTM D5185(m)		31		
Tin	ppm	ASTM D5185(m)	>8	0		
Antimony	ppm	ASTM D5185(m)	>50	0		
Vanadium	ppm	ASTM D5185(m)		0		
Beryllium	ppm	ASTM D5185(m)		0		
Cadmium	ppm	ASTM D5185(m)		0		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185(m)		1		
Barium	ppm	ASTM D5185(m)		<1		
Molybdenum	ppm	ASTM D5185(m)		2		
Manganese	ppm	ASTM D5185(m)		1		
Magnesium	ppm	ASTM D5185(m)		9		
Calcium	ppm	ASTM D5185(m)		3233		
Phosphorus	ppm	ASTM D5185(m)		1025		
Zinc	ppm	ASTM D5185(m)		1202		
Sulfur	ppm	ASTM D5185(m)		7414		
Lithium	ppm	ASTM D5185(m)		<1		
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185(m)	>400	18		
Sodium	ppm	ASTM D5185(m)		2		
Potassium	ppm	ASTM D5185(m)	>20	1		



# **OIL ANALYSIS REPORT**

VISUAL



<b>.</b>		VISUAL		method	limit/base	current	history1	history2
		White Metal	scalar	Visual*	NONE	NONE		
		Yellow Metal	scalar	Visual*	NONE	NONE		
		Precipitate	scalar	Visual*	NONE	NONE		
		Silt	scalar	Visual*	NONE	NONE		
		Debris	scalar	Visual*	NONE	VLITE		
		Sand/Dirt	scalar	Visual*	NONE	NONE		
	Dec18/23	Appearance	scalar	Visual*	NORML	NORML		
	Dec	Odor	scalar	Visual*	NORML	NORML		
		Emulsified Water	scalar	Visual*	>0.2	NEG		
		Free Water	scalar	Visual*		NEG		
		FLUID PROPERT	IFS	method	limit/base	current	history1	history2
		Visc @ 40°C	cSt	ASTM D7279(m)		95.7		
		_						
		SAMPLE IMAGES	5	method	limit/base	current	history1	history2
		Color					no image	no image
		Bottom					no image	no image
		GRAPHS						
		Iron (ppm)				Lead (ppm)		
	20	Severe			30			
	톱 10	000 - Abnormal			문 <sup>20</sup>	Abnormal		
		0						
		Jec18/23			Dec18/23	Dec18/23		Dec18/23
		Deci			Deci	Dec		Deci
		Aluminum (ppm)				Chromium (pp	om)	
	2	200 Severe			3	0 COLOR		
	uid	100 - Abnormal			<sup>20</sup>	Abnormal		
		0			<u> </u>	jL <u> </u>		
		Jec18/23			Dec18/23	Dec18/23		Dec18/23
		Deci			Deci	Dec		Deci
		Copper (ppm)				Silicon (ppm)		
		200 Severe				Severe		
	udd	100 - Abnormal			틆 500	Abnormal		
		0				, L,		
		Dec18/23			Dec18/23	Dec18/23		Dec18/23
					Dec	Dec		Dec
		Viscosity @ 40°C			100	Additives		
		Abnormal			400	C		
	cSt (40°C)	100 - Abnormal			E 300	)	•	
	0	04				)	~	
		Dec18/23			Dec18/23	Dec18/23		Dec18/23
		Dec			Der	Det		Dec
		: 02605389 I : 5698474 I : MOB 1 ontact Customer Servi	Recieved Diagnose Diagnosti	: 27 ed : 27 ician : We	Dec 2023 Dec 2023 s Davis 1.	1350 Gov AEM_KL_n	ernment Rd. W, MA Kirł Contact: Mito nacassaoilsampleresu	kland Lake, ON CA P2N 3J1 ch Lamontagne lts@agnicoeagle.com
		of accreditation, (m) m tion are based on the s						(705)567-5208 (705)567-5221