




OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL



Area
11

Machine Id
11-0110-020-000 STACK GATHERING DRIVE #2 (11M102)

Component
11 Gearbox

Fluid
SHELL OMALA S2 GX 220 (4 LTR)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

SAMPLE INFORMATION		method	limit/base	current	history1	history2
Sample Number	Client Info			WC0855142	WC0754090	WC0412718
Sample Date	Client Info			21 Nov 2023	02 Dec 2022	13 Dec 2019
Machine Age	hrs	Client Info		0	0	0
Oil Age	hrs	Client Info		0	0	0
Oil Changed	Client Info			N/A	N/A	N/A
Sample Status				NORMAL	NORMAL	NORMAL

CONTAMINATION		method	limit/base	current	history1	history2
Water	WC Method		>0.2	NEG	NEG	NEG

WEAR METALS		method	limit/base	current	history1	history2
PQ		ASTM D8184*		0	0	10
Iron	ppm	ASTM D5185(m)	>200	32	95	29
Chromium	ppm	ASTM D5185(m)	>15	<1	<1	<1
Nickel	ppm	ASTM D5185(m)	>15	<1	<1	<1
Titanium	ppm	ASTM D5185(m)		0	0	<1
Silver	ppm	ASTM D5185(m)		0	0	0
Aluminum	ppm	ASTM D5185(m)	>25	<1	<1	<1
Lead	ppm	ASTM D5185(m)	>100	0	<1	0
Copper	ppm	ASTM D5185(m)	>200	<1	0	<1
Tin	ppm	ASTM D5185(m)	>25	0	0	0
Antimony	ppm	ASTM D5185(m)	>5	0	<1	<1
Vanadium	ppm	ASTM D5185(m)		0	0	0
Beryllium	ppm	ASTM D5185(m)		0	0	0
Cadmium	ppm	ASTM D5185(m)		0	0	0




ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185(m)	6.2	9	14	22
Barium	ppm	ASTM D5185(m)	0.0	12	15	20
Molybdenum	ppm	ASTM D5185(m)	0	0	<1	<1
Manganese	ppm	ASTM D5185(m)		0	1	<1
Magnesium	ppm	ASTM D5185(m)	0	<1	2	<1
Calcium	ppm	ASTM D5185(m)	0.0	11	11	14
Phosphorus	ppm	ASTM D5185(m)	290	235	346	315
Zinc	ppm	ASTM D5185(m)	3.8	7	13	5
Sulfur	ppm	ASTM D5185(m)	8167	11258	13449	14502
Lithium	ppm	ASTM D5185(m)		<1	<1	<1

CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185(m)	>50	<1	4	<1
Sodium	ppm	ASTM D5185(m)		2	4	2
Potassium	ppm	ASTM D5185(m)	>20	<1	2	<1

FLUID DEGRADATION		method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D974*		0.55	0.62	0.641




OIL ANALYSIS REPORT








VISUAL	method	limit/base	current	history1	history2
White Metal	scalar	Visual*	NONE	NONE	VLITE
Yellow Metal	scalar	Visual*	NONE	NONE	NONE
Precipitate	scalar	Visual*	NONE	NONE	NONE
Silt	scalar	Visual*	NONE	NONE	NONE
Debris	scalar	Visual*	NONE	NONE	NONE
Sand/Dirt	scalar	Visual*	NONE	NONE	NONE
Appearance	scalar	Visual*	NORML	NORML	NORML
Odor	scalar	Visual*	NORML	NORML	NORML
Emulsified Water	scalar	Visual*	>0.2	NEG	NEG
Free Water	scalar	Visual*		NEG	NEG

FLUID PROPERTIES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D7279(m)	220	212	208

SAMPLE IMAGES	method	limit/base	current	history1	history2
Color					
Bottom					
PrtFilter					



GRAPHS



Laboratory : WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9
Sample No. : WC0855142 **Received** : 27 Dec 2023
Lab Number : 02605470 **Diagnosed** : 28 Dec 2023
Unique Number : 5698555 **Diagnostician** : Wes Davis
Test Package : IND 2

Roseburg Pembroke MDF Inc.
 777 Fibreboard Drive
 Pembroke, ON
 CA K8A 6W5
 Contact: Dan Havis
 danielh@rfpco.com
 T: (613)732-3939
 F: (613)732-2869

To discuss this sample report, contact Customer Service at 1-800-268-2131.
 Test denoted (*) outside scope of accreditation, (m) method modified, (e) tested at external lab.
 Validity of results and interpretation are based on the sample and information as supplied.