


OIL ANALYSIS REPORT







NO UNIT WC0892376

Component **Diesel Engine**

NOT GIVEN (--- GAL)

| D 1 | | \sim | . 10 | \neg | 71/ | $\overline{}$ |
|------------|-----|--------|------|--------|-----|---------------|
| DI | А | (51 | МÜ | D). | 3 I | 5 |
| -1 | , , | | | | | |

Recommendation

No corrective action is recommended at this time. Resample at the next service interval to monitor. The fluid was not specified, however, a fluid match indicates that this fluid is SAE 5W20 Diesel Engine Oil. Please confirm the oil type and grade, and specify the brand of the oil on your next sample. Please specify the component make and model with your next sample.

Wear

All component wear rates are normal.

Contamination

Fuel content negligible. There is no indication of any contamination in the oil.


Fluid Condition

Viscosity of sample indicates oil is within SAE 5W20 range, advise investigate. The condition of the oil is acceptable for the time in service.

| | | | | Dec2023 | | |
|---------------|-----------------|------------------------|-------------|-------------|----------|----------|
| SAMPLE INFORM | AATION | method | limit/base | | history | hiotory? |
| | MATION | | iiiiiivbase | current | history1 | history2 |
| Sample Number | | Client Info | | WC0892376 | | |
| Sample Date | | Client Info | | 26 Dec 2023 | | |
| Machine Age | kms | Client Info | | 0 | | |
| Oil Age | kms | Client Info | | 0 | | |
| Oil Changed | | Client Info | | Changed | | |
| Sample Status | | | | NORMAL | | |
| CONTAMINATION | ٧ | method | limit/base | current | history1 | history2 |
| Water | | WC Method | >0.2 | NEG | | |
| Glycol | | WC Method | | NEG | | |
| WEAR METALS | | method | limit/base | current | history1 | history2 |
| Iron | ppm | ASTM D5185(m) | >100 | 52 | | |
| Chromium | ppm | ASTM D5185(m) | >20 | <1 | | |
| Nickel | ppm | ASTM D5185(m) | >4 | <1 | | |
| Titanium | ppm | ASTM D5185(m) | | 16 | | |
| Silver | ppm | ASTM D5185(m) | >3 | 0 | | |
| Aluminum | ppm | ASTM D5185(m) | >20 | 19 | | |
| Lead | ppm | ASTM D5185(m) | >40 | 0 | | |
| Copper | ppm | ASTM D5185(m) | >330 | 3 | | |
| Tin | ppm | ASTM D5185(m) | >15 | <1 | | |
| Antimony | ppm | ASTM D5185(m) | | 0 | | |
| Vanadium | ppm | ASTM D5185(m) | | 0 | | |
| Beryllium | ppm | ASTM D5185(m) | | 0 | | |
| Cadmium | ppm | ASTM D5185(m) | | 0 | | |
| ADDITIVES | | method | limit/base | current | history1 | history2 |
| Boron | ppm | ASTM D5185(m) | | 88 | | |
| Barium | ppm | ASTM D5185(m) | | 0 | | |
| Molybdenum | ppm | ASTM D5185(m) | | 68 | | |
| Manganese | ppm | ASTM D5185(m) | | 1 | | |
| Magnesium | ppm | ASTM D5185(m) | | 602 | | |
| Calcium | ppm | ASTM D5185(m) | | 1146 | | |
| Phosphorus | ppm | ASTM D5185(m) | | 686 | | |
| Zinc | ppm | ASTM D5185(m) | | 782 | | |
| Sulfur | ppm | ASTM D5185(m) | | 1855 | | |
| Lithium | ppm | ASTM D5185(m) | | <1 | | |
| CONTAMINANTS | | method | limit/base | current | history1 | history2 |
| Silicon | ppm | ASTM D5185(m) | >25 | 12 | | |
| Sodium | ppm | ASTM D5185(m) | | 15 | | |
| Potassium | ppm | ASTM D5185(m) | >20 | 5 | | |
| Fuel | % | ASTM D7593* | >5 | 0.9 | | |
| INFRA-RED | | method | limit/base | current | history1 | history2 |
| Soot % | % | ASTM D7844* | >3 | 0 | | |
| Nitration | Abs/cm | ASTM D7624* | >20 | 9.2 | | |
| Sulfation | Abs/.1mm | ASTM D7024 ASTM D7415* | >30 | 17.3 | | |
| Canadon | / 100/. 1111111 | 01111 01 710 | - 00 | | | |



OIL ANALYSIS REPORT





CALA ISO 17025:2017 Accredited Laboratory

Laboratory Sample No. Lab Number **Unique Number**

: 5706921

: WC0892376 : 02605835

: WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9 Recieved

: 02 Jan 2024 Diagnosed Diagnostician : Kevin Marson

: 03 Jan 2024

Deepak Kumar 6960 Mayfield Rd. Caledon, ON CA L7C 0G8 Contact: Deepak Kumar

Test Package : MOB 1 (Additional Tests: FuelDilution, KV40, PercentFuel, VI, Visual) To discuss this sample report, contact Customer Service at 1-800-268-2131.

deepakkumarsts1@gmail.com T: (519)562-8131

Test denoted (*) outside scope of accreditation, (m) method modified, (e) tested at external lab. Validity of results and interpretation are based on the sample and information as supplied.