

OIL ANALYSIS REPORT

Sample Rating Trend WATER

Pratt Longueuil Circ#B [0068815-H663] **ČARRIER 1908Q09139(B)** Component

Chiller Fluid COMP OIL (ESTER) ISO 220 (--- GAL)

DIAGNOSIS	SAMPLE INFOR	MATION	method	limit/base	current	history1	history2
Recommendation	Sample Number		Client Info		GTT0001306	GTT7385	GTT7386
not recently done change any filter driers to	Sample Date		Client Info		25 Sep 2023	13 Jan 2023	27 Jun 2022
duce moisture level. We recommend an early	Machine Age	hrs	Client Info		0		
sample to monitor this condition.	Oil Age	hrs	Client Info		0		
ear	Oil Changed		Client Info		N/A	N/A	N/A
component wear rates are normal.	Sample Status				MARGINAL	NORMAL	ABNORMAL
Contamination isture is above typical range for this type of	WEAR METALS		method	limit/base	current	history1	history2
npressor.	Iron	ppm	ASTM D5185(m)	>8	<1	<1	3
d Condition	Chromium	ppm	ASTM D5185(m)	>2	0	<1	<1
AN level is acceptable for this fluid. The	Nickel	ppm	ASTM D5185(m)		0		
lition of the oil is suitable for further service.	Titanium	ppm	ASTM D5185(m)		0		
	Silver	ppm	ASTM D5185(m)	>2	0		
	Aluminum	ppm	ASTM D5185(m)	>3	<1	<1	<1
	Lead	ppm	ASTM D5185(m)	>2	<1	<1	<1
	Copper	ppm	ASTM D5185(m)	>8	1	2	2
	Tin	ppm	ASTM D5185(m)	>4	<1	<1	<1
	Antimony	ppm	ASTM D5185(m)		0		
	Vanadium	ppm	ASTM D5185(m)		0		
	Beryllium	ppm	ASTM D5185(m)		0		
	Cadmium	ppm	ASTM D5185(m)		0		
	ADDITIVES		method	limit/base	current	history1	history2
	Boron	ppm	ASTM D5185(m)	5	<1		
	Barium	ppm	ASTM D5185(m)	5	0		
	Molybdenum	ppm	ASTM D5185(m)	5	0		
	Manganese	ppm	ASTM D5185(m)		0		
	Magnesium	ppm	ASTM D5185(m)	5	<1		
	Calcium	ppm	ASTM D5185(m)	5	0		
	Phosphorus	ppm	ASTM D5185(m)	400	22		
	Zinc	ppm	ASTM D5185(m)	5	4	3	1
	Sulfur	ppm	ASTM D5185(m)	100	0		
	Lithium	ppm	ASTM D5185(m)		<1		
	CONTAMINANT	S	method	limit/base	current	history1	history2
	Silicon	ppm	ASTM D5185(m)	>15	1		
	Sodium	ppm	ASTM D5185(m)		0		
				>20	5		
	Potassium	ppm	ASTM D5185(m)	20	0		
	Potassium ppm Water	ppm ppm	ASTM D5185(m) ASTM D6304*		<u>▲</u> 467	248	▲ 594
		ppm			4 67		



OIL ANALYSIS REPORT

VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	Visual*	NONE	NONE		
Yellow Metal	scalar	Visual*	NONE	NONE		
Precipitate	scalar	Visual*	NONE	NONE		
Silt	scalar	Visual*	NONE	NONE		
Debris	scalar	Visual*	NONE	NONE		
Sand/Dirt	scalar	Visual*	NONE	NONE		
Appearance	scalar	Visual*	NORML	NORML		
Odor	scalar	Visual*	NORML	NORML		
FLUID PROPERT	IES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D7279(m)	220	190		
SAMPLE IMAGES	6	method	limit/base	current	history1	history2
Color					no image	no image
Bottom					no image	no image
GRAPHS			_			



Sample No.: GTT0001306Recieved: 03 Jan 2024Lab Number: 02606378Diagnosed: 12 Jan 2024Unique Number: 5707464Diagnostician: Bill QuesnelTest Package: IND 2 (Additional Tests: KV40): Bill QuesnelTo discuss this sample report, contact Customer Service at 1-905-847-9300 Ext 26.Test denoted (*) outside scope of accreditation, (m) method modified, (e) tested at external lab.Damages: Seller shall in no event be liable for special, incidental, or consequential damages, of a commercial nature, resulting from any cause.

Baulne Inc 1850 32nd Avenue Montreal, QC CA H8T 3J7 Contact: Paula Carvalho pcarvalho@baulne.ca T: (514)422-0444 F: