

OIL ANALYSIS REPORT

Area **150 Slater Ch#2** [4500054809]

Sample Rating Trend



WATER

Fluid COMP OIL (POE) ISO 68 (--- GAL)

Component Chiller

CARRIER 1710Q19767

DIAGNOSIS	SAMPLE INFORM	MATION	method	limit/base	current	history1	history2
Recommendation	Sample Number		Client Info		GTT0001439	GTT6914	GTT6915
Resample at the next service interval to monitor.	Sample Date		Client Info		31 Oct 2023	05 Apr 2023	01 Mar 2021
Please specify the brand, type, and viscosity of the	Machine Age	hrs	Client Info		0		
oil on your next sample.	Oil Age	hrs	Client Info		0		
Wear	Oil Changed		Client Info		N/A	N/A	N/A
All component wear rates are normal.	Sample Status				ATTENTION	ATTENTION	NORMAL
Contamination	WEAR METALS		mathad	linsit/base	ourropt	biotomut	biotomyO
The elevated moisture content is associated with	WEAR METALS		method	limit/base	current	history1	history2
POE oils which are hygroscopic, and can absorb	Iron	ppm	ASTM D5185(m)	>8	<1	<1	<1
noisture from sampling and processing.	Chromium	ppm	ASTM D5185(m)	>2	0	<1	<1
Fluid Condition	Nickel	ppm	ASTM D5185(m)		<1		
The AN level is acceptable for this fluid. The	Titanium	ppm	ASTM D5185(m)		0		
condition of the oil is suitable for further service.	Silver	ppm	ASTM D5185(m)	>2	0		
	Aluminum	ppm	ASTM D5185(m)	>3	<1	<1	<1
	Lead	ppm	ASTM D5185(m)	>2	<1	<1	<1
	Copper	ppm	ASTM D5185(m)	>8	<1	<1	<1
	Tin	ppm	ASTM D5185(m)	>4	0	<1	<1
	Antimony	ppm	ASTM D5185(m)		0		
	Vanadium	ppm	ASTM D5185(m)		0		
	Beryllium	ppm	ASTM D5185(m)		0		
	Cadmium	ppm	ASTM D5185(m)		0		
	ADDITIVES		method	limit/base	current	history1	history2
	Boron	ppm	ASTM D5185(m)	5	<1		
	Barium	ppm	ASTM D5185(m)	5	0		
	Molybdenum	ppm	ASTM D5185(m)	5	0		
	Manganese	ppm	ASTM D5185(m)		0		
	Magnesium	ppm	ASTM D5185(m)	5	0		
	Calcium	ppm	ASTM D5185(m)	5	0		
	Phosphorus	ppm	ASTM D5185(m)		1499		
	Zinc	ppm	ASTM D5185(m)		2	8	<1
	Sulfur	ppm	ASTM D5185(m)		4		
	Lithium	ppm	ASTM D5185(m)		<1		
	CONTAMINANTS	\$	method	limit/base	current	history1	history2
	Silicon	ppm	ASTM D5185(m)	>15	14		
	Sodium	ppm	ASTM D5185(m)	-	0		
	Potassium	ppm	ASTM D5185(m)	>20	5		
	ppm Water	ppm	ASTM D6304*		▲ 586	▲ 346	192
	FLUID DEGRADA		method	limit/base		history1	history2
	Acid Number (AN)	rng KOH/g	ASTM D974*	0.40	0.06	0.078	0.054



OIL ANALYSIS REPORT

VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	Visual*	NONE	NONE		
Yellow Metal	scalar	Visual*	NONE	NONE		
Precipitate	scalar	Visual*	NONE	NONE		
Silt	scalar	Visual*	NONE	NONE		
Debris	scalar	Visual*	NONE	NONE		
Sand/Dirt	scalar	Visual*	NONE	NONE		
Appearance	scalar	Visual*	NORML	NORML		
Odor	scalar	Visual*	NORML	NORML		
FLUID PROPERT	IES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D7279(m)	68	56.5		
SAMPLE IMAGES	;	method	limit/base	current	history1	history2
Color					no image	no image
Bottom					no image	no image
GRAPHS						



 Sample No.
 : GTT0001439
 Recieved
 : 03 Jan 2024
 C/0 Conduent Div of C

 Lab Number
 : 02606391
 Diagnosed
 : 12 Jan 2024

 Unique Number
 : 5707477
 Diagnostician
 : Bill Quesnel

 Test Package
 : IND 2 (Additional Tests: KV40)
 Co

 To discuss this sample report, contact Customer Service at 1-905-847-9300 Ext 26.
 Brian.F

 Test denoted (*) outside scope of accreditation, (m) method modified, (e) tested at external lab.
 Damages: Seller shall in no event be liable for special, incidental, or consequential damages, of a commercial nature, resulting from any cause.

Carrier Commerical Service C/O Conduent Div of Carrier Canada, 1-2740 Matheson Blvd Mississauga, ON CA L4W 4X3 Contact: Brian Raymundo Brian.Raymundo@carrier.com T: m any cause. F:

Contact/Location: Brian Raymundo - GTT0000224