




OIL ANALYSIS REPORT

Area
RONI
 Machine Id
381
 Component
Diesel Engine
 Fluid
PETRO CANADA 10W30 (--- GAL)

Sample Rating Trend



NORMAL



DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The condition of the oil is acceptable for the time in service.

SAMPLE INFORMATION

	method	limit/base	current	history1	history2
Sample Number	Client Info		WC0888492	---	---
Sample Date	Client Info		23 Dec 2023	---	---
Machine Age	hrs	Client Info	0	---	---
Oil Age	hrs	Client Info	0	---	---
Oil Changed	Client Info		Changed	---	---
Sample Status			NORMAL	---	---

CONTAMINATION

	method	limit/base	current	history1	history2
Fuel	WC Method	>5	<1.0	---	---
Water	WC Method	>0.2	NEG	---	---
Glycol	WC Method		NEG	---	---

WEAR METALS

	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185(m)	>100	23	---
Chromium	ppm	ASTM D5185(m)	>20	<1	---
Nickel	ppm	ASTM D5185(m)	>2	<1	---
Titanium	ppm	ASTM D5185(m)	>2	0	---
Silver	ppm	ASTM D5185(m)	>2	0	---
Aluminum	ppm	ASTM D5185(m)	>25	4	---
Lead	ppm	ASTM D5185(m)	>40	<1	---
Copper	ppm	ASTM D5185(m)	>330	10	---
Tin	ppm	ASTM D5185(m)	>15	<1	---
Antimony	ppm	ASTM D5185(m)		0	---
Vanadium	ppm	ASTM D5185(m)		0	---
Beryllium	ppm	ASTM D5185(m)		0	---
Cadmium	ppm	ASTM D5185(m)		0	---

ADDITIVES

	method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185(m)		13	---
Barium	ppm	ASTM D5185(m)		0	---
Molybdenum	ppm	ASTM D5185(m)		48	---
Manganese	ppm	ASTM D5185(m)		0	---
Magnesium	ppm	ASTM D5185(m)		711	---
Calcium	ppm	ASTM D5185(m)		1333	---
Phosphorus	ppm	ASTM D5185(m)		935	---
Zinc	ppm	ASTM D5185(m)		1164	---
Sulfur	ppm	ASTM D5185(m)		2765	---
Lithium	ppm	ASTM D5185(m)		<1	---

CONTAMINANTS


	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185(m)	>25	6	---
Sodium	ppm	ASTM D5185(m)		15	---
Potassium	ppm	ASTM D5185(m)	>20	4	---

INFRA-RED

	method	limit/base	current	history1	history2
Soot %	%	ASTM D7844*	>3	0	---
Nitration	Abs/cm	ASTM D7624*	>20	10.4	---
Sulfation	Abs./1mm	ASTM D7415*	>30	20.9	---



OIL ANALYSIS REPORT



FLUID DEGRADATION

Method	Limit/Base	Current	History1	History2
Oxidation	Abs.:1mm ASTM D7414*	18.3	---	---









VISUAL

Method	Limit/Base	Current	History1	History2
Emulsified Water	scalar Visual*	NEG	---	---
Free Water	scalar Visual*	NEG	---	---

FLUID PROPERTIES

Method	Limit/Base	Current	History1	History2
Visc @ 100°C	cSt ASTM D7279(m)	11.2	---	---

GRAPHS



Laboratory : WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9 **RONI/IRON SHORE EXCAVATING LTD.**
Sample No. : WC0888492 **Received** : 08 Jan 2024 **100 MACINTOSH BLVD**
Lab Number : 02606920 **Diagnosed** : 08 Jan 2024 **VAUGHAN, ON**
Unique Number : 5708006 **Diagnostician** : Wes Davis **CA L4K 4P3**
Test Package : MOBCE **Contact: Service Team**
service.team@roni.ca

To discuss this sample report, contact Customer Service at 1-800-268-2131.
 Test denoted (*) outside scope of accreditation, (m) method modified, (e) tested at external lab.
 Validity of results and interpretation are based on the sample and information as supplied.