OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL

Area
[4399]
Machine Id
01-013-CE
Component
New (Unused) Oil
Fluid
PETRO CANADA LUMINOL TRI (--- GAL)

DIAGNOSIS

Recommendation
This is a baseline read-out on the submitted sample.

Wear
{not applicable}

Contamination
{not applicable}

Fluid Condition
Pour Point = -60°C.

SAMPLE INFORMATION		method	limit/base	current	history1	history2
Sample Number		Client Info		**PP0000882**	---	---
Sample Date		Client Info		**12 Jan 2024**	---	---
Machine Age	hrs	Client Info		**0**	---	---
Oil Age	hrs	Client Info		**0**	---	---
Oil Changed		Client Info		**N/A**	---	---
Sample Status				**NORMAL**	---	---

CONTAMINATION	method	limit/base	current	history1	history2
Water	WC Method		**NEG**	---	---

WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185(m)	>5	**0**	---	---
Chromium	ppm	ASTM D5185(m)	>5	**0**	---	---
Nickel	ppm	ASTM D5185(m)	>5	**0**	---	---
Titanium	ppm	ASTM D5185(m)		**0**	---	---
Silver	ppm	ASTM D5185(m)	>5	**0**	---	---
Aluminum	ppm	ASTM D5185(m)	>5	**<1**	---	---
Lead	ppm	ASTM D5185(m)	>5	**0**	---	---
Copper	ppm	ASTM D5185(m)	>5	**0**	---	---
Tin	ppm	ASTM D5185(m)	>5	**0**	---	---
Antimony	ppm	ASTM D5185(m)		**0**	---	---
Vanadium	ppm	ASTM D5185(m)		**0**	---	---
Beryllium	ppm	ASTM D5185(m)		**0**	---	---
Cadmium	ppm	ASTM D5185(m)		**0**	---	---

ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185(m)	0	**0**	---	---
Barium	ppm	ASTM D5185(m)	0	**0**	---	---
Molybdenum	ppm	ASTM D5185(m)	0	**0**	---	---
Manganese	ppm	ASTM D5185(m)	0	**0**	---	---
Magnesium	ppm	ASTM D5185(m)	0	**<1**	---	---
Calcium	ppm	ASTM D5185(m)	0	**0**	---	---
Phosphorus	ppm	ASTM D5185(m)	0	**0**	---	---
Zinc	ppm	ASTM D5185(m)	0	**<1**	---	---
Sulfur	ppm	ASTM D5185(m)	10	**0**	---	---
Lithium	ppm	ASTM D5185(m)		**<1**	---	---

CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185(m)	>15	**0**	---	---
Sodium	ppm	ASTM D5185(m)	>5	**0**	---	---
Potassium	ppm	ASTM D5185(m)	>20	**<1**	---	---

VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	Visual*	NONE	**NONE**	---	---
Yellow Metal	scalar	Visual*	NONE	**NONE**	---	---
Precipitate	scalar	Visual*	NONE	**NONE**	---	---
Silt	scalar	Visual*	NONE	**NONE**	---	---
Debris	scalar	Visual*	NONE	**NONE**	---	---
Sand/Dirt	scalar	Visual*	NONE	**NONE**	---	---
Appearance	scalar	Visual*	NORML	**NORML**	---	---
Odor	scalar	Visual*	NORML	**NORML**	---	---

OIL ANALYSIS REPORT

FLUID PROPERTIES		method	limit/base	current	history1	history2
Pour Point	°C	ASTM D97*	-60	**-60**	---	---

SAMPLE IMAGES	method	limit/base	current	history1	history2
Color				*no image*	*no image*
Bottom				*no image*	*no image*

GRAPHS

ISO 17025:2017 Accredited Laboratory

Laboratory : WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9
Sample No. : PP0000882 **Recieved** : 15 Jan 2024
Lab Number : 02608825 **Diagnosed** : 15 Jan 2024
Unique Number : 5709911 **Diagnostician** : Kevin Marson
Test Package : TEST (Additional Tests: ICP, PourPt, Visual)

To discuss this sample report, contact Customer Service at 1-800-268-2131.
Test denoted (*) outside scope of accreditation, (m) method modified, (e) tested at external lab.
Validity of results and interpretation are based on the sample and information as supplied.

Oleo Energies
5800 Thorold Stone Road
Niagara Falls, ON
CA L2J 1A2
Contact: Mark Michalkoff
mmichalkoff@oleoenergies.com
T: (905)358-5133
F: