



# OIL ANALYSIS REPORT


Sample Rating Trend

**NORMAL**



Area  
**OZR/BD09**  
Machine Id  
**101903 SC Drive**

Component  
**Gearbox**  
Fluid  
**MOBIL MOBILGEAR 600 XP 320 (140 LTR)**



## DIAGNOSIS

### Recommendation

Resample at the next service interval to monitor.

### Wear

All component wear rates are normal.

### Contamination

There is no indication of any contamination in the oil.

### Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

## SAMPLE INFORMATION

method	limit/base	current	history1	history2
Sample Number	Client Info	<b>WC0855087</b>	WC0790639	WC0763684
Sample Date	Client Info	<b>19 Dec 2023</b>	20 Jun 2023	12 Dec 2022
Machine Age	hrs	Client Info	<b>0</b>	0
Oil Age	hrs	Client Info	<b>0</b>	0
Oil Changed	Client Info	<b>N/A</b>	N/A	N/A
Sample Status		<b>NORMAL</b>	NORMAL	NORMAL

## CONTAMINATION

method	limit/base	current	history1	history2
Water	WC Method >0.2	<b>NEG</b>	NEG	NEG

## WEAR METALS

method	limit/base	current	history1	history2	
PQ	ASTM D8184*	<b>0</b>	29	22	
Iron	ppm	ASTM D5185(m) >200	<b>28</b>	64	59
Chromium	ppm	ASTM D5185(m) >15	<b>0</b>	<1	0
Nickel	ppm	ASTM D5185(m) >15	<b>&lt;1</b>	<1	<1
Titanium	ppm	ASTM D5185(m)	<b>0</b>	0	0
Silver	ppm	ASTM D5185(m)	<b>0</b>	0	0
Aluminum	ppm	ASTM D5185(m) >25	<b>&lt;1</b>	0	<1
Lead	ppm	ASTM D5185(m) >100	<b>&lt;1</b>	1	1
Copper	ppm	ASTM D5185(m) >200	<b>&lt;1</b>	<1	<1
Tin	ppm	ASTM D5185(m) >25	<b>0</b>	0	0
Antimony	ppm	ASTM D5185(m) >5	<b>0</b>	0	<1
Vanadium	ppm	ASTM D5185(m)	<b>0</b>	0	0
Beryllium	ppm	ASTM D5185(m)	<b>0</b>	0	0
Cadmium	ppm	ASTM D5185(m)	<b>0</b>	0	0

## ADDITIVES

method	limit/base	current	history1	history2	
Boron	ppm	ASTM D5185(m)	<b>24</b>	9	11
Barium	ppm	ASTM D5185(m)	<b>0</b>	0	0
Molybdenum	ppm	ASTM D5185(m)	<b>0</b>	0	0
Manganese	ppm	ASTM D5185(m)	<b>0</b>	1	1
Magnesium	ppm	ASTM D5185(m)	<b>&lt;1</b>	<1	<1
Calcium	ppm	ASTM D5185(m)	<b>1</b>	4	3
Phosphorus	ppm	ASTM D5185(m)	<b>329</b>	333	340
Zinc	ppm	ASTM D5185(m)	<b>5</b>	16	14
Sulfur	ppm	ASTM D5185(m)	<b>9817</b>	14367	15059
Lithium	ppm	ASTM D5185(m)	<b>&lt;1</b>	<1	<1

## CONTAMINANTS




method	limit/base	current	history1	history2	
Silicon	ppm	ASTM D5185(m) >50	<b>3</b>	10	8
Sodium	ppm	ASTM D5185(m)	<b>0</b>	<1	<1
Potassium	ppm	ASTM D5185(m) >20	<b>1</b>	<1	0

## FLUID DEGRADATION

method	limit/base	current	history1	history2	
Acid Number (AN)	mg KOH/g	ASTM D974*	<b>0.74</b>	0.75	0.76




# OIL ANALYSIS REPORT








VISUAL	method	limit/base	current	history1	history2
White Metal	scalar	Visual*	NONE	NONE	NONE
Yellow Metal	scalar	Visual*	NONE	NONE	NONE
Precipitate	scalar	Visual*	NONE	NONE	NONE
Silt	scalar	Visual*	NONE	NONE	NONE
Debris	scalar	Visual*	NONE	NONE	NONE
Sand/Dirt	scalar	Visual*	NONE	NONE	NONE
Appearance	scalar	Visual*	NORML	NORML	NORML
Odor	scalar	Visual*	NORML	NORML	NORML
Emulsified Water	scalar	Visual*	>0.2	NEG	.2%
Free Water	scalar	Visual*		NEG	NEG

FLUID PROPERTIES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D7279(m)	320	310	312

SAMPLE IMAGES	method	limit/base	current	history1	history2
---------------	--------	------------	---------	----------	----------



## GRAPHS



**Laboratory** : WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9  
**Sample No.** : WC0855087 **Recieved** : 18 Jan 2024  
**Lab Number** : 02609784 **Diagnosed** : 19 Jan 2024  
**Unique Number** : 5710870 **Diagnostician** : Wes Davis  
**Test Package** : IND 2 ( Additional Tests: TAN Man )

To discuss this sample report, contact Customer Service at 1-800-268-2131.  
 Test denoted (\*) outside scope of accreditation, (m) method modified, (e) tested at external lab.  
 Validity of results and interpretation are based on the sample and information as supplied.

**MICHELIN TIRE**  
 866 RANDOLPH RD  
 WATERVILLE, NS  
 CA B0P 1V0  
 Contact: Alan Davies  
 alan.davies@michelin.com  
 T: (902)534-3590  
 F: x: