

## **OIL ANALYSIS REPORT**

## Berry Plastics - 888068 **AG241** Component

**Hydraulic System** AW 32 or 46 (--- GAL)

#### Recommendation

This is a baseline read-out on the submitted sample.

### Wear

{not applicable}

#### Contamination

The sample submitted is 2 times dirtier than the ISO dirt count recommendation of 19/16/14.

### Fluid Condition

{not applicable}

				Jan 2024			
SAMPLE INFORM	1ATION	method	limit/base	current	history1	history2	
Machine ID		Client Info		Downstair Cast			
Department		Client Info		Sales			
Sample From		Client Info		Machine			
Production Stage		Client Info		Initial			
Sent to WC		Client Info		01/17/2024			
Sample Number		Client Info		E30001165			
Sample Date		Client Info		12 Jan 2024			
Machine Age	hrs	Client Info		0			
Dil Age	hrs	Client Info		0			
Dil Changed		Client Info		N/A			
Sample Status				NORMAL			
WEAR METALS		method	limit/base	current	history1	history2	
ron	ppm	ASTM D5185(m)	>20	0			
Chromium	ppm	ASTM D5185(m)	>20	0			
Nickel	ppm	ASTM D5185(m)	>20	0			
Fitanium	ppm	ASTM D5185(m)		0			
Silver	ppm	ASTM D5185(m)		0			
Aluminum	ppm	ASTM D5185(m)	>20	<1			
_ead	ppm	ASTM D5185(m)	>20	<1			
Copper	ppm	ASTM D5185(m)	>20	2			
Tin	ppm	ASTM D5185(m)	>20	0			
Antimony	ppm	ASTM D5185(m)		0			
Vanadium	ppm	ASTM D5185(m)		0			
Beryllium	ppm	ASTM D5185(m)		0			
Cadmium	ppm	ASTM D5185(m)		0			
ADDITIVES		method	limit/base	current	history1	history2	
Boron	ppm	ASTM D5185(m)		0			
Barium	ppm	ASTM D5185(m)		0			
Nolybdenum	ppm	ASTM D5185(m)		0			
Manganese	ppm	ASTM D5185(m)		0			
Magnesium	ppm	ASTM D5185(m)		<1			
Calcium	ppm	ASTM D5185(m)		63			
Phosphorus	ppm	ASTM D5185(m)		343			
Zinc	ppm	ASTM D5185(m)		434			
Sulfur	ppm	ASTM D5185(m)		1429			
Lithium	ppm	ASTM D5185(m)		<1			
		method	limit/base	current	history1	history2	
CONTAMINANTS							
	ppm	ASTM D5185(m)	>15	<1			
Silicon			>15	<1 0			
CONTAMINANTS Silicon Sodium Potassium	ppm	ASTM D5185(m)	>15 >20				
Silicon Sodium	ppm ppm	ASTM D5185(m) ASTM D5185(m)		0			


Sample Rating Trend





NORMAL




# **OIL ANALYSIS REPORT**









FLUID CLEANLIN	ESS	method	limit/base	current	history1	history2
Particles >4µm		ASTM D7647	>10000	9548		
Particles >6µm		ASTM D7647	>2500	1753		
Particles >14µm		ASTM D7647	>320	41		
Particles >21µm		ASTM D7647	>80	6		
Particles >38µm		ASTM D7647	>20	1		
Particles >71µm		ASTM D7647	>4	0		
Oil Cleanliness		ISO 4406 (c)	>20/18/15	20/18/13		
FLUID DEGRADA	TION	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D974*		0.31		
VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	Visual*	NONE	NONE		
Yellow Metal	scalar	Visual*	NONE	NONE		
Precipitate	scalar	Visual*	NONE	NONE		
Silt	scalar	Visual*	NONE	NONE		
Debris	scalar	Visual*	NONE	NONE		
Sand/Dirt	scalar	Visual*	NONE	NONE		
Appearance	scalar	Visual*	NORML	NORML		
Odor	scalar	Visual*	NORML	NORML		
Emulsified Water	scalar	Visual*	>0.05	NEG		
Free Water	scalar	Visual*		NEG		
FLUID PROPERT	IES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D7279(m)		33.7		
Visc @ 100°C	cSt	ASTM D7279(m)		5.7		
Viscosity Index (VI)	Scale	ASTM D2270*		108		
SAMPLE IMAGES	;	method	limit/base	current	history1	history2
Color					no image	no image
					no image	no image

: WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9 Environmental 360 Solutions Ltd. : E30001165 Recieved : 19 Jan 2024 640 Victoria Street : 02609961 Diagnosed : 23 Jan 2024 Cobourg, ON Accredited Laboratory Unique Number : 5711047 Diagnostician : Tatiana Sorkina CA K9A 5H5 Test Package : IND 2 (Additional Tests: KF, KV100, VI) Contact: Tatiana Sorkina To discuss this sample report, contact Customer Service at 1-905-372-2251. tsorkina@e360s.ca T: (800)263-3939 Test denoted (\*) outside scope of accreditation, (m) method modified, (e) tested at external lab. Validity of results and interpretation are based on the sample and information as supplied. F: (905)373-4950