




OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL



Area
Hyatt Hotel. Ch#1 [794661]
Machine Id
CARRIER 42333
Component
Chiller
Fluid
SHELL TELLUS T68 (17 GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

The increased readings on copper, zinc and the oil acid number are all associated with the effects of additives blended in this oil formula. All component wear rates are normal.

Contamination

The water content is negligible. There is no indication of any contamination in the oil.

Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

SAMPLE INFORMATION

	method	limit/base	current	history1	history2
Sample Number	Client Info		GTT0000985	GTT13864	GTT13865
Sample Date	Client Info		03 Jan 2024	18 Apr 2023	22 Feb 2022
Machine Age	yrs	Client Info	0	---	---
Oil Age	yrs	Client Info	5	---	---
Oil Changed	Client Info		Not Chngd	N/A	N/A
Sample Status			NORMAL	ABNORMAL	ABNORMAL

WEAR METALS

	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185(m) >8	2	<1	1
Chromium	ppm	ASTM D5185(m) >2	0	<1	<1
Nickel	ppm	ASTM D5185(m)	0	---	---
Titanium	ppm	ASTM D5185(m)	0	---	---
Silver	ppm	ASTM D5185(m) >2	0	---	---
Aluminum	ppm	ASTM D5185(m) >3	<1	<1	<1
Lead	ppm	ASTM D5185(m) >2	11	<1	<1
Copper	ppm	ASTM D5185(m) >8	405	143	202
Tin	ppm	ASTM D5185(m) >4	0	<1	<1
Antimony	ppm	ASTM D5185(m)	0	---	---
Vanadium	ppm	ASTM D5185(m)	0	---	---
Beryllium	ppm	ASTM D5185(m)	0	---	---
Cadmium	ppm	ASTM D5185(m)	0	---	---

ADDITIVES

	method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185(m)	<1	---	---
Barium	ppm	ASTM D5185(m)	0	---	---
Molybdenum	ppm	ASTM D5185(m)	0	---	---
Manganese	ppm	ASTM D5185(m)	0	---	---
Magnesium	ppm	ASTM D5185(m)	<1	---	---
Calcium	ppm	ASTM D5185(m) 48	34	---	---
Phosphorus	ppm	ASTM D5185(m) 377	278	---	---
Zinc	ppm	ASTM D5185(m) 426	176	76	126
Sulfur	ppm	ASTM D5185(m) 2300	2489	---	---
Lithium	ppm	ASTM D5185(m)	<1	---	---

CONTAMINANTS

	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185(m) >15	3	---	---
Sodium	ppm	ASTM D5185(m)	<1	---	---
Potassium	ppm	ASTM D5185(m) >20	2	---	---
ppm Water	ppm	ASTM D6304* >100	17	93	53



FLUID DEGRADATION

	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D974* .6	0.19	▲ 0.225	▲ 0.312

OIL ANALYSIS REPORT

VISUAL	method	limit/base	current	history1	history2
White Metal	scalar	Visual*	NONE	NONE	---
Yellow Metal	scalar	Visual*	NONE	NONE	---
Precipitate	scalar	Visual*	NONE	NONE	---
Silt	scalar	Visual*	NONE	NONE	---
Debris	scalar	Visual*	NONE	NONE	---
Sand/Dirt	scalar	Visual*	NONE	NONE	---
Appearance	scalar	Visual*	NORML	NORML	---
Odor	scalar	Visual*	NORML	NORML	---

FLUID PROPERTIES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D7279(m)	67.88	40.3	---

SAMPLE IMAGES	method	limit/base	current	history1	history2
Color				no image	no image
Bottom				no image	no image

GRAPHS



Sample No. : GTT0000985 **Recieved** : 19 Jan 2024
Lab Number : **02610074** **Diagnosed** : 24 Jan 2024
Unique Number : 5711160 **Diagnostician** : Bill Quesnel
Test Package : IND 2 (Additional Tests: KV40)

*To discuss this sample report, contact Customer Service at 1-905-847-9300 Ext 26.
 Test denoted (*) outside scope of accreditation, (m) method modified, (e) tested at external lab.
 Damages: Seller shall in no event be liable for special, incidental, or consequential damages, of a commercial nature, resulting from any cause.*

Ainsworth Electric
 131 Bermondsey Road
 Toronto, ON
 CA M4A 1X4
 Contact: Service Manager
 invoices@ainsworth.com
 T: (905)694-6302
 F: