



OIL ANALYSIS REPORT

Sample Rating Trend

NORMAL



Area
ORIN CONTRACTORS
 Machine Id
880
 Component
Diesel Engine
 Fluid
PETRO CANADA 10W30 (--- GAL)



DIAGNOSIS

Recommendation
 Resample at the next service interval to monitor.

Wear
 All component wear rates are normal.

Contamination
 There is no indication of any contamination in the oil.

Fluid Condition
 The condition of the oil is acceptable for the time in service.

SAMPLE INFORMATION

	method	limit/base	current	history1	history2
Sample Number	Client Info		WC0899522	---	---
Sample Date	Client Info		23 Feb 2024	---	---
Machine Age	hrs	Client Info	0	---	---
Oil Age	hrs	Client Info	0	---	---
Oil Changed	Client Info		Changed	---	---
Sample Status			NORMAL	---	---

CONTAMINATION

	method	limit/base	current	history1	history2
Fuel	WC Method	>2.1	<1.0	---	---
Water	WC Method	>0.21	NEG	---	---
Glycol	WC Method		NEG	---	---

WEAR METALS

	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185(m)	>51	17	---
Chromium	ppm	ASTM D5185(m)	>11	<1	---
Nickel	ppm	ASTM D5185(m)	>5	<1	---
Titanium	ppm	ASTM D5185(m)		0	---
Silver	ppm	ASTM D5185(m)	>3	0	---
Aluminum	ppm	ASTM D5185(m)	>31	6	---
Lead	ppm	ASTM D5185(m)	>26	1	---
Copper	ppm	ASTM D5185(m)	>26	7	---
Tin	ppm	ASTM D5185(m)	>4	<1	---
Antimony	ppm	ASTM D5185(m)		0	---
Vanadium	ppm	ASTM D5185(m)		0	---
Beryllium	ppm	ASTM D5185(m)		0	---
Cadmium	ppm	ASTM D5185(m)		0	---

ADDITIVES

	method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185(m)		4	---
Barium	ppm	ASTM D5185(m)		0	---
Molybdenum	ppm	ASTM D5185(m)		62	---
Manganese	ppm	ASTM D5185(m)		0	---
Magnesium	ppm	ASTM D5185(m)		888	---
Calcium	ppm	ASTM D5185(m)		1006	---
Phosphorus	ppm	ASTM D5185(m)		928	---
Zinc	ppm	ASTM D5185(m)		1089	---
Sulfur	ppm	ASTM D5185(m)		2458	---
Lithium	ppm	ASTM D5185(m)		<1	---

CONTAMINANTS


	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185(m)	>22	8	---
Sodium	ppm	ASTM D5185(m)		2	---
Potassium	ppm	ASTM D5185(m)	>20	<1	---

INFRA-RED

	method	limit/base	current	history1	history2
Soot %	%	ASTM D7844*	>3	0.2	---
Nitration	Abs/cm	ASTM D7624*	>20	8.7	---
Sulfation	Abs./1mm	ASTM D7415*	>30	20.0	---



OIL ANALYSIS REPORT



FLUID DEGRADATION		method	limit/base	current	history1	history2
-------------------	--	--------	------------	---------	----------	----------

Oxidation	Abs./1mm	ASTM D7414*	>25	17.5	---	---
-----------	----------	-------------	-----	-------------	-----	-----

VISUAL		method	limit/base	current	history1	history2
--------	--	--------	------------	---------	----------	----------









Emulsified Water	scalar	Visual*	>0.21	NEG	---	---
------------------	--------	---------	-------	------------	-----	-----

Free Water	scalar	Visual*		NEG	---	---
------------	--------	---------	--	------------	-----	-----

FLUID PROPERTIES		method	limit/base	current	history1	history2
------------------	--	--------	------------	---------	----------	----------

Visc @ 100°C	cSt	ASTM D7279(m)		12.4	---	---
--------------	-----	---------------	--	-------------	-----	-----

GRAPHS



Laboratory : WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9
Sample No. : WC0899522 **Received** : 11 Mar 2024
Lab Number : **02621062** **Tested** : 11 Mar 2024
Unique Number : 5746181 **Diagnosed** : 11 Mar 2024 - Wes Davis
Test Package : MOBCE

RONI/IRON SHORE EXCAVATING LTD.
 100 MACINTOSH BLVD
 VAUGHAN, ON
 CA L4K 4P3
 Contact: Service Team
 service.team@roni.ca

To discuss this sample report, contact Customer Service at 1-800-268-2131.
 Test denoted (*) outside scope of accreditation, (m) method modified, (e) tested at external lab.
 Validity of results and interpretation are based on the sample and information as supplied.

T:
F: