

Chem-Ecol

A2403035

OIL ANALYSIS REPORT

Sample Rating Trend







Component Unknown Component Fluid CHEM-ECOL GREENLUBE 46 (--- GAL)

DIAGNOSIS

Recommendation

We certify this oil to be clean, that the additives are at acceptable levels and the oil is suitable for use.

Wear

Copper and iron ppm levels are noted.


Fluid Condition


Sodium ppm levels are notably high.


SAMPLE INFORM	IATION	method	limit/base	current	history1	history2
Batch #		Client Info		3026-A		
Department		Client Info		Production		
Sample From		Client Info		Machine		
Production Stage		Client Info		Final		
Sent to WC		Client Info		03/07/2024		
Sample Number		Client Info		E30001528		
Sample Date		Client Info		06 Mar 2024		
Machine Age	hrs	Client Info		0		
Oil Age	hrs	Client Info		0		
Oil Changed		Client Info		N/A		
Sample Status				NORMAL		
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185(m)		41		
Chromium	ppm	ASTM D5185(m)		0		
Nickel	ppm	ASTM D5185(m)		<1		
Titanium	ppm	ASTM D5185(m)		0		
Silver	ppm	ASTM D5185(m)		0		
Aluminum	ppm	ASTM D5185(m)		5		
Lead	ppm	ASTM D5185(m)		2		
Copper	ppm	ASTM D5185(m)		12		
Tin	ppm	ASTM D5185(m)		0		
Antimony	ppm	ASTM D5185(m)		0		
Vanadium	ppm	ASTM D5185(m)		0		
Beryllium	ppm	ASTM D5185(m)		0		
Cadmium	ppm	ASTM D5185(m)		0		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185(m)		0		
Barium	ppm	ASTM D5185(m)		7		
Molybdenum	ppm	ASTM D5185(m)		0		
Manganese	ppm	ASTM D5185(m)		0		
Magnesium	ppm	ASTM D5185(m)		166		
Calcium	ppm	ASTM D5185(m)		134		
Phosphorus	ppm	ASTM D5185(m)		910		
Zinc	ppm	ASTM D5185(m)		977		
Sulfur	ppm	ASTM D5185(m)		2192		
Lithium	ppm	ASTM D5185(m)		<1		
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185(m)		2		
Sodium	ppm	ASTM D5185(m)		10		
Potassium	ppm	ASTM D5185(m)	>20	<1		
Water	%	ASTM D6304*		0.004		
ppm Water	ppm	ASTM D6304*		45		



OIL ANALYSIS REPORT







FLUID CLEANLINESS method limit/base current history1 history1 Particles >4μm ASTM D7647 >5000 282 Particles >6μm ASTM D7647 >640 104 Particles >6μm ASTM D7647 >160 8 Particles >14μm ASTM D7647 >160 8 Particles >21μm ASTM D7647 >40 2 Particles >38μm ASTM D7647 >10 1 Particles >71μm ASTM D7647 >3 1 Particles >71μm ASTM D7647 >3 1 Oil Cleanliness ISO 4406 (c) >19/16/14 15/14/10 FLUID DEGRADATION method limit/base current history1 history1	ry2
Particles >6μm ASTM D7647 >640 104 Particles >14μm ASTM D7647 >160 8 Particles >14μm ASTM D7647 >160 2 Particles >21μm ASTM D7647 >40 2 Particles >38μm ASTM D7647 >10 1 Particles >71μm ASTM D7647 >3 1 Oil Cleanliness ISO 4406 (c) >19/16/14 15/14/10	
Particles >14μm ASTM D7647 >160 8 Particles >21μm ASTM D7647 >40 2 Particles >38μm ASTM D7647 >10 1 Particles >38μm ASTM D7647 >3 1 Particles >71μm ASTM D7647 >3 1 Oil Cleanliness ISO 4406 (c) >19/16/14 15/14/10	
Particles >21μm ASTM D7647 >40 2 Particles >38μm ASTM D7647 >10 1 Particles >71μm ASTM D7647 >3 1 Oil Cleanliness ISO 4406 (c) >19/16/14 15/14/10	
Particles >38μm ASTM D7647 >10 1 Particles >71μm ASTM D7647 >3 1 Oil Cleanliness ISO 4406 (c) >19/16/14 15/14/10	
Particles >71µm ASTM D7647 >3 1 Oil Cleanliness ISO 4406 (c) >19/16/14 15/14/10	
Oil Cleanliness ISO 4406 (c) >19/16/14 15/14/10	
FLUID DEGRADATION method limit/base current history1 histo	
Teore bear induced initial and carrow initiality initial	ry2
Acid Number (AN) mg KOH/g ASTM D974* 1.36	
VISUAL method limit/base current history1 histo	ry2
White Metal scalar Visual* NONE NONE	
Yellow Metal scalar Visual* NONE NONE	
Precipitate scalar Visual* NONE NONE	
Silt scalar Visual* NONE NONE	
Debris scalar Visual* NONE NONE	
Sand/Dirt scalar Visual* NONE NONE	
Appearance scalar Visual* NORML NORML	
Odor scalar Visual* NORML NORML	
Emulsified Water scalar Visual* NEG	
Free Water scalar Visual* NEG	
FLUID PROPERTIES method limit/base current history1 histo	ry2
Visc @ 40°C cSt ASTM D7279(m) 46 48.3	
Visc @ 100°C cSt ASTM D7279(m) 7.3	
Viscosity Index (VI) Scale ASTM D2270* 111	
SAMPLE IMAGES method limit/base current history1 histo	ry2
Color no image no ima	ge
Bottom no image no image	ge

