

OIL ANALYSIS REPORT

Sample Rating Trend






RONI 9-101 Component

Front Left Final Drive

{not provided} (--- GAL)





Recommendation

Resample at the next service interval to monitor. Please specify the brand, type, and viscosity of the oil on your next sample.

All component wear rates are normal.

Contamination

There is no indication of any contamination in the


Fluid Condition

The condition of the oil is acceptable for the time in service.

L)				Mar2024		
SAMPLE INFORM	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		WC0899478		
Sample Date		Client Info		06 Mar 2024		
Machine Age	hrs	Client Info		0		
Oil Age	hrs	Client Info		0		
Oil Changed		Client Info		N/A		
Sample Status				NORMAL		
CONTAMINATION	N	method	limit/base	current	history1	history2
Water		WC Method	>0.2	NEG		
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185(m)	>800	49		
Chromium	ppm	ASTM D5185(m)	>10	0		
Nickel	ppm	ASTM D5185(m)	>5	<1		
Titanium	ppm	ASTM D5185(m)	>15	0		
Silver	ppm	ASTM D5185(m)	>2	0		
Aluminum	ppm	ASTM D5185(m)	>75	8		
Lead	ppm	ASTM D5185(m)	>10	0		
Copper	ppm	ASTM D5185(m)	>75	1		
Tin	ppm	ASTM D5185(m)	>8	0		
Antimony	ppm	ASTM D5185(m)	>50	0		
Vanadium	ppm	ASTM D5185(m)		0		
Beryllium	ppm	ASTM D5185(m)		0		
Cadmium	ppm	ASTM D5185(m)		0		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185(m)		<1		
Barium	ppm	ASTM D5185(m)		0		
Molybdenum	ppm	ASTM D5185(m)		0		
Manganese	ppm	ASTM D5185(m)		0		
Magnesium	ppm	ASTM D5185(m)		926		
Calcium	ppm	ASTM D5185(m)		1055		
Phosphorus	ppm	ASTM D5185(m)		1130		
Zinc	ppm	ASTM D5185(m)		1229		
Sulfur	ppm	ASTM D5185(m)		3722		
Lithium	ppm	ASTM D5185(m)		<1		
CONTAMINANTS	;	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185(m)	>400	32		
Sodium	ppm	ASTM D5185(m)		<1		
Potassium	ppm	ASTM D5185(m)	>20	2		



OIL ANALYSIS REPORT



VISUAL		method	limit/base	current	history1	history2		
White Metal	scalar	Visual*	NONE	VLITE				
Yellow Metal	scalar	Visual*	NONE	NONE				
Precipitate	scalar	Visual*	NONE	NONE				
Silt	scalar	Visual*	NONE	NONE				
Debris	scalar	Visual*	NONE	NONE				
Sand/Dirt	scalar	Visual*	NONE	NONE				
Appearance	scalar	Visual*	NORML	NORML				
Odor	scalar	Visual*	NORML	NORML				
Emulsified Water	scalar	Visual*	>0.2	NEG				
Free Water	scalar	Visual*		NEG				
FLUID PROPER	TIES	method	limit/base	current	history1	history2		
Visc @ 40°C	cSt	ASTM D7279(m)		197				
SAMPLE IMAGE	S	method	limit/base	current	history1	history2		
Color					no image	no image		
Bottom					no image	no image		
GRAPHS								
Iron (ppm)				Lead (ppm)				
Severe			30	Severe				
Abnormal			E 20	Abnormal				
,			- 10					
Mar6/24			Mar6/24	Mar6/24				
Mai			Mai	Ma				
Aluminum (ppm)				Chromium (ppm)				
Severe			30	0				
Abnormal			E 20	Abnormal				
			0					
Mar6/24			Mar6/24	Mar6/24				
Ma			Ma	Ma				
Copper (ppm)				Silicon (ppm)				
Severe			1000	Severe				



CALA ISO 17025:2017 Accredited Laboratory

Laboratory Sample No.

Lab Number : 02621216

St (40°C)

: WC0899478

Received **Tested** Unique Number : 5746335 Diagnosed

: 11 Mar 2024 : 11 Mar 2024 : 11 Mar 2024 - Kevin Marson

: WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9 RONI/IRON SHORE EXCAVATING LTD. 100 MACINTOSH BLVD

Additives

1300

> VAUGHAN, ON CA L4K 4P3 Contact: Service Team

Test Package: MOBCE (Additional Tests: Visual) To discuss this sample report, contact Customer Service at 1-800-268-2131. Test denoted (*) outside scope of accreditation, (m) method modified, (e) tested at external lab.

Validity of results and interpretation are based on the sample and information as supplied.

Viscosity @ 40°C

service.team@roni.ca T:

Report Id: RONVAU [WCAMIS] 02621216 (Generated: 03/11/2024 15:32:05) Rev: 1

F: