




OIL ANALYSIS REPORT

Sample Rating Trend

NORMAL



Area
Compressors [4004082180]
 Machine Id
Low Stage #2 (S/N S0192RFMFTHAA03)
 Component
Rotary Compressor
 Fluid
FRICK COMPRESSOR OIL #3 (40 GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

The water content is negligible. There is no indication of any contamination in the oil.

Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

SAMPLE INFORMATION

method	limit/base	current	history1	history2	
Sample Number	Client Info	WC0900555	WC0436633	WC0861031	
Sample Date	Client Info	26 Feb 2024	02 Oct 2023	25 Sep 2023	
Machine Age	hrs	Client Info	10490	0	75848
Oil Age	hrs	Client Info	0	0	0
Oil Changed	Client Info	Not Chngd	Filtered	N/A	
Sample Status		NORMAL	NORMAL	NORMAL	

WEAR METALS

method	limit/base	current	history1	history2	
PQ	ASTM D8184*	0	0	0	
Iron	ppm	ASTM D5185(m) >70	<1	<1	<1
Chromium	ppm	ASTM D5185(m) >10	0	0	0
Nickel	ppm	ASTM D5185(m)	<1	<1	0
Titanium	ppm	ASTM D5185(m)	0	0	0
Silver	ppm	ASTM D5185(m)	0	<1	<1
Aluminum	ppm	ASTM D5185(m) >3	<1	0	0
Lead	ppm	ASTM D5185(m) >4	0	0	<1
Copper	ppm	ASTM D5185(m) >20	<1	<1	<1
Tin	ppm	ASTM D5185(m) >3	0	0	0
Antimony	ppm	ASTM D5185(m)	0	0	0
Vanadium	ppm	ASTM D5185(m)	0	0	0
Beryllium	ppm	ASTM D5185(m)	0	0	0
Cadmium	ppm	ASTM D5185(m)	0	0	0

ADDITIVES

method	limit/base	current	history1	history2	
Boron	ppm	ASTM D5185(m)	0	<1	<1
Barium	ppm	ASTM D5185(m)	6	6	4
Molybdenum	ppm	ASTM D5185(m)	0	0	0
Manganese	ppm	ASTM D5185(m)	0	0	0
Magnesium	ppm	ASTM D5185(m)	0	0	0
Calcium	ppm	ASTM D5185(m)	<1	1	3
Phosphorus	ppm	ASTM D5185(m)	0	<1	0
Zinc	ppm	ASTM D5185(m)	<1	2	<1
Sulfur	ppm	ASTM D5185(m)	0	20	38
Lithium	ppm	ASTM D5185(m)	<1	<1	<1

CONTAMINANTS





method	limit/base	current	history1	history2	
Silicon	ppm	ASTM D5185(m) >45	0	<1	0
Sodium	ppm	ASTM D5185(m)	0	<1	<1
Potassium	ppm	ASTM D5185(m) >20	<1	0	0
Water	%	ASTM D6304* >0.6	0.00	0.001	0.001
ppm Water	ppm	ASTM D6304*	0	14.8	12.1

FLUID DEGRADATION

method	limit/base	current	history1	history2	
Acid Number (AN)	mg KOH/g	ASTM D974*	0.02	0.01	0.01




OIL ANALYSIS REPORT








VISUAL	method	limit/base	current	history1	history2
White Metal	scalar	Visual*	NONE	NONE	NONE
Yellow Metal	scalar	Visual*	NONE	NONE	NONE
Precipitate	scalar	Visual*	NONE	NONE	NONE
Silt	scalar	Visual*	NONE	NONE	NONE
Debris	scalar	Visual*	NONE	NONE	NONE
Sand/Dirt	scalar	Visual*	NONE	NONE	NONE
Appearance	scalar	Visual*	NORML	NORML	NORML
Odor	scalar	Visual*	NORML	NORML	NORML
Emulsified Water	scalar	Visual*	>0.6	NEG	NEG
Free Water	scalar	Visual*		NEG	NEG

FLUID PROPERTIES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D7279(m)	73	69.8	70.9

SAMPLE IMAGES	method	limit/base	current	history1	history2
---------------	--------	------------	---------	----------	----------



GRAPHS



Laboratory : WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9
Sample No. : WC0900555 **Received** : 13 Mar 2024
Lab Number : **02621787** **Tested** : 14 Mar 2024
Unique Number : 5746906 **Diagnosed** : 14 Mar 2024 - Wes Davis
Test Package : IND 2 (Additional Tests: KF, TAN Man)

To discuss this sample report, contact Customer Service at 1-800-268-2131.
 Test denoted (*) outside scope of accreditation, (m) method modified, (e) tested at external lab.
 Validity of results and interpretation are based on the sample and information as supplied.

Cargill Ltd.
 180 Watson Parkway South
 Guelph, ON
 CA N1L 1K8
 Contact: Eoin Roe
 eoin_roe@cargill.com
 T: (519)823-5200
 F: (416)748-5075