

### **OIL ANALYSIS REPORT**

Sample Rating Trend

NORMAL

# EXTRUDER 340 (S/N 93021413)

Gearbox

#### Fluid SHELL OMALA 220 (12 LTR)

#### DIAGNOSIS

#### Recommendation

Resample at the next service interval to monitor.

#### Wear

All component wear rates are normal.

#### Contamination

There is no indication of any contamination in the oil.


#### Fluid Condition


The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

				Mar2024		
SAMPLE INFORM	IATION	method	limit/base	current	history1	history2
Sample Number		Client Info		WC0883781		
Sample Date		Client Info		07 Mar 2024		
Machine Age	mths	Client Info		0		
Oil Age	mths	Client Info		4		
Oil Changed		Client Info		N/A		
Sample Status				NORMAL		
CONTAMINATION	٧	method	limit/base	current	history1	history2
Water		WC Method	>0.2	NEG		
WEAR METALS		method	limit/base	current	history1	history2
PQ		ASTM D8184*		0		
Iron	ppm	ASTM D5185(m)	>200	3		
Chromium	ppm	ASTM D5185(m)	>15	0		
Nickel	ppm	ASTM D5185(m)	>15	<1		
Titanium	ppm	ASTM D5185(m)		0		
Silver	ppm	ASTM D5185(m)		0		
Aluminum	ppm	ASTM D5185(m)	>25	<1		
Lead	ppm	ASTM D5185(m)	>100	0		
Copper	ppm	ASTM D5185(m)	>200	0		
Tin	ppm	ASTM D5185(m)	>25	0		
Antimony	ppm	ASTM D5185(m)	>5	0		
Vanadium	ppm	ASTM D5185(m)		0		
Beryllium	ppm	ASTM D5185(m)		0		
Cadmium	ppm	ASTM D5185(m)		0		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185(m)	4.4	58		
Barium	ppm	ASTM D5185(m)	0.0	0		
Molybdenum	ppm	ASTM D5185(m)	0	0		
Manganese	ppm	ASTM D5185(m)		0		
Magnesium	ppm	ASTM D5185(m)	0	<1		
Calcium	ppm	ASTM D5185(m)	0	1		
Phosphorus	ppm	ASTM D5185(m)	215	255		
Zinc	ppm	ASTM D5185(m)	0	2		
Sulfur	ppm	ASTM D5185(m)	7039	12338		
Lithium	ppm	ASTM D5185(m)		<1		
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185(m)	>50	4		
Sodium	ppm	ASTM D5185(m)		0		
Potassium	ppm	ASTM D5185(m)	>20	<1		
FLUID DEGRADA		method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D974*		0.42		



## **OIL ANALYSIS REPORT**





VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	Visual*	NONE	VLITE		
Yellow Metal	scalar	Visual*	NONE	NONE		
Precipitate	scalar	Visual*	NONE	NONE		
Silt	scalar	Visual*	NONE	NONE		
Debris	scalar	Visual*	NONE	NONE		
Sand/Dirt	scalar	Visual*	NONE	NONE		
Appearance	scalar	Visual*	NORML	NORML		
Ddor	scalar	Visual*	NORML	NORML		
Emulsified Water	scalar	Visual*	>0.2	NEG		
Free Water		Visual*	20.2	NEG		
	scalar			NEG		
FLUID PROPERT		method	limit/base	current	history1	history2
/isc @ 40°C	cSt	ASTM D7279(m)	220	243		
SAMPLE IMAGES	S	method	limit/base	current	history1	history2
Color					no image	no image
Bottom					no image	no image
GRAPHS		•				
Ferrous Alloys				PQ		
nickel			200 180 160 + 			
Non-ferrous Metal	s		100	Abnormal		
copper lead tin			60 40			
			20	•		
Mar7/24			Mar7/24	Mar7/24		c r
– Viscosity @ 40°C						5 1
Abnormal			(b) 400 (b) 400 (b) 400 (b) 400 (b) 400 (b) 400 (c) 40			
			U.40			
Base			ຍັ 0.30 ສ			
Abnormal			- e 0.20	-		
			2 0.10	•		
Mar7/24 +			Mar7/24 +	Mar7/24		e C F
earCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9 C0883781 <b>Received</b> : 14 Mar 2024 622118 <b>Tested</b> : 14 Mar 2024					<b>Euramax Canac</b> 26 Lorena Stre Barrie, O	
47237 D 2 ( Additional Tes tact Customer Serv	sts: TAN	Man )		es Davis		CA L4N 4P ct: Mark Loma @euramax.cor

To discuss this sample report, of Test denoted (\*) outside scope of accreditation, (m) method modified, (e) tested at external lab. Validity of results and interpretation are based on the sample and information as supplied.

đ

Laboratory

Sample No. Lab Number

**Unique Number Test Package**  T: (705)728-7141 F:

CALA

ISO 17025:2017 Accredited Laboratory