

OIL ANALYSIS REPORT

Sample Rating Trend

NORMAL





Cheo Circ#2 [GTT224-326] Machine Id MCQUAY STNU080600084(2)

Component Chiller

ICI EMKARATE RL 68H (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Moor

All component wear rates are normal.

Contamination

The water content is negligible. There is no indication of any contamination in the oil.

Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

I (GAL)						
				Oct2022		
SAMPLE INFORM	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		GTT0002163		
Sample Date		Client Info		26 Oct 2022		
Machine Age	hrs	Client Info		0		
Oil Age	hrs	Client Info		0		
Oil Changed		Client Info		N/A		
Sample Status				NORMAL		
WEAR METALS		method	limit/base	current	history1	history2
ron	ppm	ASTM D5185(m)	>100	2		
Chromium	ppm	ASTM D5185(m)	>2	0		
Nickel	ppm	ASTM D5185(m)		0		
Titanium	ppm	ASTM D5185(m)		0		
Silver	ppm	ASTM D5185(m)	>2	0		
Aluminum	ppm	ASTM D5185(m)	>50	0		
Lead	ppm	ASTM D5185(m)	>2	0		
Copper	ppm	ASTM D5185(m)	>100	<1		
Tin	ppm	ASTM D5185(m)	>4	0		
Antimony	ppm	ASTM D5185(m)		0		
Vanadium	ppm	ASTM D5185(m)		0		
Beryllium	ppm	ASTM D5185(m)		0		
Cadmium	ppm	ASTM D5185(m)		0		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185(m)	0	0		
Barium	ppm	ASTM D5185(m)	0	0		
Molybdenum	ppm	ASTM D5185(m)	0	0		
Manganese	ppm	ASTM D5185(m)		0		
Magnesium	ppm	ASTM D5185(m)	0	<1		
Calcium	ppm	ASTM D5185(m)	0	0		
Phosphorus	ppm	ASTM D5185(m)	1900	1329		
Zinc	ppm	ASTM D5185(m)	0	<1		
Sulfur	ppm	ASTM D5185(m)	25	19		
Lithium	ppm	ASTM D5185(m)		<1		
CONTAMINANTS	6	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185(m)	>50	19		
Sodium	ppm	ASTM D5185(m)		<1		
Potassium	ppm	ASTM D5185(m)	>20	<1		
opm Water	ppm	ASTM D6304*	>400	183		
FLUID DEGRADA	ATION	method	limit/base	current	history1	history2

Acid Number (AN)

mg KOH/g ASTM D974* 0.02

0.02



OIL ANALYSIS REPORT

VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	Visual*	NONE	NONE		
Yellow Metal	scalar	Visual*	NONE	NONE		
Precipitate	scalar	Visual*	NONE	NONE		
Silt	scalar	Visual*	NONE	NONE		
Debris	scalar	Visual*	NONE	NONE		
Sand/Dirt	scalar	Visual*	NONE	NONE		
Appearance	scalar	Visual*	NORML	NORML		
Odor	scalar	Visual*	NORML	NORML		
FLUID PROPERT	IES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D7279(m)	72.3	68.0		
SAMPLE IMAGES	;	method	limit/base	current	history1	history2
Color					no image	no image
Bottom					no image	no image



Report Id: GTT0000875 [WCAMIS] 02622918 (Generated: 03/20/2024 18:34:07) Rev: 1

Sample No. : GTT0002163 Received : 18 Mar 2024 Lab Number : 02622918 Tested : 20 Mar 2024

Unique Number : 5748037 Diagnosed : 20 Mar 2024 - Bill Quesnel

Test Package: IND 2 (Additional Tests: KV40) To discuss this sample report, contact Customer Service at 1-905-847-9300 Ext 26.

Test denoted (*) outside scope of accreditation, (m) method modified, (e) tested at external lab. Damages: Seller shall in no event be liable for special, incidental, or consequential damages, of a commercial nature, resulting from any cause.

Seguin Morris Inc 8-1590 Liverpool Court

Ottawa, ON CA K1B 4L2

Contact: Service Manager ottawainvoices@seguinmorris.com

T: (613)233-7538