OIL ANALYSIS REPORT

Sample Rating Trend



WEAR

Machine Id
SS 1-6
Component
Gearbox
Fluid
GEAR OIL ISO 150 (--- LTR)

DIAGNOSIS

Recommendation

Little or no information is provided as to the component and lubricant being tested. Recommendations are therefore generic in nature and may not apply to the current application. Please forward information as to equipment type, reservoir capacity, lubricant type and any pertinent information to allow for a more accurate assessment. We recommend that you drain the oil from the component if this has not already been done. We recommend an early resample to monitor this condition. NOTE: Please provide information regarding reservoir capacity, filter type and micron rating with next sample. Please specify the brand, type, and viscosity of the oil on your next sample.

Wear

Iron ppm levels are abnormal. The low ferrous density (PQ) index indicates the wear metal levels are due to corrosion.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The oil is no longer serviceable as a result of the abnormal and/or severe wear.

SAMPLE INFORMATION		method	limit/base	current	history1	history2
Sample Number		Client Info		**WC0909073**	WC0877658	---
Sample Date		Client Info		**20 Mar 2024**	05 Dec 2023	---
Machine Age	hrs	Client Info		**0**	0	---
Oil Age	hrs	Client Info		**0**	0	---
Oil Changed		Client Info		**N/A**	N/A	---
Sample Status				**ABNORMAL**	ABNORMAL	---

CONTAMINATION		method	limit/base	current	history1	history2
Water		WC Method	>0.2	**NEG**	NEG	---

WEAR METALS		method	limit/base	current	history1	history2
PQ		ASTM D8184*		**60**	207	---
Iron	ppm	ASTM D5185(m)	>200	▲ **363**	▲ 294	---
Chromium	ppm	ASTM D5185(m)	>15	**2**	3	---
Nickel	ppm	ASTM D5185(m)	>15	**0**	<1	---
Titanium	ppm	ASTM D5185(m)		**0**	0	---
Silver	ppm	ASTM D5185(m)		**0**	<1	---
Aluminum	ppm	ASTM D5185(m)	>25	**0**	<1	---
Lead	ppm	ASTM D5185(m)	>100	**0**	0	---
Copper	ppm	ASTM D5185(m)	>200	**1**	<1	---
Tin	ppm	ASTM D5185(m)	>25	**0**	0	---
Antimony	ppm	ASTM D5185(m)	>5	**0**	0	---
Vanadium	ppm	ASTM D5185(m)		**0**	0	---
Beryllium	ppm	ASTM D5185(m)		**0**	0	---
Cadmium	ppm	ASTM D5185(m)		**0**	0	---

ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185(m)	50	**27**	20	---
Barium	ppm	ASTM D5185(m)	15	**7**	8	---
Molybdenum	ppm	ASTM D5185(m)	15	**0**	0	---
Manganese	ppm	ASTM D5185(m)		**2**	5	---
Magnesium	ppm	ASTM D5185(m)	50	**0**	<1	---
Calcium	ppm	ASTM D5185(m)	50	**4**	12	---
Phosphorus	ppm	ASTM D5185(m)	350	**320**	311	---
Zinc	ppm	ASTM D5185(m)	100	**7**	27	---
Sulfur	ppm	ASTM D5185(m)	12500	**13230**	12382	---
Lithium	ppm	ASTM D5185(m)		**<1**	<1	---

CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185(m)	>50	**1**	3	---
Sodium	ppm	ASTM D5185(m)		**<1**	2	---
Potassium	ppm	ASTM D5185(m)	>20	**0**	1	---

OIL ANALYSIS REPORT

Ferrous Alloys



Viscosity @ 40°C



PQ



VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	Visual*	NONE	**NONE**	NONE	---
Yellow Metal	scalar	Visual*	NONE	**NONE**	NONE	---
Precipitate	scalar	Visual*	NONE	**NONE**	NONE	---
Silt	scalar	Visual*	NONE	**NONE**	NONE	---
Debris	scalar	Visual*	NONE	**NONE**	LIGHT	---
Sand/Dirt	scalar	Visual*	NONE	**NONE**	NONE	---
Appearance	scalar	Visual*	NORML	**NORML**	NORML	---
Odor	scalar	Visual*	NORML	**NORML**	NORML	---
Emulsified Water	scalar	Visual*	>0.2	**NEG**	NEG	---
Free Water	scalar	Visual*		**NEG**	NEG	---

FLUID PROPERTIES		method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D7279(m)	150	**149**	155	---

SAMPLE IMAGES	method	limit/base	current	history1	history2
Color					*no image*
Bottom					*no image*

GRAPHS

Ferrous Alloys



Non-ferrous Metals

Viscosity @ 40°C



PQ



ISO 17025:2017 Accredited Laboratory

Laboratory : WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9
Sample No. : WC0909073 **Received** : 21 Mar 2024
Lab Number : 02623856 **Tested** : 21 Mar 2024
Unique Number : 5748975 **Diagnosed** : 21 Mar 2024 - Kevin Marson
Test Package : IND 1 (Additional Tests: PQ)

To discuss this sample report, contact Customer Service at 1-800-268-2131.
Test denoted (*) outside scope of accreditation, (m) method modified, (e) tested at external lab.
Validity of results and interpretation are based on the sample and information as supplied.

EMF ELECTRICAL SERVICES
2690 SLOUGH STREET
MISSISSAUGA, ON
CA L4T 1G3
Contact: Wilson
Wilson@emfelectrical.ca
T: (905)405-8836
F: