


## **OIL ANALYSIS REPORT**

Sample Rating Trend



NORMAL



# TICO 827-8977

Component

Diesel Engine

**DIESEL ENGINE OIL SAE 15W40 (--- GAL)** 

### Recommendation

Resample at the next service interval to monitor.

All component wear rates are normal.

### Contamination

There is no indication of any contamination in the


### **Fluid Condition**

The condition of the oil is acceptable for the time in service.

			Aug2023	Feb2024		
SAMPLE INFORM	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		WC0889836	WC0818410	
Sample Date		Client Info		23 Feb 2024	11 Aug 2023	
Machine Age	hrs	Client Info		2693	2186	
Oil Age	hrs	Client Info		0	0	
Oil Changed		Client Info		Changed	Changed	
Sample Status				NORMAL	NORMAL	
CONTAMINATION	٧	method	limit/base	current	history1	history2
Fuel		WC Method	>5	<1.0	<1.0	
Water		WC Method	>0.2	NEG	NEG	
Glycol		WC Method		NEG	NEG	
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185(m)	>100	45	61	
Chromium	ppm	ASTM D5185(m)	>20	1	1	
Nickel	ppm	ASTM D5185(m)	>4	<1	<1	
Titanium	ppm	ASTM D5185(m)		0	0	
Silver	ppm	ASTM D5185(m)	>3	0	0	
Aluminum	ppm	ASTM D5185(m)	>20	5	3	
Lead	ppm	ASTM D5185(m)	>40	0	0	
Copper	ppm	ASTM D5185(m)	>330	2	4	
Tin	ppm	ASTM D5185(m)	>15	0	<1	
Antimony	ppm	ASTM D5185(m)		0	0	
Vanadium	ppm	ASTM D5185(m)		0	0	
Beryllium	ppm	ASTM D5185(m)		0	0	
Cadmium	ppm	ASTM D5185(m)		0	0	
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185(m)	250	57	3	
Barium	ppm	ASTM D5185(m)	10	<1	<1	
Molybdenum	ppm	ASTM D5185(m)	100	86	6	
Manganese	ppm	ASTM D5185(m)		0	<1	
Magnesium	ppm	ASTM D5185(m)	450	97	24	
Calcium	ppm	ASTM D5185(m)	3000	2130	2121	
Phosphorus	ppm	ASTM D5185(m)	1150	883	858	
Zinc	ppm	ASTM D5185(m)	1350	1051	971	
Sulfur	ppm	ASTM D5185(m)	4250	2879	2764	
Lithium	ppm	ASTM D5185(m)		<1	<1	
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185(m)	>25	6	7	
Sodium	ppm	ASTM D5185(m)	>158	2	2	
Potassium	ppm	ASTM D5185(m)	>20	1	2	
INFRA-RED		method	limit/base	current	history1	history2
Soot %	%	ASTM D7844*	>3	1.6	1.4	
Nitration	Abs/cm	ASTM D7624*	>20	12.0	10.3	
Sulfation	Abs/.1mm	ASTM D7415*	>30	25.3	23.3	



### **OIL ANALYSIS REPORT**





Visc @ 100°C	cSt	ASTM D7279(m)	14.4	14.7	14.6	
GRAPHS						
Iron (ppm)				Lead (ppm)	)	
Severe				Severe		
150+				60		
Abnormal				Abnormal		
50				20 -		
0				0		_
Aug11/23			Feb23/24	Aug11/23		Feb23/24
			굔		(nnm)	卫
Aluminum (ppm)				Chromium 50	(ррііі)	
40 Severe				40 Severe		
E 30				E 30+		
Abnormal 20				Abnormal 20		 
10				10		
0			55	0 0		<b>→</b>
Aug11/23			Feb23/24	Aug11/23		Feb23/24
Copper (ppm)				⊲ Silicon (ppn	n)	
400 Severe 350 Abnormal				80 Severe		
300				60		
250				50 + E 40 +		
150				30 Abnormal		 
50-				10		 
1/23 1			3/24	1/23 ± 0		Feb23/24
Aug11/23			Feb23/24	Augll		Feb2;
Viscosity @ 100°	С			Soot %		
17 Abnormal				5.0 + Severe		 -
16				4.0		
(S) 15 Base				Abnormal		 -
Abnormal				2.0		 
12-			-	0.0		
Aug11/23			Feb23/24 -	Aug11/23		Feb23/24 -
Aug			퓬	Aug		歪



**CALA** ISO 17025:2017 Accredited Laboratory

Laboratory Sample No.

: WC0889836 Lab Number : 02623927 Unique Number : 5749046 Test Package : MOB 1

: WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9 Received **Tested** 

Diagnosed

: 22 Mar 2024 : 22 Mar 2024

: 22 Mar 2024 - Wes Davis

**BRITANNIA FLEET SERVICES** 1831 SHAWSON DRIVE (SHOP) MISSISSAUGA, ON

CA L4W 1T9

Contact: Tania Henriques tania.henriques@britanniafleet.ca

T: (905)670-4545 F: (905)670-9036

To discuss this sample report, contact Customer Service at 1-800-268-2131. Test denoted (\*) outside scope of accreditation, (m) method modified, (e) tested at external lab. Validity of results and interpretation are based on the sample and information as supplied.