




OIL ANALYSIS REPORT

Sample Rating Trend

WEAR



Machine Id
RACK C (S/N 0908001477)
 Component
Reciprocating Compressor
 Fluid
EMKARATE RL 32H (6 GAL)



DIAGNOSIS

Recommendation

We recommend that you drain the oil from the component if this has not already been done. We recommend an early resample to monitor this condition.

Wear

Iron ppm levels are abnormal.

Contamination

The water content is negligible. There is no indication of any contamination in the oil.

Fluid Condition

The AN level is acceptable for this fluid. The oil is no longer serviceable as a result of the abnormal and/or severe wear.

SAMPLE INFORMATION

	method	limit/base	current	history1	history2
Sample Number	Client Info		WC0826355	WC0725502	WC0600486
Sample Date	Client Info		21 Mar 2024	03 Apr 2023	30 Mar 2022
Machine Age	yrs	Client Info	3	2	1
Oil Age	yrs	Client Info	3	2	1
Oil Changed	Client Info		Not Changed	Not Changed	Filtered
Sample Status			ABNORMAL	NORMAL	NORMAL

WEAR METALS

	method	limit/base	current	history1	history2
PQ	ASTM D8184*		0	0	0
Iron	ppm	ASTM D5185(m) >50	▲ 60	37	4
Chromium	ppm	ASTM D5185(m) >10	<1	<1	0
Nickel	ppm	ASTM D5185(m)	0	<1	<1
Titanium	ppm	ASTM D5185(m)	0	0	0
Silver	ppm	ASTM D5185(m)	0	0	0
Aluminum	ppm	ASTM D5185(m) >25	0	<1	<1
Lead	ppm	ASTM D5185(m) >25	0	<1	0
Copper	ppm	ASTM D5185(m) >50	0	<1	<1
Tin	ppm	ASTM D5185(m) >15	4	<1	<1
Antimony	ppm	ASTM D5185(m)	0	<1	<1
Vanadium	ppm	ASTM D5185(m)	0	0	0
Beryllium	ppm	ASTM D5185(m)	0	0	0
Cadmium	ppm	ASTM D5185(m)	0	0	0

ADDITIVES

	method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185(m) 0	2	3	2
Barium	ppm	ASTM D5185(m) 0	0	0	0
Molybdenum	ppm	ASTM D5185(m) 0	0	0	0
Manganese	ppm	ASTM D5185(m)	0	<1	0
Magnesium	ppm	ASTM D5185(m) 0	<1	<1	<1
Calcium	ppm	ASTM D5185(m) 0	<1	0	<1
Phosphorus	ppm	ASTM D5185(m) 5	<1	0	<1
Zinc	ppm	ASTM D5185(m) 10	7	2	<1
Sulfur	ppm	ASTM D5185(m) 50	12	3	0
Lithium	ppm	ASTM D5185(m)	<1	<1	<1

CONTAMINANTS






	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185(m) >25	5	6	6
Sodium	ppm	ASTM D5185(m)	<1	<1	<1
Potassium	ppm	ASTM D5185(m) >20	<1	1	<1
Water	%	ASTM D6304* >0.1	0.013	0.010	---
ppm Water	ppm	ASTM D6304* >1000	138	107.3	---

FLUID DEGRADATION

	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D974* .05	0.04	0.03	0.02




OIL ANALYSIS REPORT








VISUAL	method	limit/base	current	history1	history2
White Metal	scalar	Visual*	NONE	NONE	NONE
Yellow Metal	scalar	Visual*	NONE	NONE	NONE
Precipitate	scalar	Visual*	NONE	NONE	NONE
Silt	scalar	Visual*	NONE	NONE	NONE
Debris	scalar	Visual*	NONE	NONE	NONE
Sand/Dirt	scalar	Visual*	NONE	NONE	NONE
Appearance	scalar	Visual*	NORML	NORML	NORML
Odor	scalar	Visual*	NORML	FREON	FREON
Emulsified Water	scalar	Visual*	>0.1	NEG	NEG
Free Water	scalar	Visual*		NEG	NEG

FLUID PROPERTIES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D7279(m)	31.5	29.3	29.7

SAMPLE IMAGES	method	limit/base	current	history1	history2
---------------	--------	------------	---------	----------	----------



GRAPHS



Laboratory : WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9
Sample No. : WC0826355 **Received** : 22 Mar 2024
Lab Number : 02623961 **Tested** : 22 Mar 2024
Unique Number : 5749080 **Diagnosed** : 22 Mar 2024 - Kevin Marson
Test Package : IND 2 (Additional Tests: KF, TAN Man)

Parson Refrigeration (1985) Ltd.
 37 Capital Drive
 Ottawa, ON
 CA K2G 0E7
 Contact: Jim Brown
 jim@parsonref.ca
 T: (613)232-1171
 F: (613)232-2498

To discuss this sample report, contact Customer Service at 1-800-268-2131.
 Test denoted (*) outside scope of accreditation, (m) method modified, (e) tested at external lab.
 Validity of results and interpretation are based on the sample and information as supplied.