




OIL ANALYSIS REPORT

Sample Rating Trend

NORMAL



Area
FORD PERFORMANCE
 Machine Id
FRICK COMPRESSOR #2 (S/N 0541)
 Component
Screw Compressor
 Fluid
CIMCO TYPE A (50 GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

The water content is negligible. There is no indication of any contamination in the oil.

Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

SAMPLE INFORMATION

	method	limit/base	current	history1	history2
Sample Number	Client Info		WC0885231	WC0778476	---
Sample Date	Client Info		29 Jan 2024	07 Feb 2023	---
Machine Age	hrs	Client Info	5405	84767	---
Oil Age	hrs	Client Info	5405	0	---
Oil Changed	Client Info		N/A	Not Chngd	---
Sample Status			NORMAL	NORMAL	---

WEAR METALS

	method	limit/base	current	history1	history2
PQ	ASTM D8184*		0	0	---
Iron	ppm	ASTM D5185(m) >60	<1	<1	---
Chromium	ppm	ASTM D5185(m) >4	0	0	---
Nickel	ppm	ASTM D5185(m)	0	0	---
Titanium	ppm	ASTM D5185(m)	0	0	---
Silver	ppm	ASTM D5185(m)	0	0	---
Aluminum	ppm	ASTM D5185(m) >5	0	<1	---
Lead	ppm	ASTM D5185(m) >10	0	0	---
Copper	ppm	ASTM D5185(m) >30	0	0	---
Tin	ppm	ASTM D5185(m) >15	0	0	---
Antimony	ppm	ASTM D5185(m)	0	0	---
Vanadium	ppm	ASTM D5185(m)	0	0	---
Beryllium	ppm	ASTM D5185(m)	0	0	---
Cadmium	ppm	ASTM D5185(m)	0	0	---

ADDITIVES

	method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185(m)	0	<1	---
Barium	ppm	ASTM D5185(m)	<1	0	---
Molybdenum	ppm	ASTM D5185(m)	0	0	---
Manganese	ppm	ASTM D5185(m)	0	0	---
Magnesium	ppm	ASTM D5185(m)	<1	0	---
Calcium	ppm	ASTM D5185(m)	<1	0	---
Phosphorus	ppm	ASTM D5185(m)	0	0	---
Zinc	ppm	ASTM D5185(m)	<1	1	---
Sulfur	ppm	ASTM D5185(m)	6	30	---
Lithium	ppm	ASTM D5185(m)	<1	<1	---

CONTAMINANTS




	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185(m) >50	0	<1	---
Sodium	ppm	ASTM D5185(m)	0	0	---
Potassium	ppm	ASTM D5185(m) >20	<1	0	---
Water	%	ASTM D6304* >0.1	0.001	0.002	---
ppm Water	ppm	ASTM D6304* >1000	6	17.0	---

FLUID DEGRADATION

	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D974* 0.05	0.01	0.01	---




OIL ANALYSIS REPORT








VISUAL	method	limit/base	current	history1	history2	
White Metal	scalar	Visual*	NONE	NONE	NONE	---
Yellow Metal	scalar	Visual*	NONE	NONE	NONE	---
Precipitate	scalar	Visual*	NONE	NONE	NONE	---
Silt	scalar	Visual*	NONE	NONE	NONE	---
Debris	scalar	Visual*	NONE	NONE	NONE	---
Sand/Dirt	scalar	Visual*	NONE	NONE	NONE	---
Appearance	scalar	Visual*	NORML	NORML	NORML	---
Odor	scalar	Visual*	NORML	NORML	NORML	---
Emulsified Water	scalar	Visual*	>0.1	NEG	NEG	---
Free Water	scalar	Visual*		NEG	NEG	---

FLUID PROPERTIES	method	limit/base	current	history1	history2	
Visc @ 40°C	cSt	ASTM D7279(m)	58	56.0	55.1	---

SAMPLE IMAGES	method	limit/base	current	history1	history2
---------------	--------	------------	---------	----------	----------



GRAPHS



Laboratory : WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9
Sample No. : WC0885231 **Received** : 22 Mar 2024
Lab Number : **02623965** **Tested** : 25 Mar 2024
Unique Number : 5749084 **Diagnosed** : 25 Mar 2024 - Wes Davis
Test Package : IND 2 (Additional Tests: KF)

CIMCO Refrigeration
 1551 Corporate Drive
 Burlington, ON
 CA L7L 6M3
 Contact: DAVID PARISE
 DPARISE@ToROMONT.COM
 T: (416)465-7581
 F: (416)465-8815

To discuss this sample report, contact Customer Service at 1-800-268-2131.
 Test denoted (*) outside scope of accreditation, (m) method modified, (e) tested at external lab.
 Validity of results and interpretation are based on the sample and information as supplied.