


# **OIL ANALYSIS REPORT**



[GTT224-336] **CARRIER 4009Q17897(A)** 

Chiller

CASTROL AIRCOL SW 220 (--- GAL)





## Recommendation

Resample at the next service interval to monitor.

All component wear rates are normal.

### Contamination

The water content is negligible. There is no indication of any contamination in the oil.

## **Fluid Condition**

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

/ 220 ( GAL)			Apr2017	Mar2024		
SAMPLE INFORM	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		GTT0001941	GTT12863	
Sample Date		Client Info		06 Mar 2024	07 Apr 2017	
Machine Age	hrs	Client Info		0		
Oil Age	hrs	Client Info		0		
Oil Changed		Client Info		N/A	N/A	
Sample Status				NORMAL	NORMAL	
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185(m)	>8	<1	<1	
Chromium	ppm	ASTM D5185(m)	>2	0	<1	
Nickel	ppm	ASTM D5185(m)		0		
Titanium	ppm	ASTM D5185(m)		0		
Silver	ppm	ASTM D5185(m)	>2	0		
Aluminum	ppm	ASTM D5185(m)	>3	<1	<1	
Lead	ppm	ASTM D5185(m)	>2	0	2	
Copper	ppm	ASTM D5185(m)	>8	<1	<1	
Tin	ppm	ASTM D5185(m)	>4	0	<1	
Antimony	ppm	ASTM D5185(m)		0		
Vanadium	ppm	ASTM D5185(m)		0		
Beryllium	ppm	ASTM D5185(m)		0		
Cadmium	ppm	ASTM D5185(m)		0		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185(m)	0	0		
Barium	ppm	ASTM D5185(m)	0	0		
Molybdenum	ppm	ASTM D5185(m)	0	0		
Manganese	ppm	ASTM D5185(m)	0	0		
Magnesium	ppm	ASTM D5185(m)	0	0		
Calcium	ppm	ASTM D5185(m)	0	0		
Phosphorus	ppm	ASTM D5185(m)	30	29		
Zinc	ppm	ASTM D5185(m)	0	<1	1	
Sulfur	ppm	ASTM D5185(m)	30	37		
Lithium	ppm	ASTM D5185(m)		<1		
CONTAMINANTS	;	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185(m)	>15	4		
Sodium	ppm	ASTM D5185(m)		<1		
Potassium	ppm	ASTM D5185(m)	>20	<1		
ppm Water	ppm	ASTM D6304*	>200	181	77	
FLUID DEGRADA	NOITA	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D974*	0.03	0.11	0.047	



# **OIL ANALYSIS REPORT**

VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	Visual*	NONE	NONE		
Yellow Metal	scalar	Visual*	NONE	NONE		
Precipitate	scalar	Visual*	NONE	NONE		
Silt	scalar	Visual*	NONE	NONE		
Debris	scalar	Visual*	NONE	NONE		
Sand/Dirt	scalar	Visual*	NONE	NONE		
Appearance	scalar	Visual*	NORML	NORML		
Odor	scalar	Visual*	NORML	NORML		
FLUID PROPERT	IES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D7279(m)	220	136		
SAMPLE IMAGES		method	limit/base	current	history1	history2
Color					no image	no image
Bottom					no image	no image
GRAPHS						



 Sample No.
 : GTT0001941
 Received
 : 22 Mar 2024

 Lab Number
 : 02624060
 Tested
 : 26 Mar 2024

 Unique Number
 : 5749179
 Disapposed
 : 38 Mar 2024

Unique Number : 5749179 Diagnosed : 26 Mar 2024 - Bill Quesnel Test Package : IND 2 ( Additional Tests: KV40 )

To discuss this sample report, contact Customer Service at 1-905-847-9300 Ext 26.

Test denoted (\*) outside scope of accreditation, (m) method modified, (e) tested at external lab.

Damages: Seller shall in no event be liable for special, incidental, or consequential damages, of a commercial nature, resulting from any cause.

Cynergy Mechanical Ltd.

34 Leading Road Etobicoke, ON CA M9V 3S9

Contact: Service Manager ap@cynergymechanical.ca

T: (416)749-2200

nmercial nature, resulting from any cause.

Contact/Location: Service Manager - GTT0000446