


# **OIL ANALYSIS REPORT**

# Equipment d'urgence/Salle des Machines 15J02B Compresseur d'air d'urgence (S/N 1401587)

Air Compressor

**MOBIL RARUS 827 (8 LTR)** 



# Sample Rating Trend **WEAR**

## **DIAGNOSIS**

## Recommendation

We recommend that you drain the oil from the component if this has not already been done. We recommend an early resample to monitor this condition.

Tin ppm levels are abnormal. Piston wear is indicated.

## Contamination

The water content is negligible. There is no indication of any contamination in the oil.


## Fluid Condition


The oil is no longer serviceable as a result of the abnormal and/or severe wear.


SAMPLE INFORM	NOITAN	method	limit/base	current	history1	history2
Sample Number		Client Info		WC0878519	WC0477011	WC0392735
Sample Date		Client Info		18 Mar 2024	23 Jun 2021	26 Oct 2020
Machine Age	hrs	Client Info		40	24	50
Oil Age	hrs	Client Info		18	3	50
Oil Changed		Client Info		Not Changd	Not Changd	N/A
Sample Status				ABNORMAL	ABNORMAL	NORMAL
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185(m)	>50	8	8	10
Chromium	ppm	ASTM D5185(m)	>4	0	0	0
Nickel	ppm	ASTM D5185(m)	>4	0	0	<1
Titanium	ppm	ASTM D5185(m)		0	0	0
Silver	ppm	ASTM D5185(m)		0	<1	<1
Aluminum	ppm	ASTM D5185(m)	>10	4	<1	3
Lead	ppm	ASTM D5185(m)	>20	0	0	0
Copper	ppm	ASTM D5185(m)	>40	<1	<1	<1
Tin	ppm	ASTM D5185(m)	>5	<u>^</u> 8	<b>4</b> 9	4
Antimony	ppm	ASTM D5185(m)		0	<1	0
Vanadium	ppm	ASTM D5185(m)		0	0	0
Beryllium	ppm	ASTM D5185(m)		0	0	0
Cadmium	ppm	ASTM D5185(m)		0	0	0
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185(m)		<1	2	<1
Barium	ppm	ASTM D5185(m)		0	0	0
Molybdenum	ppm	ASTM D5185(m)		0	0	0
Manganese	ppm	ASTM D5185(m)		0	0	<1
Magnesium	ppm	ASTM D5185(m)		<1	<1	0
Calcium	ppm	ASTM D5185(m)		0	2	2
Phosphorus	ppm	ASTM D5185(m)		372	387	415
Zinc	ppm	ASTM D5185(m)		<1	1	1
Sulfur	ppm	ASTM D5185(m)		9	456	17
Lithium	ppm	ASTM D5185(m)		<1	<1	<1
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185(m)	>25	0	<1	1
Sodium	ppm	ASTM D5185(m)		<1	<1	1
Potassium	ppm	ASTM D5185(m)	>20	<1	<1	2
Water	%	ASTM D6304*	>0.6	0.010		
ppm Water	ppm	ASTM D6304*	>6000	109		



## **OIL ANALYSIS REPORT**









VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	Visual*	NONE	NONE	NONE	NONE
Yellow Metal	scalar	Visual*	NONE	NONE	NONE	NONE
Precipitate	scalar	Visual*	NONE	NONE	NONE	NONE
Silt	scalar	Visual*	NONE	NONE	NONE	NONE
Debris	scalar	Visual*	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	Visual*	NONE	NONE	NONE	NONE
Appearance	scalar	Visual*	NORML	NORML	NORML	NORML
Odor	scalar	Visual*	NORML	NORML	NORML	NORML
<b>Emulsified Water</b>	scalar	Visual*	>0.6	NEG	NEG	NEG
Free Water	scalar	Visual*		NEG	NEG	NEG
ELLID DDODEDT	150		11 11 11		1111	111 0
FLUID PROPERTIES		method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D7279(m)	107.5	108	107	106
SAMPLE IMAGES		method	limit/hasa	current	history1	history2


Color






## **GRAPHS**











Laboratory Sample No.

: WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9 : WC0878519 Lab Number : 02624289

To discuss this sample report, contact Customer Service at 1-800-268-2131.

Received **Tested** Unique Number : 5749408 Diagnosed

: 25 Mar 2024 : 26 Mar 2024

CCGS Amundsen, 101 Boul. Champlain : 26 Mar 2024 - Kevin Marson Test Package : MAR 5 ( Additional Tests: ICP, KF, KV40, Spat, Visual )

Test denoted (\*) outside scope of accreditation, (m) method modified, (e) tested at external lab.

CA G1K 7Y7 Contact: Chief Engineer amundsense@ccgs-ngcc.gc.ca T: (418)953-8233

**Canadian Coast Guard** 

Validity of results and interpretation are based on the sample and information as supplied. Report Id: AMUNDSEN [WCAMIS] 02624289 (Generated: 05/15/2024 19:44:11) Rev: 1

Contact/Location: Chief Engineer - AMUNDSEN

F: x:

Quebec, QC