OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL

Machine Id
NOVA BUS 1631
Component
Natural Gas Engine
Fluid
VALVOLINE PREMIUM BLUE 9200 15W40 (--- GAL)

DIAGNOSIS

Recommendation
We recommend an early resample to monitor this condition.

Wear
An increase in the copper level is noted. All other component wear rates are normal.

Contamination
There is no indication of any contamination in the oil.

Fluid Condition
The condition of the oil is acceptable for the time in service.

SAMPLE INFORMATION		method	limit/base	current	history1	history2
Sample Number		Client Info		**WC0877941**	WC0878172	WC0830134
Sample Date		Client Info		**21 Mar 2024**	19 Dec 2023	23 Sep 2023
Machine Age	kms	Client Info		**488969**	469029	0
Oil Age	kms	Client Info		**0**	0	0
Oil Changed		Client Info		**N/A**	N/A	N/A
Sample Status				**NORMAL**	NORMAL	NORMAL

CONTAMINATION		method	limit/base	current	history1	history2
Water		WC Method	>0.1	**NEG**	NEG	NEG

WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185(m)	>50	**11**	9	14
Chromium	ppm	ASTM D5185(m)	>4	**<1**	<1	<1
Nickel	ppm	ASTM D5185(m)	>2	**<1**	<1	<1
Titanium	ppm	ASTM D5185(m)		**0**	0	0
Silver	ppm	ASTM D5185(m)	>3	**0**	0	0
Aluminum	ppm	ASTM D5185(m)	>9	**2**	2	2
Lead	ppm	ASTM D5185(m)	>30	**4**	1	2
Copper	ppm	ASTM D5185(m)	>35	**23**	3	11
Tin	ppm	ASTM D5185(m)	>4	**0**	0	0
Antimony	ppm	ASTM D5185(m)		**0**	0	0
Vanadium	ppm	ASTM D5185(m)		**0**	0	0
Beryllium	ppm	ASTM D5185(m)		**0**	0	0
Cadmium	ppm	ASTM D5185(m)		**0**	0	0

ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185(m)		**6**	7	6
Barium	ppm	ASTM D5185(m)		**0**	0	<1
Molybdenum	ppm	ASTM D5185(m)		**54**	51	56
Manganese	ppm	ASTM D5185(m)		**0**	0	0
Magnesium	ppm	ASTM D5185(m)		**827**	804	859
Calcium	ppm	ASTM D5185(m)		**1235**	1229	1309
Phosphorus	ppm	ASTM D5185(m)		**664**	643	685
Zinc	ppm	ASTM D5185(m)		**895**	860	925
Sulfur	ppm	ASTM D5185(m)		**1812**	1995	1906
Lithium	ppm	ASTM D5185(m)		**<1**	<1	<1

CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185(m)	>+100	**5**	5	6
Sodium	ppm	ASTM D5185(m)		**4**	4	3
Potassium	ppm	ASTM D5185(m)	>20	**<1**	<1	0

INFRA-RED		method	limit/base	current	history1	history2
Soot %	%	ASTM D7844*		**0**	0	0
Nitration	Abs/cm	ASTM D7624*	>20	**13.2**	12.5	12.6
Sulfation	Abs/.1mm	ASTM D7415*	>30	**25.7**	24.6	24.0

FLUID DEGRADATION		method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	ASTM D7414*	>25	**24.1**	22.6	21.4

OIL ANALYSIS REPORT

Non-ferrous Metals



Non-ferrous Metals



VISUAL		method	limit/base	current	history1	history2
Emulsified Water	scalar	Visual*	>0.1	**NEG**	NEG	NEG
Free Water	scalar	Visual*		**NEG**	NEG	NEG

FLUID PROPERTIES		method	limit/base	current	history1	history2
Visc @ 100°C	cSt	ASTM D7279(m)	14.8	**14.6**	14.8	14.6

GRAPHS

Iron (ppm)



Lead (ppm)



Aluminum (ppm)



Chromium (ppm)



Copper (ppm)



Silicon (ppm)



Viscosity @ 100°C



Additives



ISO 17025:2017 Accredited Laboratory

Laboratory : WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9
Sample No. : WC0877941
Lab Number : 02624671
Unique Number : 5749790
Test Package : MOB 1

Received : 26 Mar 2024
Tested : 26 Mar 2024
Diagnosed : 26 Mar 2024 - Kevin Marson

To discuss this sample report, contact Customer Service at 1-800-268-2131.
Test denoted (*) outside scope of accreditation, (m) method modified, (e) tested at external lab.
Validity of results and interpretation are based on the sample and information as supplied.

CITY OF HAMILTON
2200 UPPER JAMES,, MOUNTAIN TRANSIT STOREROOM
MOUNT HOPE, ON
CA L0R 1W0
Contact: Jeff Parr
jeff.parr@hamilton.ca
T: (905)546-2424
F: (905)679-4502