OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL

Machine Id
DIESEL AIR COMP
Component
Air Compressor
Fluid
{not provided} (--- GAL)

DIAGNOSIS

Recommendation
Resample at the next service interval to monitor. Please specify the brand, type, and viscosity of the oil on your next sample.

Wear
All component wear rates are normal.

Contamination
There is no indication of any contamination in the oil.

Fluid Condition
The condition of the oil is acceptable for the time in service.

SAMPLE INFORMATION		method	limit/base	current	history1	history2
Sample Number		Client Info		**PP**	---	---
Sample Date		Client Info		**31 Mar 2024**	---	---
Machine Age	hrs	Client Info		**0**	---	---
Oil Age	hrs	Client Info		**0**	---	---
Oil Changed		Client Info		**N/A**	---	---
Sample Status				**NORMAL**	---	---

WEAR METALS		method	limit/base	current	history1	history2
PQ		ASTM D8184*		**0**	---	---
Iron	ppm	ASTM D5185(m)	>50	**5**	---	---
Chromium	ppm	ASTM D5185(m)	>4	**0**	---	---
Nickel	ppm	ASTM D5185(m)	>4	**<1**	---	---
Titanium	ppm	ASTM D5185(m)		**0**	---	---
Silver	ppm	ASTM D5185(m)		**0**	---	---
Aluminum	ppm	ASTM D5185(m)	>10	**4**	---	---
Lead	ppm	ASTM D5185(m)	>20	**0**	---	---
Copper	ppm	ASTM D5185(m)	>40	**<1**	---	---
Tin	ppm	ASTM D5185(m)	>5	**0**	---	---
Antimony	ppm	ASTM D5185(m)		**0**	---	---
Vanadium	ppm	ASTM D5185(m)		**0**	---	---
Beryllium	ppm	ASTM D5185(m)		**0**	---	---
Cadmium	ppm	ASTM D5185(m)		**0**	---	---

ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185(m)		**<1**	---	---
Barium	ppm	ASTM D5185(m)		**<1**	---	---
Molybdenum	ppm	ASTM D5185(m)		**0**	---	---
Manganese	ppm	ASTM D5185(m)		**0**	---	---
Magnesium	ppm	ASTM D5185(m)		**<1**	---	---
Calcium	ppm	ASTM D5185(m)		**<1**	---	---
Phosphorus	ppm	ASTM D5185(m)		**170**	---	---
Zinc	ppm	ASTM D5185(m)		**4**	---	---
Sulfur	ppm	ASTM D5185(m)		**156**	---	---
Lithium	ppm	ASTM D5185(m)		**<1**	---	---

CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185(m)	>25	**0**	---	---
Sodium	ppm	ASTM D5185(m)		**5**	---	---
Potassium	ppm	ASTM D5185(m)	>20	**2**	---	---
Water	%	ASTM D6304*	>0.6	**0.001**	---	---
ppm Water	ppm	ASTM D6304*	>6000	**13**	---	---

FLUID DEGRADATION		method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D974*		**0.29**	---	---

OIL ANALYSIS REPORT







VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	Visual*	NONE	**NONE**	---	---
Yellow Metal	scalar	Visual*	NONE	**NONE**	---	---
Precipitate	scalar	Visual*	NONE	**NONE**	---	---
Silt	scalar	Visual*	NONE	**NONE**	---	---
Debris	scalar	Visual*	NONE	**NONE**	---	---
Sand/Dirt	scalar	Visual*	NONE	**NONE**	---	---
Appearance	scalar	Visual*	NORML	**NORML**	---	---
Odor	scalar	Visual*	NORML	**NORML**	---	---
Emulsified Water	scalar	Visual*	>0.6	**NEG**	---	---
Free Water	scalar	Visual*		**NEG**	---	---

FLUID PROPERTIES		method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D7279(m)		**48.7**	---	---

SAMPLE IMAGES	method	limit/base	current	history1	history2
Color				*no image*	*no image*
Bottom				*no image*	*no image*

GRAPHS









ISO 17025:2017 Accredited Laboratory

Laboratory : WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9
Sample No. : PP
Lab Number : 02625715
Unique Number : 5750834
Test Package : IND 2 (Additional Tests: KF, TAN Man)

Received : 01 Apr 2024
Tested : 02 Apr 2024
Diagnosed : 02 Apr 2024 - Kevin Marson

To discuss this sample report, contact Customer Service at 1-800-268-2131.
Test denoted (*) outside scope of accreditation, (m) method modified, (e) tested at external lab.
Validity of results and interpretation are based on the sample and information as supplied.

HIBERNIA MGMT & DEVELOPMENT CO. LTD
SUITE 1000,, 100 NEW GOWER STREET
ST.JOHNS, NL
CA A1C 6K3
Contact: Sam Nash
samantha.m.nash@exxonmobil.com
T:
F: (709)722-3766