

Area Chem-Ecol

OIL ANALYSIS REPORT

SAMPLE INFORMATION method

Sample Rating Trend







A2404008 Component Unknown Component Fluid CHEM-ECOL AEROGUN 35 (--- GAL)

DIAGNOSIS


Recommendation

We certify that this oil is clean, that the additives are at acceptable levels, and that it is suitable for use.


SAMPLE INFORM		method	limit/base	current	nistory i	nistory2
Batch #		Client Info		3051-A		
Department		Client Info		Production		
Sample From		Client Info		Machine		
Production Stage		Client Info		Final		
Sent to WC		Client Info		04/02/2024		
Sample Number		Client Info		E30001785		
Sample Date		Client Info		02 Apr 2024		
Machine Age	hrs	Client Info		0		
Oil Age	hrs	Client Info		0		
Oil Changed		Client Info		N/A		
Sample Status				NORMAL		
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185(m)		0		
Chromium	ppm	ASTM D5185(m)		0		
Nickel	ppm	ASTM D5185(m)		0		
Titanium	ppm	ASTM D5185(m)		<1		
Silver	ppm	ASTM D5185(m)		0		
Aluminum	ppm	ASTM D5185(m)		0		
Lead	ppm	ASTM D5185(m)		0		
Copper	ppm	ASTM D5185(m)		0		
Tin	ppm	ASTM D5185(m)		0		
Antimony	ppm	ASTM D5185(m)		0		
Vanadium	ppm	ASTM D5185(m)		0		
Beryllium	ppm	ASTM D5185(m)		0		
Cadmium	ppm	ASTM D5185(m)		0		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185(m)		0		
Barium	ppm	ASTM D5185(m)		0		
Molybdenum	ppm	ASTM D5185(m)		0		
Manganese	ppm	ASTM D5185(m)		0		
Magnesium	ppm	ASTM D5185(m)		0		
Calcium	ppm	ASTM D5185(m)		<1		
Phosphorus	ppm	ASTM D5185(m)		3		
Zinc	ppm	ASTM D5185(m)		2		
Sulfur	ppm	ASTM D5185(m)		20129		
Lithium	ppm	ASTM D5185(m)		<1		
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185(m)		0		
Sodium	ppm	ASTM D5185(m)		0		
Potassium	ppm	ASTM D5185(m)	>20	<1		
Water	%	ASTM D6304*		0.001		
ppm Water	ppm	ASTM D6304*		6		




OIL ANALYSIS REPORT










6k		4			
<u></u> == 5k •	ADHOIMA	4µm 6µm	 	 	
1 2 2 2 2 2 2 2 2 2 2 2 2 2 2 2 2 2 2 2		14µm			
in clea					
jo 3K					
Ja 2k -					
² 1k∙					
Ok			 	 	
	Apr2/24				Apr2/24
	Ap				Api

FLUID CLEANLIN	IESS	method	limit/base	current	history1	history2
Particles >4µm		ASTM D7647	>5000	364		
Particles >6µm		ASTM D7647	>640	98		
Particles >14µm		ASTM D7647	>160	11		
Particles >21µm		ASTM D7647	>40	4		
Particles >38µm		ASTM D7647	>10	1		
Particles >71µm		ASTM D7647	>3	1		
Oil Cleanliness		ISO 4406 (c)	>19/16/14	16/14/11		
FLUID DEGRADA	TION	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D974*		0.06		
VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	Visual*	NONE	NONE		
Yellow Metal	scalar	Visual*	NONE	NONE		
Precipitate	scalar	Visual*	NONE	NONE		
Silt	scalar	Visual*	NONE	NONE		
Debris	scalar	Visual*	NONE	NONE		
Sand/Dirt	scalar	Visual*	NONE	NONE		
Appearance	scalar	Visual*	NORML	NORML		
Odor	scalar	Visual*	NORML	NORML		
Emulsified Water	scalar	Visual*		NEG		
Free Water	scalar	Visual*		NEG		
FLUID PROPERT	IES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D7279(m)	35	33.8		
Visc @ 100°C	cSt	ASTM D7279(m)		5.8		
Viscosity Index (VI)	Scale	ASTM D2270*		113		
SAMPLE IMAGES		method	limit/base	current	history1	history2
Color					no image	no image





Report Id: CHECOB [WCAMIS] 02626673 (Generated: 04/05/2024 12:25:38) Rev: 1

Contact/Location: Tatiana Sorkina - CHECOB Page 2 of 2

no image

no image