


OIL ANALYSIS REPORT

Sample Rating Trend



Machine Id

KM3301 MOTOR ELECT AC

Hydraulic System

AW HYDRAULIC OIL ISO 32 (--- GAL)

Recommendation

Little or no information is provided as to the component and lubricant being tested. Recommendations are therefore generic in nature and may not apply to the current application. Please forward information as to equipment type, reservoir capacity, lubricant type and any pertinent information to allow for a more accurate assessment. We recommend you service the filters on this component. Resample at the next service interval to monitor. NOTE: Please provide information regarding reservoir capacity, filter type and micron rating with next sample. Please specify the brand, type, and viscosity of the oil on your next sample.

Wear

All component wear rates are normal.

Contamination

There is a light amount of silt (particulates < 14 microns in size) present in the oil.

Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

| М ₉ /2016 Јаг/2017 А ₉ /2024 | | | | | | |
|--|--------|---------------|------------|-------------|-------------|-----------------|
| SAMPLE INFORM | MATION | method | limit/base | current | history1 | history2 |
| Sample Number | | Client Info | | PP | PP2391057 | WC |
| Sample Date | | Client Info | | 04 Apr 2024 | 25 Jan 2017 | 02 May 2016 |
| Machine Age | hrs | Client Info | | 0 | 0 | 0 |
| Oil Age | hrs | Client Info | | 0 | 0 | 0 |
| Oil Changed | | Client Info | | N/A | N/A | N/A |
| Sample Status | | | | ATTENTION | NORMAL | ABNORMAL |
| CONTAMINATION | ٧ | method | limit/base | current | history1 | history2 |
| Water | | WC Method | >0.05 | NEG | NEG | NEG |
| WEAR METALS | | method | limit/base | current | history1 | history2 |
| Iron | ppm | ASTM D5185(m) | >20 | 2 | 0 | 0 |
| Chromium | ppm | ASTM D5185(m) | >10 | 0 | 0 | 0 |
| Nickel | ppm | ASTM D5185(m) | >10 | 0 | 0 | 0 |
| Titanium | ppm | ASTM D5185(m) | | 0 | 0 | 0 |
| Silver | ppm | ASTM D5185(m) | | 0 | 0 | 0 |
| Aluminum | ppm | ASTM D5185(m) | >10 | 0 | 0 | 0 |
| Lead | ppm | ASTM D5185(m) | >20 | 0 | <1 | <1 |
| Copper | ppm | ASTM D5185(m) | >20 | <1 | <1 | <1 |
| Tin | ppm | ASTM D5185(m) | >10 | 0 | 1 | 1 |
| Antimony | ppm | ASTM D5185(m) | | 0 | 0 | 0 |
| Vanadium | ppm | ASTM D5185(m) | | 0 | 0 | 0 |
| Beryllium | ppm | ASTM D5185(m) | | 0 | 0 | 0 |
| Cadmium | ppm | ASTM D5185(m) | | 0 | <1 | <1 |
| ADDITIVES | | method | limit/base | current | history1 | history2 |
| Boron | ppm | ASTM D5185(m) | 5 | <1 | <1 | <1 |
| Barium | ppm | ASTM D5185(m) | 5 | 0 | 0 | <1 |
| Molybdenum | ppm | ASTM D5185(m) | 5 | 0 | 0 | 0 |
| Manganese | ppm | ASTM D5185(m) | | 0 | 0 | 0 |
| Magnesium | ppm | ASTM D5185(m) | 25 | <1 | 0 | 0 |
| Calcium | ppm | ASTM D5185(m) | 200 | 48 | 56 | 56 |
| Phosphorus | ppm | ASTM D5185(m) | 300 | 329 | 329 | 340 |
| Zinc | ppm | ASTM D5185(m) | 370 | 406 | 436 | 435 |
| Sulfur | ppm | ASTM D5185(m) | 2500 | 1045 | 3632 | 3739 |
| Lithium | ppm | ASTM D5185(m) | | <1 | <1 | <1 |
| CONTAMINANTS | | method | limit/base | current | history1 | history2 |
| Silicon | ppm | ASTM D5185(m) | >15 | 0 | 1 | 2 |
| Sodium | ppm | ASTM D5185(m) | | <1 | <1 | <1 |
| Potassium | ppm | ASTM D5185(m) | >20 | <1 | 0 | 0 |
| FLUID CLEANLIN | ESS | method | limit/base | current | history1 | history2 |
| Particles >4µm | | ASTM D7647 | >5000 | 8378 | 943 | <u> </u> |
| Particles >6µm | | ASTM D7647 | >1300 | 1680 | 180 | <u></u> 5304 |
| Particles >14µm | | ASTM D7647 | >160 | 85 | 14 | 276 |
| Particles >21µm | | ASTM D7647 | >40 | 19 | 4 | 76 |
| Particles >38µm | | ASTM D7647 | >10 | 3 | 0 | 10 |
| Particles >71µm | | ASTM D7647 | >3 | 1 | 0 | 0 |
| Oil Cleanliness | | ISO 4406 (c) | >19/17/14 | 20/18/14 | 17/15/11 | <u>22/20/15</u> |

Contact/Location: Sam Nash - HIBSTJ



OIL ANALYSIS REPORT





CALA ISO 17025:2017 Accredited Laboratory

Laboratory Sample No.

: PP Lab Number : 02626998 Unique Number : 5760130 Test Package : MAR 2

To discuss this sample report, contact Customer Service at 1-800-268-2131.

Test denoted (*) outside scope of accreditation, (m) method modified, (e) tested at external lab.

: WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9 Received : 05 Apr 2024 **Tested** Diagnosed

: 08 Apr 2024 : 08 Apr 2024 - Wes Davis

SUITE 1000,, 100 NEW GOWER STREET

ST.JOHNS, NL **CA A1C 6K3** Contact: Sam Nash

samantha.m.nash@exxonmobil.com T:

F: (709)722-3766

Validity of results and interpretation are based on the sample and information as supplied.

Contact/Location: Sam Nash - HIBSTJ

HIBERNIA MGMT & DEVELOPMENT CO. LTD