

OIL ANALYSIS REPORT

Area
Chem-Ecol A2404026

Unknown Component

CHEM-ECOL GREENLUBE 46 (--- GAL)

Sample Rating Trend



Recommendation

We certify that this oil is clean, that the additives are at acceptable levels, and that it is suitable for use.

| | | | | | | . |
|------------------|-----------|-------------------|---------------|-------------|----------|----------|
| | | | | | | |
| SAMPLE INFORM | MATION | method | limit/base | ourrent | hiotonyl | hiotom/2 |
| | VIATION | | IIIIIIIIIIIII | current | history1 | history2 |
| Batch # | | Client Info | | 3057-A | | |
| Department | | Client Info | | Production | | |
| Sample From | | Client Info | | Machine | | |
| Production Stage | | Client Info | | Final | | |
| Sent to WC | | Client Info | | 04/05/2024 | | |
| Sample Number | | Client Info | | E30001801 | | |
| Sample Date | | Client Info | | 05 Apr 2024 | | |
| Machine Age | hrs | Client Info | | 0 | | |
| Oil Age | hrs | Client Info | | 0 | | |
| Oil Changed | | Client Info | | N/A | | |
| Sample Status | | | | NORMAL | | |
| | | | | | | |
| WEAR METALS | | method | limit/base | current | history1 | history2 |
| Iron | ppm | ASTM D5185(m) | | 6 | | |
| Chromium | ppm | ASTM D5185(m) | | 0 | | |
| Nickel | ppm | ASTM D5185(m) | | 0 | | |
| Titanium | ppm | ASTM D5185(m) | | 0 | | |
| Silver | ppm | ASTM D5185(m) | | 0 | | |
| Aluminum | ppm | ASTM D5185(m) | | 2 | | |
| Lead | ppm | ASTM D5185(m) | | 0 | | |
| Copper | ppm | ASTM D5185(m) | | 7 | | |
| Tin | ppm | ASTM D5185(m) | | 0 | | |
| Antimony | ppm | ASTM D5185(m) | | 0 | | |
| Vanadium | ppm | ASTM D5185(m) | | 0 | | |
| Beryllium | ppm | ASTM D5185(m) | | 0 | | |
| Cadmium | ppm | ASTM D5185(m) | | 0 | | |
| | рріп | A01101 D0100(III) | | | | |
| ADDITIVES | | method | limit/base | current | history1 | history2 |
| Boron | ppm | ASTM D5185(m) | | <1 | | |
| Barium | ppm | ASTM D5185(m) | | 4 | | |
| Molybdenum | ppm | ASTM D5185(m) | | 0 | | |
| Manganese | ppm | ASTM D5185(m) | | <1 | | |
| Magnesium | ppm | ASTM D5185(m) | | 169 | | |
| Calcium | ppm | ASTM D5185(m) | | 154 | | |
| Phosphorus | ppm | ASTM D5185(m) | | 826 | | |
| Zinc | ppm | ASTM D5185(m) | | 963 | | |
| Sulfur | ppm | ASTM D5185(m) | | 2067 | | |
| Lithium | ppm | ASTM D5185(m) | | <1 | | |
| CONTAMINANTS | | method | limit/base | current | history1 | history2 |
| Silicon | ppm | ASTM D5185(m) | | 2 | | |
| Sodium | ppm | ASTM D5185(m) | | 4 | | |
| Potassium | | ASTM D5185(m) | >20 | <1 | | |
| Water | ppm o/ | . , | >20 | | | |
| vvaler | % | ASTM D6304* | | 0.002 | | |

ppm Water


ASTM D6304*

ppm

20



OIL ANALYSIS REPORT



| FLUID CLEANLIN | ESS | method | limit/base | current | history1 | history2 |
|----------------------|----------|---------------|------------|-----------|----------|----------|
| Particles >4µm | | ASTM D7647 | >5000 | 228 | | |
| Particles >6µm | | ASTM D7647 | >640 | 91 | | |
| Particles >14µm | | ASTM D7647 | >160 | 14 | | |
| Particles >21µm | | ASTM D7647 | >40 | 4 | | |
| Particles >38µm | | ASTM D7647 | >10 | 1 | | |
| Particles >71µm | | ASTM D7647 | >3 | 1 | | |
| Oil Cleanliness | | ISO 4406 (c) | >19/16/14 | 15/14/11 | | |
| FLUID DEGRADATION | | method | limit/base | current | history1 | history2 |
| Acid Number (AN) | mg KOH/g | ASTM D974* | | 1.32 | | |
| VISUAL | | method | limit/base | current | history1 | history2 |
| White Metal | scalar | Visual* | NONE | NONE | | |
| Yellow Metal | scalar | Visual* | NONE | NONE | | |
| Precipitate | scalar | Visual* | NONE | NONE | | |
| Silt | scalar | Visual* | NONE | NONE | | |
| Debris | scalar | Visual* | NONE | NONE | | |
| Sand/Dirt | scalar | Visual* | NONE | VLITE | | |
| Appearance | scalar | Visual* | NORML | NORML | | |
| Odor | scalar | Visual* | NORML | NORML | | |
| Emulsified Water | scalar | Visual* | | NEG | | |
| Free Water | scalar | Visual* | | NEG | | |
| FLUID PROPERT | IES | method | limit/base | current | history1 | history2 |
| Visc @ 40°C | cSt | ASTM D7279(m) | 46 | 48.6 | | |
| Visc @ 100°C | cSt | ASTM D7279(m) | | 7.5 | | |
| Viscosity Index (VI) | Scale | ASTM D2270* | | 117 | | |
| SAMPLE IMAGES | 3 | method | limit/base | current | history1 | history2 |
| | | | | B81000E3 | | |
| Color | | | | | no image | no image |
| | | | | | | |
| | | | | 9 | | |
| Bottom | | | | O+08 xent | no image | no image |
| | | | | | | |
| | | | | | | |
| | | | | | | |
| | | | | | | |
| | | | | | | |





Laboratory

Sample No.

: E30001801 Lab Number : 02627696 Unique Number : 5760828

: WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9 Received : 09 Apr 2024

Tested : 10 Apr 2024 Diagnosed : 11 Apr 2024 - Tatiana Sorkina

Test Package : IND 2 (Additional Tests: KF, KV100, PrtCount, TAN Man, VI) To discuss this sample report, contact Customer Service at 1-905-372-2251.

Test denoted (*) outside scope of accreditation, (m) method modified, (e) tested at external lab. Validity of results and interpretation are based on the sample and information as supplied.

Environmental 360 Solutions Ltd.

640 Victoria Street Cobourg, ON CA K9A 5H5

Contact: Tatiana Sorkina tsorkina@e360s.ca T: (800)263-3939

F: (905)373-4950