

OIL ANALYSIS REPORT









Machine Id **VOLVO A30G HDTR0824**

Component Rear Right Planetary

Fluid
GEAR OIL SAE 80W90

Recommendation

Resample at the next service interval to monitor. The fluid was not specified, however, a fluid match indicates that this fluid is (GENERIC) GEAR OIL SAE 80W90. Please confirm.

All component wear rates are normal.

Contamination

There is no indication of any contamination in the


Fluid Condition

The condition of the oil is acceptable for the time in service.

(CAL)						
(GAL)				Apr2024		
SAMPLE INFOR	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		WC0902330		
Sample Date		Client Info		05 Apr 2024		
Machine Age	hrs	Client Info		26244		
Oil Age	hrs	Client Info		0		
Oil Changed		Client Info		Not Changd		
Sample Status				NORMAL		
CONTAMINATIO	N	method	limit/base	current	history1	history2
Vater		WC Method	>0.2	NEG		
WEAR METALS		method	limit/base	current	history1	history2
ron	ppm	ASTM D5185(m)	>500	92		
Chromium	ppm	ASTM D5185(m)	>10	<1		
Nickel	ppm	ASTM D5185(m)	>10	<1		
Titanium	ppm	ASTM D5185(m)		0		
Silver	ppm	ASTM D5185(m)		0		
Aluminum	ppm	ASTM D5185(m)	>25	<1		
_ead	ppm	ASTM D5185(m)	>25	0		
Copper	ppm	ASTM D5185(m)	>75	2		
Γin	ppm	ASTM D5185(m)	>10	0		
Antimony	ppm	ASTM D5185(m)	>5	0		
/anadium	ppm	ASTM D5185(m)		0		
Beryllium	ppm	ASTM D5185(m)		0		
Cadmium	ppm	ASTM D5185(m)		0		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185(m)	400	25		
Barium	ppm	ASTM D5185(m)	200	0		
Nolybdenum	ppm	ASTM D5185(m)	12	0		
Manganese	ppm	ASTM D5185(m)		1		
/lagnesium	ppm	ASTM D5185(m)	12	5		
Calcium	ppm	ASTM D5185(m)	150	91		
Phosphorus	ppm	ASTM D5185(m)	1650	450		
Zinc	ppm	ASTM D5185(m)	125	43		
Sulfur	ppm	ASTM D5185(m)	22500	16284		
_ithium	ppm	ASTM D5185(m)		<1		
CONTAMINANTS	S	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185(m)	>75	5		
Sodium	ppm	ASTM D5185(m)	>170	<1		
Potassium	ppm	ASTM D5185(m)	>20	<1		



OIL ANALYSIS REPORT



VISUAL		method	limit/base	current	history1	history2	
White Metal	scalar	Visual*	NONE	NONE			
Yellow Metal	scalar	Visual*	NONE	NONE			
Precipitate	scalar	Visual*	NONE	NONE			
Silt	scalar	Visual*	NONE	NONE			
Debris	scalar	Visual*	NONE	NONE			
Sand/Dirt	scalar	Visual*	NONE	NONE			
Appearance	scalar	Visual*	NORML	NORML			
Odor	scalar	Visual*	NORML	NORML			
Emulsified Water	scalar	Visual*	>0.2	NEG			
Free Water	scalar	Visual*		NEG			
FLUID PROPERT	ΓIES	method	limit/base	current	history1	history2	
/isc @ 40°C	cSt	ASTM D7279(m)	143	139			
SAMPLE IMAGE	S	method	limit/base	current	history1	history2	
Color					no image	no image	
3ottom					no image	no image	
GRAPHS							
Iron (ppm)			Lead (ppm)				
Severe		•••••	E 100	Severe			
Abnormal			ā 50	Abnormal			
45			4			- 4-	
Apr5/24			Apr5/24	Apr5/24		Apr5/24	
Aluminum (ppm) Chromium (ppm)							
Severe				Develo			
Abnormal			E 20	Abnormal			
0 4:						5.	
Apr5/24			Apr5/24 -	Apr5/24		Apr5/24	
Copper (ppm)				Silicon (ppm)			
00 Sauera 300 L							
Abnomal Severe Care Abnomal							
, L				L			
Apr5/24			Apr5/24 .	Apr5/24		Apr5/24	
Αμ			Ap	Ap		Αp	



CALA ISO 17025:2017 Accredited Laboratory

Laboratory Sample No.

Test Package : MOB 1

: WC0902330

100

Lab Number : 02628562 Unique Number : 5761694

Abnormal

Viscosity @ 40°C

: WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9 Received : 12 Apr 2024

Tested : 12 Apr 2024 Diagnosed : 12 Apr 2024 - Wes Davis

Additives

Agnico Eagle Canada 1350 Government Rd. W, MACASSA COMPLEX Kirkland Lake, ON

CA P2N 3J1 Contact: Mitch Lamontagne

AEM_KL_macassaoilsampleresults@agnicoeagle.com T: (705)567-5208

To discuss this sample report, contact Customer Service at 1-800-268-2131. Test denoted (*) outside scope of accreditation, (m) method modified, (e) tested at external lab.

Validity of results and interpretation are based on the sample and information as supplied. F: (705)567-5221 Contact/Location: Mitch Lamontagne - KIR370KIR