




OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL



Machine Id

A
 Component
Transmission (Manual)
 Fluid
ACURA DW1 (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the fluid.

Fluid Condition

The condition of the fluid is acceptable for the time in service.

SAMPLE INFORMATION

	method	limit/base	current	history1	history2
Sample Number	Client Info		WC0890702	---	---
Sample Date	Client Info		20 Dec 2023	---	---
Machine Age	hrs	Client Info	91019	---	---
Oil Age	hrs	Client Info	26756	---	---
Oil Changed		Client Info	Changed	---	---
Sample Status			NORMAL	---	---

CONTAMINATION

	method	limit/base	current	history1	history2
Water	WC Method	>0.1	NEG	---	---

WEAR METALS

	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185(m) >200	120	---	---
Chromium	ppm	ASTM D5185(m) >5	<1	---	---
Nickel	ppm	ASTM D5185(m) >5	0	---	---
Titanium	ppm	ASTM D5185(m)	0	---	---
Silver	ppm	ASTM D5185(m) >7	0	---	---
Aluminum	ppm	ASTM D5185(m) >25	16	---	---
Lead	ppm	ASTM D5185(m) >45	0	---	---
Copper	ppm	ASTM D5185(m) >225	18	---	---
Tin	ppm	ASTM D5185(m) >10	0	---	---
Antimony	ppm	ASTM D5185(m)	0	---	---
Vanadium	ppm	ASTM D5185(m)	0	---	---
Beryllium	ppm	ASTM D5185(m)	0	---	---
Cadmium	ppm	ASTM D5185(m)	0	---	---

ADDITIVES


	method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185(m)	289	---	---
Barium	ppm	ASTM D5185(m)	4	---	---
Molybdenum	ppm	ASTM D5185(m)	0	---	---
Manganese	ppm	ASTM D5185(m)	2	---	---
Magnesium	ppm	ASTM D5185(m)	243	---	---
Calcium	ppm	ASTM D5185(m)	429	---	---
Phosphorus	ppm	ASTM D5185(m)	3	---	---
Zinc	ppm	ASTM D5185(m)	355	---	---
Sulfur	ppm	ASTM D5185(m)	843	---	---
Lithium	ppm	ASTM D5185(m)	<1	---	---

CONTAMINANTS

	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185(m) >125	18	---	---
Sodium	ppm	ASTM D5185(m)	2	---	---
Potassium	ppm	ASTM D5185(m) >20	1	---	---



OIL ANALYSIS REPORT




VISUAL	method	limit/base	current	history1	history2	
White Metal	scalar	Visual*	NONE	NONE	---	---
Yellow Metal	scalar	Visual*	NONE	NONE	---	---
Precipitate	scalar	Visual*	NONE	NONE	---	---
Silt	scalar	Visual*	NONE	NONE	---	---
Debris	scalar	Visual*	NONE	NONE	---	---
Sand/Dirt	scalar	Visual*	NONE	NONE	---	---
Appearance	scalar	Visual*	NORML	NORML	---	---
Odor	scalar	Visual*	NORML	NORML	---	---
Emulsified Water	scalar	Visual*	>0.1	NEG	---	---
Free Water	scalar	Visual*		NEG	---	---

FLUID PROPERTIES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D7279(m)	20.0	---	---

SAMPLE IMAGES	method	limit/base	current	history1	history2
---------------	--------	------------	---------	----------	----------

Color				no image	no image
Bottom				no image	no image

GRAPHS



Laboratory : WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9
Sample No. : WC0890702 **Received** : 15 Apr 2024
Lab Number : 02628907 **Tested** : 16 Apr 2024
Unique Number : 5762039 **Diagnosed** : 16 Apr 2024 - Kevin Marson
Test Package : MOB 1

Ken Purton
 488 Scotchmere Court
 Waterloo, ON
 CA N2K 3E6
 Contact: Ken Purton
 purtonk@gmail.com

To discuss this sample report, contact Customer Service at 1-800-268-2131.
 Test denoted (*) outside scope of accreditation, (m) method modified, (e) tested at external lab.
 Validity of results and interpretation are based on the sample and information as supplied.