

OIL ANALYSIS REPORT

Infasco - I02400 A2404048

Unknown Component

{not provided} (--- GAL)

Sample Rating Trend NORMAL

Recommendation

We certify that this oil is clean, that the additives are at acceptable levels, and that it is suitable for use.


Wear

Copper ppm levels are noted.

| | | | , | Apr2024 | | |
|-----------------------------|-----------|---------------|------------|-----------------------|----------|----------|
| SAMPLE INFORMATION | | method | limit/base | current | history1 | history2 |
| Batch # | ni/(TTOTY | Client Info | IIIIIIIIII | 2024 03 0331 | | mstoryz |
| | | Client Info | | | | |
| Department | | Client Info | | Production Machine | | |
| Sample From | | | | | | |
| Production Stage Sent to WC | | Client Info | | Final | | |
| | | Client Info | | 04/11/2024 | | |
| Sample Number | | Client Info | | E30001825 | | |
| Sample Date | bro | Client Info | | 11 Apr 2024 | | |
| Machine Age | hrs | Client Info | | 0 | | |
| Oil Age | hrs | Client Info | | 0 N/A | | |
| Oil Changed | | Client Info | | | | |
| Sample Status | | | | NORMAL | | |
| WEAR METALS | | method | limit/base | current | history1 | history2 |
| Iron | ppm | ASTM D5185(m) | | 15 | | |
| Chromium | ppm | ASTM D5185(m) | | 0 | | |
| Nickel | ppm | ASTM D5185(m) | | 4 | | |
| Titanium | ppm | ASTM D5185(m) | | 0 | | |
| Silver | ppm | ASTM D5185(m) | | 0 | | |
| Aluminum | ppm | ASTM D5185(m) | | <1 | | |
| Lead | ppm | ASTM D5185(m) | | 5 | | |
| Copper | ppm | ASTM D5185(m) | | 188 | | |
| Tin | ppm | ASTM D5185(m) | | 0 | | |
| Antimony | ppm | ASTM D5185(m) | | 0 | | |
| Vanadium | ppm | ASTM D5185(m) | | 0 | | |
| Beryllium | ppm | ASTM D5185(m) | | 0 | | |
| Cadmium | ppm | ASTM D5185(m) | | 0 | | |
| ADDITIVES | | method | limit/base | current | history1 | history2 |
| Boron | ppm | ASTM D5185(m) | | 4 | | |
| Barium | ppm | ASTM D5185(m) | | 0 | | |
| Molybdenum | ppm | ASTM D5185(m) | | 0 | | |
| Manganese | ppm | ASTM D5185(m) | | <1 | | |
| Magnesium | ppm | ASTM D5185(m) | | 38 | | |
| Calcium | ppm | ASTM D5185(m) | | 696 | | |
| Phosphorus | ppm | ASTM D5185(m) | | 415 | | |
| Zinc | ppm | ASTM D5185(m) | | 377 | | |
| Sulfur | ppm | ASTM D5185(m) | | 2907 | | |
| Lithium | ppm | ASTM D5185(m) | | <1 | | |
| CONTAMINANTS | ; | method | limit/base | current | history1 | history2 |
| Silicon | ppm | ASTM D5185(m) | | <1 | | |
| Sodium | ppm | ASTM D5185(m) | | 10 | | |
| Potassium | ppm | ASTM D5185(m) | >20 | 4 | | |
| Water | % | ASTM D6304* | - | 0.003 | | |
| ppm Water | ppm | ASTM D6304* | | 26 | | |



OIL ANALYSIS REPORT



| . 20.5 022, | ESS | method | limit/base | current | history1 | history2 |
|----------------------|----------|---------------|------------|----------|----------|----------|
| Particles >4µm | | ASTM D7647 | >5000 | 240 | | |
| Particles >6µm | | ASTM D7647 | >640 | 88 | | |
| Particles >14µm | | ASTM D7647 | >160 | 7 | | |
| Particles >21µm | | ASTM D7647 | >40 | 4 | | |
| Particles >38µm | | ASTM D7647 | >10 | 2 | | |
| Particles >71µm | | ASTM D7647 | >3 | 2 | | |
| Oil Cleanliness | | ISO 4406 (c) | >19/16/14 | 15/14/10 | | |
| FLUID DEGRADAT | ΓΙΟΝ | method | limit/base | current | history1 | history2 |
| Acid Number (AN) | mg KOH/g | ASTM D974* | | 0.72 | | |
| VISUAL | | method | limit/base | current | history1 | history2 |
| White Metal | scalar | Visual* | NONE | NONE | | |
| Yellow Metal | scalar | Visual* | NONE | NONE | | |
| Precipitate | scalar | Visual* | NONE | NONE | | |
| Silt | scalar | Visual* | NONE | NONE | | |
| Debris | scalar | Visual* | NONE | NONE | | |
| Sand/Dirt | scalar | Visual* | NONE | NONE | | |
| Appearance | scalar | Visual* | NORML | NORML | | |
| Odor | scalar | Visual* | NORML | NORML | | |
| Emulsified Water | scalar | Visual* | | NEG | | |
| Free Water | scalar | Visual* | | NEG | | |
| FLUID PROPERTII | ES | method | limit/base | current | history1 | history2 |
| Visc @ 40°C | cSt | ASTM D7279(m) | | 188 | | |
| Visc @ 100°C | cSt | ASTM D7279(m) | | 18.1 | | |
| Viscosity Index (VI) | Scale | ASTM D2270* | | 105 | | |
| SAMPLE IMAGES | | method | limit/base | current | history1 | history2 |
| Color | | | | | no image | no image |
| | | | | (2) | no image | no image |



CALA ISO 17025:2017 Accredited Laboratory

Laboratory

Sample No. Lab Number : 02629017 Unique Number : 5762149

: E30001825

: WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9 Received : 15 Apr 2024

Tested : 17 Apr 2024 Diagnosed : 17 Apr 2024 - Tatiana Sorkina Test Package : IND 2 (Additional Tests: KF, KV100, PrtCount, TAN Man, VI)

To discuss this sample report, contact Customer Service at 1-905-372-2251. Test denoted (*) outside scope of accreditation, (m) method modified, (e) tested at external lab. Validity of results and interpretation are based on the sample and information as supplied.

Environmental 360 Solutions Ltd.

640 Victoria Street Cobourg, ON CA K9A 5H5

Contact: Tatiana Sorkina tsorkina@e360s.ca T: (800)263-3939

F: (905)373-4950