




OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL



Area

1

Machine Id

1-3-2030

Component

Air Compressor

Fluid

GARDNER DENVER AEON 4000 (200 LTR)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

The water content is negligible. There is no indication of any contamination in the oil.

Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

SAMPLE INFORMATION

	method	limit/base	current	history1	history2
Sample Number	Client Info		WC0925305	WC0901995	WC0869848
Sample Date	Client Info		02 Apr 2024	13 Feb 2024	23 Oct 2023
Machine Age	hrs	Client Info	0	0	0
Oil Age	hrs	Client Info	0	0	0
Oil Changed	Client Info		N/A	N/A	N/A
Sample Status			NORMAL	ABNORMAL	NORMAL

WEAR METALS

	method	limit/base	current	history1	history2
PQ	ASTM D8184*		0	0	0
Iron	ppm	ASTM D5185(m) >50	<1	5	0
Chromium	ppm	ASTM D5185(m) >4	0	0	0
Nickel	ppm	ASTM D5185(m) >4	0	0	<1
Titanium	ppm	ASTM D5185(m)	0	0	0
Silver	ppm	ASTM D5185(m)	0	0	<1
Aluminum	ppm	ASTM D5185(m) >10	0	1	0
Lead	ppm	ASTM D5185(m) >20	0	4	0
Copper	ppm	ASTM D5185(m) >40	2	3	1
Tin	ppm	ASTM D5185(m) >5	0	0	0
Antimony	ppm	ASTM D5185(m)	2	▲ 30	0
Vanadium	ppm	ASTM D5185(m)	0	0	0
Beryllium	ppm	ASTM D5185(m)	0	0	0
Cadmium	ppm	ASTM D5185(m)	0	0	0

ADDITIVES

	method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185(m) 0.2	0	0	<1
Barium	ppm	ASTM D5185(m) 0.0	0	0	<1
Molybdenum	ppm	ASTM D5185(m) 0.0	0	0	0
Manganese	ppm	ASTM D5185(m) 0.0	0	0	0
Magnesium	ppm	ASTM D5185(m) 0.0	0	<1	0
Calcium	ppm	ASTM D5185(m) 0.0	<1	● 10	2
Phosphorus	ppm	ASTM D5185(m) 312	3	1	<1
Zinc	ppm	ASTM D5185(m) 0.0	1	● 16	<1
Sulfur	ppm	ASTM D5185(m) 1629	2504	1985	2152
Lithium	ppm	ASTM D5185(m)	<1	<1	<1

CONTAMINANTS

	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185(m) >25	0	9	1
Sodium	ppm	ASTM D5185(m)	0	3	<1
Potassium	ppm	ASTM D5185(m) >20	<1	12	0
Water	%	ASTM D6304* >0.6	0.002	0.287	0.002
ppm Water	ppm	ASTM D6304* >6000	16	2873	18
Glycol	%	ASTM D7922*	0.0	0.0	0.0

FLUID DEGRADATION

	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D974* 0.03	0.05	0.18	0.10

