

OIL ANALYSIS REPORT

Sample Rating Trend



Area Pumping Machine Id Machine Id Mobile Component Middle Differential Fluid MOBIL 75W90 (18 LTR)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor. Please specify the component make and model with your next sample.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The condition of the oil is acceptable for the time in service.

SAMPLE INFORM	ATION	method	limit/base	current	history1	history2
Sample Number		Client Info		WC0925773		
Sample Date		Client Info		13 Apr 2024		
Machine Age	hrs	Client Info		169430		
Oil Age	hrs	Client Info		0		
Oil Changed		Client Info		Changed		
Sample Status				NORMAL		
CONTAMINATION	l	method	limit/base	current	history1	history2
Water		WC Method	>.2	NEG		
WEAR METALS		method	limit/base	current	history1	history2
PQ		ASTM D8184*		0		
Iron	ppm	ASTM D5185(m)	>500	29		
Chromium	ppm	ASTM D5185(m)	>10	0		
Nickel	ppm	ASTM D5185(m)	>10	0		
Titanium	ppm	ASTM D5185(m)		0		
Silver	ppm	ASTM D5185(m)		0		
Aluminum	ppm	ASTM D5185(m)	>25	0		
Lead	ppm	ASTM D5185(m)	>25	2		
Copper	ppm	ASTM D5185(m)	>100	142		
Tin	ppm	ASTM D5185(m)	>10	1		
Antimony	ppm	ASTM D5185(m)	>5	0		
Vanadium	ppm	ASTM D5185(m)		0		
Beryllium	ppm	ASTM D5185(m)		0		
Cadmium	ppm	ASTM D5185(m)		0		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185(m)		189		
Barium	ppm	ASTM D5185(m)		<1		
Molybdenum	ppm	ASTM D5185(m)		0		
Manganese	ppm	ASTM D5185(m)		1		
Magnesium	ppm	ASTM D5185(m)		<1		
Calcium	ppm	ASTM D5185(m)		2		
Phosphorus	ppm	ASTM D5185(m)		1250		
Zinc	ppm	ASTM D5185(m)		3		
Sulfur	ppm	ASTM D5185(m)		20343		
Lithium	ppm	ASTM D5185(m)		<1		
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185(m)	>75	17		
Sodium	ppm	ASTM D5185(m)		1		
Potassium	ppm	ASTM D5185(m)	>20	<1		



OIL ANALYSIS REPORT



		mounou		04.101.10			
White Metal	scalar	Visual*	NONE	NONE			
Yellow Metal	scalar	Visual*	NONE	NONE			
Precipitate	scalar	Visual*	NONE	NONE			
Silt	scalar	Visual*	NONE	NONE			
Debris	scalar	Visual*	NONE	NONE			
Sand/Dirt	scalar	Visual*	NONE	VLITE			
Appearance	scalar	Visual*	NORML	NORML			
Odor	scalar	Visual*	NORML	NORML			
Emulsified Water	scalar	Visual*	>.2	NEG			
Free Water	scalar	Visual*		NEG			
FLUID PROPERT	IES	method	limit/base	current	history1	history2	
Visc @ 40°C	cSt	ASTM D7279(m)		105			
SAMPLE IMAGES	\$	method	limit/base	current	history1	history2	
Color					no image	no image	
Bottom					no image	no image	
GRAPHS							
iron iron iron iron iron			22	Severe			
0-			16	0			
0 0	******	*********	14 47/21/21/2	0 -			
◄ Non-ferrous Metals	5		₹ 2 10	0 - Abnormal			
copper			6	0			
••••••••••			4	0			
D -							
				U			
3/24			3/24	24 0		24	
Apr1			Apr1	Apr13,		Jur 13,	
Viscosity @ 40°C						4	
Abnormal							
)							
]							
D							
⁰ Abnormal							
24+10 			24				
4pr13/			4pr13/				
4			4				
earCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9 C0925773 Received : 22 Apr 2024 630700 Tested : 23 Apr 2024 63832 Diagnosed : 23 Apr 2024 - Kevin Marson EET (Additional Tests: PO)				L 5H9 vin Marson	GOLIATH ENERGY GROUP 3277 PARSONS RD NW EDMONTON, AB CA T6N 1B4		

 Laboratory
 Test Package
 : FLEET (Additional Tests: PQ)

 To discuss this sample report, contact Customer Service at 1-800-268-2131.

 Test denoted (*) outside scope of accreditation, (m) method modified, (e) tested at external lab.

 Validity of results and interpretation are based on the sample and information as supplied.

Report Id: GOLEDM [WCAMIS] 02630700 (Generated: 04/23/2024 14:17:47) Rev: 1

CALA

ISO 17025:2017 Accredited Laboratory Laboratory

Sample No. Lab Number

Unique Number

Contact/Location: Kurt Bromling - GOLEDM Page 2 of 2

kurt@goliathenergy.com

T: (780)897-6262

F: