




OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL



Area
CONGEBEC MISSISSAUGA [4501252786]
 Machine Id
FRICK COMP #2 (S/N 10241G76682680)
 Component
Screw Compressor
 Fluid
FRICK COMPRESSOR OIL #3 (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

The water content is negligible. There is no indication of any contamination in the oil.

Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

SAMPLE INFORMATION

	method	limit/base	current	history1	history2
Sample Number	Client Info		WC0939812	WC0939811	---
Sample Date	Client Info		31 May 2024	31 May 2024	---
Machine Age	hrs	Client Info	20653	36095	---
Oil Age	hrs	Client Info	20653	3065	---
Oil Changed		Client Info	Filtered	Changed	---
Sample Status			NORMAL	NORMAL	---

WEAR METALS

	method	limit/base	current	history1	history2
PQ	ASTM D8184*		0	0	---
Iron	ppm	ASTM D5185(m) >60	15	0	---
Chromium	ppm	ASTM D5185(m) >4	0	0	---
Nickel	ppm	ASTM D5185(m)	0	0	---
Titanium	ppm	ASTM D5185(m)	0	0	---
Silver	ppm	ASTM D5185(m)	0	0	---
Aluminum	ppm	ASTM D5185(m) >5	0	0	---
Lead	ppm	ASTM D5185(m) >10	0	0	---
Copper	ppm	ASTM D5185(m) >30	<1	0	---
Tin	ppm	ASTM D5185(m) >15	0	0	---
Antimony	ppm	ASTM D5185(m)	0	0	---
Vanadium	ppm	ASTM D5185(m)	0	0	---
Beryllium	ppm	ASTM D5185(m)	0	0	---
Cadmium	ppm	ASTM D5185(m)	0	0	---

ADDITIVES

	method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185(m)	<1	0	---
Barium	ppm	ASTM D5185(m)	2	3	---
Molybdenum	ppm	ASTM D5185(m)	0	0	---
Manganese	ppm	ASTM D5185(m)	0	0	---
Magnesium	ppm	ASTM D5185(m)	0	0	---
Calcium	ppm	ASTM D5185(m)	<1	0	---
Phosphorus	ppm	ASTM D5185(m)	0	0	---
Zinc	ppm	ASTM D5185(m)	10	1	---
Sulfur	ppm	ASTM D5185(m)	33	13	---
Lithium	ppm	ASTM D5185(m)	<1	<1	---

CONTAMINANTS




	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185(m) >50	<1	0	---
Sodium	ppm	ASTM D5185(m)	1	<1	---
Potassium	ppm	ASTM D5185(m) >20	<1	<1	---
Water	%	ASTM D6304* >0.1	0.00	0.00	---
ppm Water	ppm	ASTM D6304* >1000	0	0	---

FLUID DEGRADATION

	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D974*	0.01	0.00	---




OIL ANALYSIS REPORT








VISUAL	method	limit/base	current	history1	history2
White Metal	scalar	Visual*	NONE	NONE	---
Yellow Metal	scalar	Visual*	NONE	NONE	---
Precipitate	scalar	Visual*	NONE	NONE	---
Silt	scalar	Visual*	NONE	NONE	---
Debris	scalar	Visual*	NONE	NONE	---
Sand/Dirt	scalar	Visual*	NONE	NONE	VLITE
Appearance	scalar	Visual*	NORML	NORML	---
Odor	scalar	Visual*	NORML	NORML	---
Emulsified Water	scalar	Visual*	>0.1	NEG	---
Free Water	scalar	Visual*		NEG	---

FLUID PROPERTIES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D7279(m)	73	68.2	66.4

SAMPLE IMAGES	method	limit/base	current	history1	history2
---------------	--------	------------	---------	----------	----------



GRAPHS



Laboratory : WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9
Sample No. : WC0939812 **Received** : 11 Jun 2024
Lab Number : 02641153 **Tested** : 12 Jun 2024
Unique Number : 5798692 **Diagnosed** : 12 Jun 2024 - Wes Davis
Test Package : IND 2 (Additional Tests: KF)

CIMCO Refrigeration
 1551 Corporate Drive
 Burlington, ON
 CA L7L 6M3
 Contact: DAVID PARISE
 DPARISE@ToROMONT.COM
 T: (416)465-7581
 F: (416)465-8815

To discuss this sample report, contact Customer Service at 1-800-268-2131.
 Test denoted (*) outside scope of accreditation, (m) method modified, (e) tested at external lab.
 Validity of results and interpretation are based on the sample and information as supplied.