




OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL



Area
BD SHOP
 Machine Id
200304
 Component
Diesel Engine
 Fluid
TEST OIL GOLD 4 (40 LTR)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

SAMPLE INFORMATION

	method	limit/base	current	history1	history2
Sample Number	Client Info		WC0926283	WC0926282	WC0926295
Sample Date	Client Info		10 Jun 2024	10 Jun 2024	30 May 2024
Machine Age	kms	Client Info	162823	162822	155421
Oil Age	kms	Client Info	1	59904	52503
Oil Changed	Client Info		Changed	Not Changd	Not Changd
Sample Status			NORMAL	NORMAL	NORMAL

CONTAMINATION

	method	limit/base	current	history1	history2
Fuel	WC Method	>3.0	<1.0	<1.0	<1.0
Water	WC Method	>0.2	NEG	NEG	NEG

WEAR METALS

	method	limit/base	current	history1	history2	
Iron	ppm	ASTM D5185(m)	>120	2	23	22
Chromium	ppm	ASTM D5185(m)	>20	0	<1	<1
Nickel	ppm	ASTM D5185(m)	>5	0	2	2
Titanium	ppm	ASTM D5185(m)	>2	0	0	0
Silver	ppm	ASTM D5185(m)	>2	0	0	0
Aluminum	ppm	ASTM D5185(m)	>20	<1	4	4
Lead	ppm	ASTM D5185(m)	>40	0	<1	1
Copper	ppm	ASTM D5185(m)	>330	15	60	55
Tin	ppm	ASTM D5185(m)	>15	0	1	1
Antimony	ppm	ASTM D5185(m)		0	0	0
Vanadium	ppm	ASTM D5185(m)		0	0	0
Beryllium	ppm	ASTM D5185(m)		0	0	0
Cadmium	ppm	ASTM D5185(m)		0	0	0

ADDITIVES

	method	limit/base	current	history1	history2	
Boron	ppm	ASTM D5185(m)	1	1	2	2
Barium	ppm	ASTM D5185(m)	0	0	0	0
Molybdenum	ppm	ASTM D5185(m)	60	58	63	62
Manganese	ppm	ASTM D5185(m)	0	0	<1	<1
Magnesium	ppm	ASTM D5185(m)	950	941	971	933
Calcium	ppm	ASTM D5185(m)	980	996	1070	1072
Phosphorus	ppm	ASTM D5185(m)	1100	961	909	900
Zinc	ppm	ASTM D5185(m)	1150	1079	1159	1125
Sulfur	ppm	ASTM D5185(m)	2600	2466	2052	2031
Lithium	ppm	ASTM D5185(m)		<1	<1	<1

CONTAMINANTS


	method	limit/base	current	history1	history2	
Silicon	ppm	ASTM D5185(m)	>25	3	6	4
Sodium	ppm	ASTM D5185(m)		11	16	2
Potassium	ppm	ASTM D5185(m)	>20	23	43	9
Glycol	%	ASTM D7922*		0.0	0.0	NEG

INFRA-RED


	method	limit/base	current	history1	history2	
Soot %	%	ASTM D7844*	>4	0	0.5	0.5
Nitration	Abs/cm	ASTM D7624*	>20	4.7	9.5	9.8
Nitration(Diff)	Abs/cm	ASTM E2412*	< 25	0.8	11.1	11.6
Sulfation	Abs.1mm	ASTM D7415*	>30	17.8	21.7	21.6
Sulfation(Diff)	Abs/cm	ASTM E2412*		0	6.1	5.8




OIL ANALYSIS REPORT



FLUID DEGRADATION	method	limit/base	current	history1	history2	
Oxidation	Abs./1mm	ASTM D7414*	>25	13.0	17.8	18.1
Oxidation(Diff)	Abs/cm	ASTM E2412*	< 25	1	11.8	11.6
Base Number (BN)	mg KOH/g	ASTM D2896*	9.5	9.59	7.87	7.99













VISUAL	method	limit/base	current	history1	history2	
Emulsified Water	scalar	Visual*	>0.2	NEG	NEG	NEG
Free Water	scalar	Visual*		NEG	NEG	NEG



FLUID PROPERTIES	method	limit/base	current	history1	history2	
Visc @ 100°C	cSt	ASTM D7279(m)	15.3	14.9	12.8	13.0

GRAPHS



Laboratory : WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9
Sample No. : WC0926283
Lab Number : 02641596
Unique Number : 5799135
Test Package : MOB 2 (Additional Tests: FT-IR(Diff), Glycol)

WFR Technical Services
 5389 Riverside Drive
 Burlington, ON
 CA L7L 3Y1
 Contact: William Ridley
 wfr.technical.services@gmail.com

To discuss this sample report, contact Customer Service at 1-800-268-2131.
 Test denoted (*) outside scope of accreditation, (m) method modified, (e) tested at external lab.
 Validity of results and interpretation are based on the sample and information as supplied.