

OIL ANALYSIS REPORT

Sample Rating Trend



Area unassigned TURBOFLO XL 32

Reference New (Unused) Oil Fluid PETRO CANADA TURBOFLO XL32 (--- GAL)

DIAGNOSIS

Recommendation

This is the baseline readout on this new (unused) oil. The fluid is suitable for service.

Contamination

The system cleanliness is acceptable for your target ISO 4406 cleanliness code. There is no indication of any contamination in the new (unused) oil.


Fluid Condition


The AN level is acceptable for this fluid. The condition of the oil is suitable for service.


SAMPLE INFORM	1ATION	method	limit/base	current	history1	history2
Sample Number		Client Info		WC943382		
Sample Date		Client Info		13 Jun 2024		
Machine Age	hrs	Client Info		0		
Oil Age	hrs	Client Info		0		
Oil Changed		Client Info		N/A		
Sample Status				NORMAL		
CONTAMINATION	١	method	limit/base	current	history1	history2
Water		WC Method		NEG		
WEAR METALS		method	limit/base	current	history1	history2
PQ		ASTM D8184*		0		
Iron	ppm	ASTM D5185(m)	>5	0		
Chromium	ppm	ASTM D5185(m)	>5	0		
Nickel	ppm	ASTM D5185(m)	>5	0		
Titanium	ppm	ASTM D5185(m)		0		
Silver	ppm	ASTM D5185(m)	>5	0		
Aluminum	ppm	ASTM D5185(m)	>5	0		
Lead	ppm	ASTM D5185(m)	>5	0		
Copper	ppm	ASTM D5185(m)	>5	0		
Tin	ppm	ASTM D5185(m)	>5	0		
Antimony	ppm	ASTM D5185(m)		0		
Vanadium	ppm	ASTM D5185(m)		0		
Beryllium	ppm	ASTM D5185(m)		0		
Cadmium	ppm	ASTM D5185(m)		0		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185(m)	0	0		
Barium	ppm	ASTM D5185(m)	0	0		
Molybdenum	ppm	ASTM D5185(m)	0	0		
Manganese	ppm	ASTM D5185(m)	0	0		
Magnesium	ppm	ASTM D5185(m)	0	<1		
Calcium	ppm	ASTM D5185(m)	0	0		
Phosphorus	ppm	ASTM D5185(m)	5	<1		
Zinc	ppm	ASTM D5185(m)	0	<1		
Sulfur	ppm	ASTM D5185(m)	750	633		
Lithium	ppm	ASTM D5185(m)		<1		
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185(m)	>15	0		
Sodium	ppm	ASTM D5185(m)		0		
Potassium	ppm	ASTM D5185(m)	>20	0		
INFRA-RED		method	limit/base	current	history1	history2
Soot %	%	ASTM D7844*		0		
Nitration	Abs/cm	ASTM D7624*		1.9		
Sulfation	Abs/.1mm	ASTM D7415*		10.8		




OIL ANALYSIS REPORT










FLUID CLEANLIN		ام م داخم میں			histowed.	la la tarre 10
FLUID GLEANLIN	IESS	method	limit/base	current	history1	history2
Particles >4µm		ASTM D7647	>5000	546		
Particles >6µm		ASTM D7647	>1300	152		
Particles >14µm		ASTM D7647	>160	12		
Particles >21µm		ASTM D7647	>40	4		
Particles >38µm		ASTM D7647	>10	1		
Particles >71µm		ASTM D7647	>3	0		
Oil Cleanliness		ISO 4406 (c)	>19/17/14	16/14/11		
FLUID DEGRADA	TION	method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	ASTM D7414*		1.8		
Acid Number (AN)	mg KOH/g	ASTM D974*	0.04	0.03		
VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	Visual*	NONE	NONE		
Yellow Metal	scalar	Visual*	NONE	NONE		
Precipitate	scalar	Visual*	NONE	NONE		
Silt	scalar	Visual*	NONE	NONE		
Debris	scalar	Visual*	NONE	NONE		
Sand/Dirt	scalar	Visual*	NONE	NONE		
Appearance	scalar	Visual*	NORML	NORML		
Odor	scalar	Visual*	NORML	NORML		
Emulsified Water	scalar	Visual*		NEG		
Free Water	scalar	Visual*		NEG		
FLUID PROPERT	IES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D7279(m)	33.86	33.8		
Visc @ 100°C	cSt	ASTM D7279(m)	5.60	5.7		
Viscosity Index (VI)	Scale	ASTM D2270*	101	108		
SAMPLE IMAGES		method	limit/base	current	history1	history2





Report Id: OPGBAT [WCAMIS] 02641955 (Generated: 06/17/2024 14:10:07) Rev: 1

Contact/Location: Abbas Eskandari - OPGBAT Page 2 of 2