



# OIL ANALYSIS REPORT

Sample Rating Trend



WATER



Area

**DOMTAR 321-724-1 [GTT224-445 DOMTAR]**

Machine Id

**TRANE DOMTAR 321-724-1**

Component

**Chiller**

Fluid

**TRANE 0078 (--- GAL)**

## DIAGNOSIS

### Recommendation

If not recently done change any filter driers to reduce moisture level. Resample at the next service interval to monitor. Please specify the component make and model with your next sample.

### Wear

All component wear rates are normal.

### Contamination

The elevated moisture content is associated with POE oils which are hygroscopic, and can absorb moisture from sampling and processing.

### Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

## SAMPLE INFORMATION

	method	limit/base	current	history1	history2
Sample Number	Client Info		<b>GTT0003263</b>	---	---
Sample Date	Client Info		<b>30 May 2024</b>	---	---
Machine Age	hrs	Client Info	<b>0</b>	---	---
Oil Age	hrs	Client Info	<b>0</b>	---	---
Oil Changed	Client Info		<b>N/A</b>	---	---
Sample Status			<b>ATTENTION</b>	---	---

## WEAR METALS

	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185(m)	>8	<1	---
Chromium	ppm	ASTM D5185(m)	>2	0	---
Nickel	ppm	ASTM D5185(m)		<1	---
Titanium	ppm	ASTM D5185(m)		0	---
Silver	ppm	ASTM D5185(m)	>2	0	---
Aluminum	ppm	ASTM D5185(m)	>3	<1	---
Lead	ppm	ASTM D5185(m)	>2	0	---
Copper	ppm	ASTM D5185(m)	>8	<1	---
Tin	ppm	ASTM D5185(m)	>4	0	---
Antimony	ppm	ASTM D5185(m)		0	---
Vanadium	ppm	ASTM D5185(m)		0	---
Beryllium	ppm	ASTM D5185(m)		0	---
Cadmium	ppm	ASTM D5185(m)		0	---

## ADDITIVES

	method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185(m)		<1	---
Barium	ppm	ASTM D5185(m)		0	---
Molybdenum	ppm	ASTM D5185(m)		0	---
Manganese	ppm	ASTM D5185(m)		0	---
Magnesium	ppm	ASTM D5185(m)		<1	---
Calcium	ppm	ASTM D5185(m)		0	---
Phosphorus	ppm	ASTM D5185(m)		<b>750</b>	---
Zinc	ppm	ASTM D5185(m)		<1	---
Sulfur	ppm	ASTM D5185(m)		<b>211</b>	---
Lithium	ppm	ASTM D5185(m)		<1	---

## CONTAMINANTS

	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185(m)	>15	<b>26</b>	---
Sodium	ppm	ASTM D5185(m)		0	---
Potassium	ppm	ASTM D5185(m)	>20	0	---
ppm Water	ppm	ASTM D6304*	>100	<b>344</b>	---



## FLUID DEGRADATION

	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D974*		<b>0.01</b>	---

# OIL ANALYSIS REPORT

VISUAL	method	limit/base	current	history1	history2
White Metal	scalar	Visual*	NONE	<b>NONE</b>	---
Yellow Metal	scalar	Visual*	NONE	<b>NONE</b>	---
Precipitate	scalar	Visual*	NONE	<b>NONE</b>	---
Silt	scalar	Visual*	NONE	<b>NONE</b>	---
Debris	scalar	Visual*	NONE	<b>NONE</b>	---
Sand/Dirt	scalar	Visual*	NONE	<b>NONE</b>	---
Appearance	scalar	Visual*	NORML	<b>NORML</b>	---
Odor	scalar	Visual*	NORML	<b>NORML</b>	---

FLUID PROPERTIES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D7279(m)	32	<b>28.8</b>	---

SAMPLE IMAGES	method	limit/base	current	history1	history2
Color				no image	no image
Bottom				no image	no image

## GRAPHS



**Sample No.** : GTT0003263  
**Lab Number** : 02642216  
**Unique Number** : 5799755  
**Test Package** : IND 2 ( Additional Tests: KV40 )  
**Received** : 14 Jun 2024  
**Tested** : 24 Jun 2024  
**Diagnosed** : 24 Jun 2024 - Bill Quesnel

To discuss this sample report, contact Customer Service at 1-905-847-9300 Ext 26.

Test denoted (\*) outside scope of accreditation, (m) method modified, (e) tested at external lab.

Damages: Seller shall in no event be liable for special, incidental, or consequential damages, of a commercial nature, resulting from any cause.

**Bridair Inc.**  
 4704 boul Bertrand  
 Rock Forest, QC  
 CA J1N 2B1  
 Contact: Service Manager

T:  
F: